




PB-PBS\_SG225\_LEADSULFIDE @ 1200.00K  
Thermal cross sections




PB-PBS\_SG225\_LEADSULFIDE @ 1200.00K  
Thermal mubar




PB-PBS\_SG225\_LEADSULFIDE @ 1200.00K  
Thermal ebar




PB-PBS\_SG225\_LEADSULFIDE @ 1200.00K  
thermal inelastic




PB-PBS\_SG225\_LEADSULFIDE @ 1200.00K  
thermal inelastic




PB-PBS\_SG225\_LEADSULFIDE @ 1200.00K  
thermal inelastic



PB-PBS\_SG225\_LEADSULFIDE @ 1200.00K  
thermal inelastic




PB-PBS\_SG225\_LEADSULFIDE @ 1200.00K  
thermal inelastic for  $e = 1.012 \times 10^{-9}$  MeV







PB-PBS\_SG225\_LEADSULFIDE @ 1200.00K  
thermal inelastic for  $e = 1.417\text{E-}08$  MeV



PB-PBS\_SG225\_LEADSULFIDE @ 1200.00K  
thermal inelastic for e= 9.000E+08 MeV



PB-PBS\_SG225\_LEADSULFIDE @ 1200.00K  
thermal inelastic for  $e = 5.033\text{E-}07$  MeV



PB-PBS\_SG225\_LEADSULFIDE @ 1200.00K  
thermal inelastic for  $e = 4.070E-06$  MeV

