



O-CAOH2_SG164_CALCIUMHYDROXIDE @ 500.00K


Thermal cross sections




O-CAOH2_SG164_CALCIUMHYDROXIDE @ 500.00K
Thermal mubar




O-CAOH2_SG164_CALCIUMHYDROXIDE @ 500.00K
Thermal ebar




O-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K
thermal inelastic




O-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K
thermal inelastic




O-CAOH2_SG164_CALCIUMHYDROXIDE @ 500.00K
thermal inelastic




O-CAOH2_SG164_CALCULATED HYDROXIDE @ 500.00K
thermal inelastic




O-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K
thermal inelastic for e= 1.012E-09 MeV




O-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K
thermal inelastic for e= 1.417E-08 MeV



O-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K
thermal inelastic for e= 9.000E-08 MeV



O-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K
thermal inelastic for e= 5.033E-07 MeV



O-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K
thermal inelastic for e= 4.070E-06 MeV

