



H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 293.60K


Thermal cross sections




H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 293.60K
Thermal mubar




H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 293.60K
Thermal ebar




H-CAOH2_SG164_CALCULATED HYDROXIDE @ 293.60K
thermal inelastic




H-CAOH2_SG164_CALCULATED HYDROXIDE @ 293.60K
thermal inelastic




H-CAOH2_SG164_CALCULATED HYDROXIDE @ 293.60K
thermal inelastic




H-CAOH2_SG164_CALCULATED HYDROXIDE @ 293.60K
thermal inelastic




H-CAOH2_SG164_CALCULATED @ 293.60K
thermal inelastic for $e = 1.012 \times 10^{-9}$ MeV




H-CAOH2_SG164_CALCULATED @ 293.60K
thermal inelastic for $e = 1.417 \times 10^{-8}$ MeV



H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 293.60K
thermal inelastic for e= 9.000E-08 MeV



H-CAOH2_SG164_CALCULATED @ 293.60K
thermal inelastic for $e = 5.033 \times 10^{-7}$ MeV



H-CAOH2_SG164_CALCULATED @ 293.60K
thermal inelastic for $e = 4.070 \times 10^{-6}$ MeV

