




PB-PB_SG225_LEAD @ 200.00K
Thermal cross sections




PB-PB_SG225_LEAD @ 200.00K
Thermal mubar




PB-PB_SG225_LEAD @ 200.00K
Thermal ebar




PB-PB_SG225_LEAD @ 200.00K
thermal inelastic




PB-PB_SG225_LEAD @ 200.00K
thermal inelastic




PB-PB_SG225_LEAD @ 200.00K
thermal inelastic




PB-PB_SG225_LEAD @ 200.00K
thermal inelastic




PB-PB_SG225_LEAD @ 200.00K
thermal inelastic for e= 1.012E-09 MeV




PB-PB_SG225_LEAD @ 200.00K
thermal inelastic for $e = 1.417E-08$ MeV



PB-PB_SG225_LEAD @ 200.00K
thermal inelastic for $e = 9.000\text{E-}08$ MeV



PB-PB_SG225_LEAD @ 200.00K
thermal inelastic for $e = 5.033\text{E-}07$ MeV



PB-PB_SG225_LEAD @ 200.00K
thermal inelastic for e= 4.070E-06 MeV

