



H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K

Thermal cross sections




H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K
Thermal mubar




H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K


Thermal ebar




H-CAOH2_SG164_CALCULATED HYDROXIDE @ 500.00K
thermal inelastic




H-CAOH2_SG164_CALCULATED HYDROXIDE @ 500.00K
thermal inelastic




H-CAOH2_SG164_CALCULATED HYDROXIDE @ 500.00K
thermal inelastic




H-CAOH2_SG164_CALCULATED HYDROXIDE @ 500.00K
thermal inelastic




H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K
thermal inelastic for e= 1.012E-09 MeV




H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K
thermal inelastic for e= 1.417E-08 MeV



H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K
thermal inelastic for e= 9.000E-08 MeV



H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K
thermal inelastic for e= 5.033E-07 MeV



H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 500.00K
thermal inelastic for e= 4.070E-06 MeV

