




CA-CAOH2_SG164_CALCICIUMHYDROXIDE @ 700.00K
Thermal cross sections




CA-CAOH2_SG164_CALCIIUMHYDROXIDE @ 700.00K
Thermal mubar




CA-CAOH2_SG164_CALCICIUMHYDROXIDE @ 700.00K
Thermal ebar




CA-CAOH2_SG164_CALCULATED @ 700.00K
thermal inelastic




CA-CAOH2_SG164_CALCULATED
thermal inelastic




CA-CAOH2_SG164_CALCULATED HYDROXIDE @ 700.00K
thermal inelastic




CA-CAOH2_SG164_CALCULATED @ 700.00K
thermal inelastic




CA-CAOH2_SG164_CALCULATED @ 700.00K
thermal inelastic for $e = 1.012 \times 10^{-9}$ MeV




CA-CAOH2_SG164_CALCULUMHYDROXIDE @ 700.00K
thermal inelastic for e= 1.417E-08 MeV



CA-CAOH2_SG164_CALCULATED @ 700.00K
thermal inelastic for $e = 9.000E-08$ MeV



CA-CAOH2_SG164_CALCULATED HYDROXIDE @ 700.00K
thermal inelastic for $e = 5.033 \times 10^{-7}$ MeV



CA-CAOH2_SG164_CALCULUMHYDROXIDE @ 700.00K
thermal inelastic for e= 4.070E-06 MeV

