




S-PBS\_SG225\_LEADSULFIDE @ 20.00K  
Thermal cross sections




S-PBS\_SG225\_LEADSULFIDE @ 20.00K  
Thermal mubar




S-PBS\_SG225\_LEADSULFIDE @ 20.00K  
Thermal ebar




S-PBS\_SG225\_LEADSULFIDE @ 20.00K  
thermal inelastic




S-PBS\_SG225\_LEADSULFIDE @ 20.00K  
thermal inelastic




S-PBS\_SG225\_LEADSULFIDE @ 20.00K  
thermal inelastic



S-PBS\_SG225\_LEADSULFIDE @ 20.00K  
thermal inelastic




S-PBS\_SG225\_LEADSULFIDE @ 20.00K  
thermal inelastic for e= 1.012E-09 MeV







S-PBS\_SG225\_LEADSULFIDE @ 20.00K  
thermal inelastic for  $e = 1.417\text{E-}08$  MeV



S-PBS\_SG225\_LEADSULFIDE @ 20.00K  
thermal inelastic for e= 9.000E-08 MeV



S-PBS\_SG225\_LEADSULFIDE @ 20.00K  
thermal inelastic for  $e = 5.033\text{E-}07$  MeV



S-PBS\_SG225\_LEADSULFIDE @ 20.00K  
thermal inelastic for  $e = 4.070\text{E-}06$  MeV

