



H-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K

Thermal cross sections




H-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
Thermal mubar




H-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K


Thermal ebar




H-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic




H-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic




H-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic




H-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic




H-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic for e= 1.012E-09 MeV




H-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic for $e = 1.417\text{E-}08$ MeV



H-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic for $e = 9.000\text{E-}08$ MeV



H-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic for $e = 5.033\text{E-}07$ MeV



H-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic for $e = 4.070E-06$ MeV

