




O-CAO\_SG225\_CALCIUMOXIDE @ 77.00K  
Thermal cross sections




O-CAO\_SG225\_CALCIUMOXIDE @ 77.00K  
Thermal mubar




O-CAO\_SG225\_CALCIUMOXIDE @ 77.00K  
Thermal ebar




O-CAO\_SG225\_CALCIUMOXIDE @ 77.00K  
thermal inelastic




O-CAO\_SG225\_CALCIUMOXIDE @ 77.00K  
thermal inelastic




O-CAO\_SG225\_CALCIUMOXIDE @ 77.00K  
thermal inelastic



O-CAO\_SG225\_CALCIIUMOXIDE @ 77.00K  
thermal inelastic




O-CAO\_SG225\_CALCIUMOXIDE @ 77.00K  
thermal inelastic for e= 1.012E-09 MeV







O-CAO\_SG225\_CALCIUMOXIDE @ 77.00K  
thermal inelastic for e= 1.417E-08 MeV



O-CAO\_SG225\_CALCIUMOXIDE @ 77.00K  
thermal inelastic for e= 9.000E-08 MeV



O-CAO\_SG225\_CALCIUMOXIDE @ 77.00K  
thermal inelastic for e= 5.033E-07 MeV



O-CAO\_SG225\_CALCIUMOXIDE @ 77.00K  
thermal inelastic for e= 4.070E-06 MeV

