




S-PBS\_SG225\_LEADSULFIDE @ 1300.00K  
Thermal cross sections




S-PBS\_SG225\_LEADSULFIDE @ 1300.00K  
Thermal mubar




S-PBS\_SG225\_LEADSULFIDE @ 1300.00K  
Thermal ebar




S-PBS\_SG225\_LEADSULFIDE @ 1300.00K  
thermal inelastic




S-PBS\_SG225\_LEADSULFIDE @ 1300.00K  
thermal inelastic




S-PBS\_SG225\_LEADSULFIDE @ 1300.00K  
thermal inelastic



S-PBS\_SG225\_LEADSULFIDE @ 1300.00K  
thermal inelastic




S-PBS\_SG225\_LEADSULFIDE @ 1300.00K  
thermal inelastic for e= 1.012E-09 MeV







S-PBS\_SG225\_LEADSULFIDE @ 1300.00K  
thermal inelastic for e= 1.417E-08 MeV



S-PBS\_SG225\_LEADSULFIDE @ 1300.00K  
thermal inelastic for  $e = 9.000 \times 10^{-8}$  MeV



S-PBS\_SG225\_LEADSULFIDE @ 1300.00K  
thermal inelastic for e= 5.033E-07 MeV



S-PBS\_SG225\_LEADSULFIDE @ 1300.00K  
thermal inelastic for e= 4.070E-06 MeV

