




NA-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
Thermal cross sections




NA-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
Thermal mubar




NA-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
Thermal ebar




NA-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic




NA-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic




NA-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic




NA-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic




NA-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic for e= 1.012E-09 MeV




NA-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic for e= 1.417E-08 MeV



NA-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic for e= 9.000E-08 MeV



NA-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic for $e = 5.033\text{E-}07$ MeV



NA-NAOH_SG63_SODIUMHYDROXIDE @ 77.00K
thermal inelastic for e= 4.070E-06 MeV

