




O-NAOH_SG63_SODIUMHYDROXIDE @ 293.60K
Thermal cross sections




O-NAOH_SG63_SODIUMHYDROXIDE @ 293.60K
Thermal mubar




O-NAOH_SG63_SODIUMHYDROXIDE @ 293.60K
Thermal ebar




O-NAOH_SG63_SODIUMHYDROXIDE @ 293.60K
thermal inelastic




O-NAOH_SG63_SODIUMHYDROXIDE @ 293.60K
thermal inelastic




O-NAOH_SG63_SODIUMHYDROXIDE @ 293.60K
thermal inelastic




O-NAOH_SG63_SODIUMHYDROXIDE @ 293.60K
thermal inelastic




O-NAOH_SG63_SODIUMHYDROXIDE @ 293.60K
thermal inelastic for e= 1.012E-09 MeV




O-NAOH_SG63_SODIUMHYDROXIDE @ 293.60K
thermal inelastic for $e = 1.417\text{E-}08$ MeV



O-NAOH_SG63_SODIUMHYDROXIDE @ 293.60K
thermal inelastic for e= 9.000E-08 MeV



O-NAOH_SG63_SODIUMHYDROXIDE @ 293.60K
thermal inelastic for $e = 5.033\text{E-}07$ MeV



O-NAOH_SG63_SODIUMHYDROXIDE @ 293.60K
thermal inelastic for $e = 4.070E-06$ MeV

