



H-CAOH2_SG164_CALCIUMHYDROXIDE @ 100.00K


Thermal cross sections




H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 100.00K
Thermal mubar




H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 100.00K
Thermal ebar




H-CAOH2_SG164_CALCULATED HYDROXIDE @ 100.00K
thermal inelastic




H-CAOH2_SG164_CALCULATED HYDROXIDE @ 100.00K
thermal inelastic




H-CAOH2_SG164_CALCULATED HYDROXIDE @ 100.00K
thermal inelastic




H-CAOH2_SG164_CALCULATED HYDROXIDE @ 100.00K
thermal inelastic




H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 100.00K
thermal inelastic for e= 1.012E-09 MeV




H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 100.00K
thermal inelastic for e= 1.417E-08 MeV



H-CAOH2_SG164_CALCULATED HYDROXIDE @ 100.00K
thermal inelastic for $e = 9.000\text{E-}08$ MeV



H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 100.00K
thermal inelastic for e= 5.033E-07 MeV



H-CAOH2_SG164_CALCIIUMHYDROXIDE @ 100.00K
thermal inelastic for e= 4.070E-06 MeV

