




O-MGOH2_SG164_MAGNESIUMHYDROXIDE @ 77.00K
Thermal cross sections




O-MGOH2_SG164_MAGNESIUMHYDROXIDE @ 77.00K
Thermal mubar




O-MGOH2_SG164_MAGNESIUMHYDROXIDE @ 77.00K
Thermal ebar




O-MGOH2_SG164_MAGNESIUMHYDROXIDE @ 77.00K
thermal inelastic




O-MGOH2_SG164_MAGNESIUMHYDROXIDE @ 77.00K
thermal inelastic




O-MGOH2_SG164_MAGNESIUMHYDROXIDE @ 77.00K
thermal inelastic




O-MGOH2_SG164_MAGNESIUMHYDROXIDE @ 77.00K
thermal inelastic




O-MGOH2_SG164_MAGNESIUMHYDROXIDE @ 77.00K
thermal inelastic for e= 1.012E-09 MeV




O-MGOH2_SG164_MAGNESIUMHYDROXIDE @ 77.00K
thermal inelastic for e= 1.417E-08 MeV



O-MGOH2_SG164_MAGNESIUMHYDROXIDE @ 77.00K
thermal inelastic for e= 9.000E-08 MeV



O-MGOH2_SG164_MAGNESIUMHYDROXIDE @ 77.00K
thermal inelastic for e= 5.033E-07 MeV



O-MGOH2_SG164_MAGNESIUMHYDROXIDE @ 77.00K
thermal inelastic for e= 4.070E-06 MeV

