

	BOROSIL RENEWABLES LIMITED		DOC. NO: ROM/L4/009
			ISSUE NO. / DATE: 01/08.04.2026
	INSPECTION PLAN FOR ROLLER		REV. NO: 00
			REV. DATE: --

A POST-LASER ENGRAVING INSPECTION					
#	Characteristics to be checked		Test Method / Measuring instrument	Specification	Remarks
1	Visual Inspection, Check for Any:	Damage mark	Visually	The roller face surface should be free from any line/damage/scratch /crack or other issues.	No presence of any line, scratch or damage
		Dent marks			
		Cracks			
		Visible lines			
		Other issues.			
2	Top Roller Ra		Surface roughness tester	8 – 9 µm	λc = 0.8 & N = 5
3	Bottom Roller Ra		Surface roughness tester	12 – 17 µm	λc = 0.8 & N = 5
4	Depth of the pattern		Depth inspection equipment	> 100 µm	

Prepared By	Reviewed By	Approved By	Page 1 of 3
Mr. Ripal Rana Sr. Executive	Mr. Prabhakar P HOD – Hotend	Dr. Ajay Singh Plant Head	

	BOROSIL RENEWABLES LIMITED	DOC. NO: ROM/L4/009
		ISSUE NO. / DATE: 01/08.04.2026
	INSPECTION PLAN FOR ROLLER	REV. NO: 00
		REV. DATE: --

B	PRE DISPATCH INSPECTION			
#	Characteristics to be checked	Test Method / Measuring instrument	Specification	Remarks
1	Roller Diameter	Vernier Caliper	SG#1: 260/270 $\pm$ 6 mm SG#2: 340 $\pm$ 6 mm SG#3: 400 $\pm$ 6 mm	
2	Roller Face length	Measuring tape	SG#1: 2800 mm SG#2: 2800 mm SG#3: 3000 mm	
3	Visual Condition, Check for Any damage, Dent, Crack, visible lines.	Visually	No presence of any line, scratch or damage	
4	Top Roller Ra	Surface roughness tester	8 – 9 μ m	$\lambda_c = 0.8$ & N = 5
5	Bottom Roller Ra	Surface roughness tester	12 – 17 μ m	$\lambda_c = 0.8$ & N = 5
6	Roller Run out	Run out gauge	< 0.1 mm	
7	DU shaft/journal roughness	Surface roughness tester	< 0.4 μ m	$\lambda_c = 2.5$ & N = 2
8	DU Shaft diameter (for 400mm & 340mm Roller)	Vernier Caliper	249.93 to 250.00 mm	
9	DU Shaft diameter (for 260mm & 270 mm Roller)	Vernier Caliper	209.93 to 210.00 mm	
10	The DU shaft mounting position	Visually	Should be perfectly round fit.	No Oval
11	Circlip grooves	Visually	Should be damage free	
12	Tapped holes threads	Visually & physically	Should be damage free	
13	Depth of the pattern	Depth inspection equipment	> 100 μ m	
14	Chrome coating layer thickness	Elcometer 456 Coating Thickness Gauge	> 60 μ m	

Prepared By	Reviewed By	Approved By	Page 2 of 3
Mr. Ripal Rana Sr. Executive	Mr. Prabhakar P HOD – Hotend	Dr. Ajay Singh Plant Head	

	BOROSIL RENEWABLES LIMITED	DOC. NO: ROM/L4/009
		ISSUE NO. / DATE: 01/08.04.2026
	INSPECTION PLAN FOR ROLLER	REV. NO: 00
		REV. DATE: --

Revision History:

Revision No.	Description of Change made	Date	Approved by
00	Initial release	04.08.2026	Plant Head

Prepared By	Reviewed By	Approved By	Page 3 of 3
Mr. Ripal Rana Sr. Executive	Mr. Prabhakar P HOD – Hotend	Dr. Ajay Singh Plant Head	