


PRECIPITATED AMORPHOUS SILICA · PEARL GRADE

Highly Dispersible Silica from Rice Husk Ash


A 98% SiO₂ high-structure white filler, precipitated entirely from agricultural waste. Reinforcement performance for rubber compounding, without the smelt-route carbon of sand-and-soda silica.



STRUCTURE & MICROPOROSITY, M²/G



BET / CTAB RATIO



A BET/CTAB ratio of 1.23 — close to unity — means nitrogen and CTAB see nearly the same surface: the aggregate is open and silane-accessible rather than locked behind micropores. That is the structure rubber compounding look for in a tread-grade silica.

98%

SiO₂ PURITY

177

BET SURFACE, M²/G

>95%

WHITENESS


100%

AGRI-WASTE



PROCESS ROUTE

RICE HUSK ASH → GRADED SILICA + BIOCHAR



enquiries@ecosil.org · +91 87907 60055

Typical properties



Values are typical and may vary marginally by production batch. Each shipment ships against a batch certificate of analysis.

PROPERTY	UNIT	TYPICAL VALUE	METHOD
Silicon dioxide (SiO ₂) purity	% w/w	98	ISO 3262-19
BET specific surface area	m ² /g	176 – 183	ISO 9277
CTAB surface area	m ² /g	134 – 144	ISO 5794-1
BET / CTAB ratio (structure openness)	—	1.2	Calculated
Moisture	% w/w	5 – 7	ISO 787-2
pH, aqueous suspension	—	5.0 – 7.5	ISO 787-9
Bulk density	g/l	213	ISO 787-11
Tapped density	g/l	234	ISO 787-11
Whiteness	%	> 95	ISO 787-25

Why the ash route

Conventional precipitated silica begins with quartz sand smelted with soda ash at furnace temperature. Ecosil starts from rice husk ash, in which the silica is already amorphous – extraction runs at modest temperature, so process energy and embedded carbon fall sharply and no quarried mineral is consumed. The residual carbon fraction leaves the plant as biochar rather than waste.

PEAK PROCESS TEMPERATURE, °C



FILTER-PRESS BANK · REACTOR VESSELS · SPRAY-DRYING TOWER



Ecosil India Pvt. Ltd.
CIN U24290AP2017PTC105320
GSTIN 37AAECE5515H1ZP

OFFICES

D.No. 9-13-45, Balaji Nagar, C.B.M
Compound, Visakhapatnam 530003,
Andhra Pradesh
Works: Madapam, Pothayyavalasa 532421

ENQUIRIES & SAMPLES

enquiries@ecosil.org
+91 87907 60055
ecosil.org

1 kg and 25 kg trial quantities on request