Two-pack epoxy primer, 80 % zinc in dry film — long-term steel protection

Anti-Corrosion Coatings · Model **HN-AC-201**

OVERVIEW

Two-pack chemically curing epoxy primer with up to 80 % metallic zinc in the dry film. Excellent corrosion resistance and abrasion resistance; also suitable as welding primer on blast-cleaned plate and as the anti-rust primer under fire-protection coatings.

TYPICAL APPLICATIONS

Long-term protective primer for steel in medium to severe corrosivity (C3–C5).

PHYSICAL & APPLICATION DATA

Binder / resin: Epoxy

Colour: Red-grey / grey

Mix ratio (base : hardener): 10 : 1 (by weight)

Pot life: 8 h (20 °C)

Flash point: 25 °C

Density: 2.3 kg/L

Volume solids: 49 %

Theoretical spreading rate: 12 m²/L @ 40 µm DFT

Drying (touch-dry / full cure): 1 h / 7 d (20 °C)

Recoating interval (min / max): 1 h – 7 d

Finish: Matt

Application methods: Airless spray · brush · conventional spray

Thinner (max, by method): brush 5–10 % · airless 10 % · spray 15 %

Cleaner: Matched HN epoxy thinner

SURFACE PREPARATION

Steel must be dry, free of loose paint, grease and dirt. Abrasive blast to Sa 2.5 (ISO 8501-1 / Swedish standard), surface profile Rugotest No.3 BN9a; remove dust and abrasives before coating. For special substrates consult our technical desk.

RECOMMENDED SYSTEM (HN CODES)

HN-AC-201 x1 coat(s) (0.10 L/m²)

HN-AC-302 x1 coat(s) (0.10 L/m²)

HN-AC-405 | HN-AC-607 x2 coat(s) (0.20 L/m²)

SAFETY

Flammable — keep away from heat and ignition; no smoking in the working area. Use only with adequate ventilation; avoid inhalation of vapours and spray mist; avoid skin and eye contact. Store in a cool, dry place. For professional use only.

Values quoted from the manufacturer's technical data sheet; confirm the batch TDS before specification.

© 2026 HONG NGUYEN. Values quoted from the manufacturer's technical data sheet; the batch TDS shipped with each order prevails.