Two-pack epoxy with micaceous iron oxide — the workhorse intermediate coat

Anti-Corrosion Coatings · Model **HN-AC-302**

OVERVIEW

Two-pack epoxy coating pigmented with micaceous iron oxide. Resistant to sea water, corrosion, impact, mineral oils, aliphatic hydrocarbons and many chemicals; laminar MIO platelets reinforce barrier protection.

TYPICAL APPLICATIONS

Primer / intermediate for epoxy systems on steel and concrete; quality intermediate and finish for bridges, car decks and structural steel buildings.

PHYSICAL & APPLICATION DATA

Binder / resin: Epoxy

Colour: Black / grey

Mix ratio (base : hardener): 3 : 1 (by volume) = 5.8 : 1 (by weight)

Pot life: 5 h (20 °C)

Flash point: 26 °C

Density: 1.6 kg/L

Volume solids: 48 %

Theoretical spreading rate: 10 m²/L @ 48 µm DFT

Drying (touch-dry / full cure): 4 h / 7 d (20 °C)

Recoating interval (min / max): 6 h – 5 d

Finish: Flat

Application methods: Airless spray · brush · conventional spray

Thinner (max, by method): brush 5–10 % · airless 5 % · spray 15 %

Cleaner: Matched HN epoxy thinner

SURFACE PREPARATION

Surface must be clean and free of grease and dirt. When used directly as an anti-rust primer, de-rust the steel first; as intermediate or topcoat, apply over a sound primed surface. Consult our technical desk for special substrates.

RECOMMENDED SYSTEM (HN CODES)

HN-AC-201 x1 coat(s) (0.10 L/m²)

HN-AC-302 x1 coat(s) (0.10 L/m²)

HN-AC-405 | HN-AC-607 x2 coat(s) (0.20 L/m²)

SAFETY

Flammable — keep away from heat and ignition; no smoking in the working area. Use only with adequate ventilation; avoid inhalation of vapours and spray mist; avoid skin and eye contact. Store in a cool, dry place. For professional use only.

Values quoted from the manufacturer's technical data sheet; confirm the batch TDS before specification.

© 2026 HONG NGUYEN. Values quoted from the manufacturer's technical data sheet; the batch TDS shipped with each order prevails.