Two-pack PU finish with gloss & colour retention, non-yellowing

Anti-Corrosion Coatings · Model **HN-AC-405**

OVERVIEW

Two-pack polyurethane finish with outstanding gloss and colour retention. Resistant to water, animal and vegetable oils, abrasion, impact and UV — for medium to severe corrosive environments. Non-yellowing chemical-resistant finish over epoxy primers/intermediates.

TYPICAL APPLICATIONS

Long-term decorative-protective finish on steel in severe environments; also on non-ferrous metal, concrete, cement, timber, pipework and GRP.

PHYSICAL & APPLICATION DATA

Binder / resin: Acrylic polyurethane

Colour: Wide colour range

Mix ratio (base : hardener): 9 : 1 (by volume) = 10 : 1 (by weight)

Pot life: 3 h (20 °C)

Flash point: 31 °C

Density: 1.2 kg/L

Volume solids: 42 %

Theoretical spreading rate: 10 m²/L @ 42 µm DFT

Drying (touch-dry / full cure): 5 h / 7 d (20 °C)

Recoating interval (min / max): 8 h – 7 d

Finish: Semi-gloss / gloss

Application methods: Airless spray · brush · conventional spray

Thinner (max, by method): brush 15–20 % · airless 5 % · spray 30 %

Cleaner: Matched HN PU thinner

SURFACE PREPARATION

Surface must be clean, dry and free of contaminants; apply over an appropriate primer / intermediate coat. Previously contaminated surfaces: high-pressure fresh-water wash and let dry before recoating.

RECOMMENDED SYSTEM (HN CODES)

HN-AC-201 x1 coat(s) (0.10 L/m²)

HN-AC-302 x1 coat(s) (0.10 L/m²)

HN-AC-405 x2 coat(s) (0.20 L/m²)

SAFETY

Flammable — keep away from heat and ignition; no smoking in the working area. Use only with adequate ventilation; avoid inhalation of vapours and spray mist; avoid skin and eye contact. Store in a cool, dry place. For professional use only.

Values quoted from the manufacturer's technical data sheet; confirm the batch TDS before specification.

Inquiries: hogoshi2023@gmail.com · WhatsApp +86 131 7420 8290 · OEM/ODM & colour matching on request
© 2026 HONG NGUYEN. Values quoted from the manufacturer's technical data sheet; the batch TDS shipped with each order prevails.