100 % solids self-leveling epoxy — seamless heavy-duty floors, 2–3 mm builds

Epoxy Floor Coatings · Model **HN-FL-101**

OVERVIEW

Solvent-free, self-leveling high-build epoxy for tough, seamless floors. Applied with a notched trowel / spiked roller to 2–3 mm; anti-static, anti-slip or orange-peel textures possible with adjusted mixes. Full cure 7 days; foot traffic after ~36 h.

TYPICAL APPLICATIONS

Floors under severe vehicle wear and chemical attack — factories, warehouses and parking decks.

PHYSICAL & APPLICATION DATA

Binder / resin: Self-leveling epoxy

Colour: Wide colour range

Mix ratio (base : hardener): base : hardener = 5 : 1 (by weight)

Volume solids: 100 %

Flash point: 100 °C

Density: 1.5 kg/L

Recommended DFT: 2–3 mm (WFT - DFT)

Drying (touch-dry / full cure): 24 h foot traffic / 7 d full cure (20 °C)

Recoating interval (min / max): 36 h – 3 d (20 °C)

Finish: Gloss

Application methods: Notched trowel / spiked roller

Cleaner: Matched HN epoxy thinner

SURFACE PREPARATION

Concrete must be fully cured and dry (moisture content < 10 %, pH < 10); remove laitance, dust, grease and efflorescence; repair and level with putty where required. New concrete walls: allow ~30 days before putty and paint.

RECOMMENDED SYSTEM (HN CODES)

HN-FL-503 sealer x1 coat(s) (0.10 L/m²)

epoxy mortar / putty x1 coat(s) (per spec)

HN-FL-101 x1 coat(s) (2–3 mm)

SAFETY

Flammable — keep away from heat and ignition; no smoking in the working area. Use only with adequate ventilation; avoid inhalation of vapours and spray mist; avoid skin and eye contact. Store in a cool, dry place. For professional use only.

Values quoted from the manufacturer's technical data sheet; confirm the batch TDS before specification.

© 2026 HONG NGUYEN. Values quoted from the manufacturer's technical data sheet; the batch TDS shipped with each order prevails.