Single-pack air-drying silicone HT paint — hot surfaces up to 550 °C

High-Temperature Coatings · Model **HN-HT-200**

OVERVIEW

Heat-resistant, single-pack, air-drying coating pigmented with aluminium paste; custom colours and temperature grades available on request. Note: the film becomes slightly thermoplastic with loss of gloss on heating — keep total DFT below ~75 µm and do not heat before the film is fully dry (24 h / 20 °C).

TYPICAL APPLICATIONS

Long-term protection of hot pipes, exhaust ducts, chimneys and other surfaces up to 550 °C; may serve as its own primer and finish.

PHYSICAL & APPLICATION DATA

Binder / resin: Heat-resistant silicone resin

Colour: Silver, black and other colours

Density: 1.1 kg/L

Flash point: 25 °C

Volume solids: 31 %

Theoretical spreading rate: 12 m²/L @ 25 µm DFT

Drying (touch-dry / full cure): 1 h / 24 h (20 °C)

Recoating interval (min / max): Not required

Finish: Semi-flat

Application methods: Airless spray · brush · conventional spray

Thinner (max, by method): airless 5 % · brush 10 % · spray 15 %

Cleaner: Matched HN silicone thinner

SURFACE PREPARATION

Remove grease with a suitable detergent and remove salts / dirt by high-pressure fresh water; abrasive blast to Sa 2.5 before application.

RECOMMENDED SYSTEM (HN CODES)

HN-HT-200 x1 coat(s) (0.08 L/m²)

SAFETY

Flammable — keep away from heat and ignition; no smoking in the working area. Use only with adequate ventilation; avoid inhalation of vapours and spray mist; avoid skin and eye contact. Store in a cool, dry place. For professional use only.

Values quoted from the manufacturer's technical data sheet; confirm the batch TDS before specification.

© 2026 HONG NGUYEN. Values quoted from the manufacturer's technical data sheet; the batch TDS shipped with each order prevails.