asianpaints

PRODUCT CODE 0006

Decoprime Premium Metal Primer

Asian Paints Decoprime Premium Metal Primer is a Red Oxide primer that can be used as an undercoat for ferrous metal substrates, which offers good rust protection for the substrate and assures strong adhesion of the paint film.

SOLVENT BASED

asianpaints
LEAD FREE* GUARANTEE

* All Asian Paints products contain no added Lead, Mercury, Arsenic or Chromium from April 2008.

PRODUCT BENEFITS

Asian Paints Decoprime Premium Metal Primer is based on synthetic resins and contains corrosion inhibiting plgments. It offers good corrosion resistance and hence serves as a good quality metal primer. It can be easily applied by brush or spray and dries hard to form a good adherent coating and is economical in use.

PRODUCT FEATURES

AVAILABLE PACKS

Shelf Life: 18 months from date of manufacture in original tightly closed containers away from direct sunlight and excessive heat.

COLOURS AVAILABLE

Red Oxide



*Please note: Decoprime Premium Metal Primer is an undercoat

COVERAGE

1 COAT

150 - 170 sq. ft/ltr**

**Actual coverage may vary from the quoted coverage due to factors such as method and condition of application and surface roughness

DRYING TIME TO RECOAT



After 8 hours

FINISH

MATT | LOW SHEEN | HIGH SHEEN | HIGH GLOSS

✓ SMOOTH

Refer to sheen levels in technical details

RECOMMENDED USAGE



Decoprime Premium Metal Primer can be used in ferrous substrates.

HOW TO APPLY

APPLICATION PROCESS

PRODUCT	CODE	THINNER	DILUTION %	APPLICATION VISCOSITY[1]	RECOATING PERIOD
STEP 1 SANDING SURFACE PREPARATION	SAND THE SURFACE WITH EMERY PAPER 180 AND WIPE CLEAN				
STEP 2 FIRST COAT ASIAN PAINTS DECOPRIME PREMIUM METAL PRIMER BRUSH/SPRAY	0006	MTO*	5 - 10	BRUSHING 40 - 45 SEC SPRAYING 20 - 25 SEC	8 HRS
STEP 3 SANDING	SAND LIGHTLY WITH EMERY PAPER 180 AND WIPE CLEAN				
STEP 4 ASIAN PAINTS KNIFING PASTE FILLER OPTIONAL	SMOOTHEN THE SURFACE BY FILLING DENTS WITH THIN COATS OF ASIAN PAINTS KNIFING PASTE FILLER. ALLOW IT TO DRY FOR 4 - 6 HOURS. SAND LIGHTLY WITH EMERY PAPER 180 AND WIPE CLEAN.				
STEP 5 SECOND COAT ASIAN PAINTS PREMIUM DECOPRIME METAL PRIMER BRUSHING & SPRAYING ON AREAS WHERE KPF IS APPLIED	0006	MTO*	5 - 10	BRUSHING 40 - 45 SEC SPRAYING 20 - 25 SEC	8 HRS
STEP 6 SANDING	SAND LIGHTLY WITH EMERY PAPER 320 BEFORE APPLICATION OF TOPCOATS.				

1. As Measured through Ford Cup FC B4 @ 30 Deg C. 2. Recoat period is quoted for 25°C and 50% Relative Humidity, these may vary under different conditions. * Mineral Turpentine Oil

ADDITIONAL INFORMATION

TECHNICAL DETAILS

a. Drying time: Surface dry not more than 1 hour. Hard dry - not more than 18 hours
b. Flash point: > 30°C [> 85° F]
c. Stability of thinned paint: To be used within 24 Hours

PRECAUTIONS

- This product is flammable.
- Do not apply when ambient temperature is less than 10°C or if the temperature might drop to this level within 4 hours of application.
- Work in a well-ventilated place. Wear protective clothing like overalls and gloves. Store the product at ambient conditions in well ventilated locations and away from source of ignition and fire. Do not over-thin or over- extend the brush.
- Avoid eye and skin contact. In case of eye and skin contact wash with plenty of clean water.
- Do not inhale or inject. In case of inhalation move to fresh air. Seek medical attention if symptoms persist in both the cases.
- Use protective equipment like rubber/polythene gloves, safety goggles/glasses and face mask while handling the paint.
- In case if settling is noticed, homogenize the material by mixing and use.

SAFETY FEATURES

- Kindly refer to the MSDS for Asian Paints Decoprime Premium Metal Primer which gives detailed information on safety measures while handling the paint, available on request.
- Store the container with the lid tightly closed in an upright position, in a cool, dry place.
- Keep out of reach of children and away from eatables.
- May be harmful if swallowed. In case of ingestion, seek immediate medical attention.
- Wear eye protection during application. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- In case of skin contact, immediately wash skin with soap and plenty of water. Get medical attention if irritation develops or persists.
- Do not breathe vapour or spray. It is recommended to wear suitable nose pad during sanding and surface preparation to avoid dust inhalation.
- Do not pour leftover paint down the drain or in water courses.
- In the event of spills, contain spillage using sand or earth.
- No added Lead, Mercury or Chromium compounds.
- Disposal in land filling and not in drain or any water channel.

Version No. VN01/05/2015