GALVANIZED STEEL WIRE EARTHWIRE / STAYWIRE / GUYWIRE / SPACER CABLE (GSW)

REF. SPECIFICATION -IS 2141

Sectional Area	Stranding		Diameter of EARTHWIRE	Weight	Rated Strength				
	No. of Wires	Individual wire diameter			Grade 1770	Grade 1570	Grade 1100	Grade 700	'Grade 450
mm²	No.	mm	mm	Kg/km	KN	KN	KN	KN	KN
23.38	3	3.15	6.79	-	40.10	35.60	24.90	15.90	10.20
31.17	4	3.15	7.60	-	52.40	46.50	32.60	20.70	13.30
2.01	4	0.80	2.40	-	5.50	4.90	3.40	2.20	1.40
4.91	4	1.25	3.75	-	13.50	12.00	8.40	5.40	3.40
3.14	4	1.00	4.80	-	22.20	19.70	13.80	8.80	5.60
12.57	4	2.00	6.00	-	34.70	30.80	21.60	13.70	8.80
27.59	7	2.24	6.72	-	43.50	38.60	27.00	17.20	11.10
34.36	7	2.50	7.50	-	54.20	48.10	33.70	21.40	13.80
54.55	7	3.15	9.45	-	86.00	76.30	53.50	34.00	21.90
87.96	7	4.00	12.00	-	139.00	123.00	86.20	54.90	35.30
3.52	7	0.80	4.00	-	14.90	13.20	9.20	5.90	3.80
8.59	7	1.25	6.25	-	36.30	32.20	22.60	14.40	9.20
14.07	7	1.60	8.00	-	59.50	52.80	37.00	23.50	15.10
59.69	19	2.00	10.00	-	93.00	82.50	57.80	36.80	23.60
74.88	19	2.24	11.20	-	117.00	103.00	72.50	46.10	29.70
93.27	19	2.50	12.50	-	145.00	129.00	90.30	57.50	36.90
238.76	19	4.00	20.00	-	372.00	330.00	231.00	147.00	94.60
9.55	19	0.80	5.60	-	28.80	25.50	17.90	11.40	7.30
23.32	19	1.25	8.75	-	70.30	62.30	43.70	27.80	17.90
38.20	19	1.60	11.20	-	115.00	102.00	71.50	45.50	29.30
148	19	3.15	15.75	-	231.00	205.00	143.00	91.20	58.60

REF. SPECIFICATION - IS 12776

Sectional Area	Stranding		Diameter of EARTHWIRE	Weight	Rated Strength		
	No. of Wires	Individual wire diameter			Grade 981	Grade 1100	Grade 1310
mm²	No.	mm	mm	Kg/km	KN	KN	KN
49.48	7	3.00	9.00	386.00	43.70	49.00	58.30
54.55	7	3.15	9.45	426.00	48.20	54.00	64.30
58.07	7	3.25	9.75	454.00	51.30	57.50	68.50
60.96	7	3.33	9.99	476.00	53.80	60.40	71.90
73.65	7	3.66	10.98	575.00	65.00	72.90	86.80
87.96	7	4.00	12.00	687.00	77.70	87.10	104.00

REF. SPECIFICATION - ASTM A 363

Sectional Area	Stranding		Diameter of EARTHWIRE	Weight	Rated Strength		
	No. of Wires	Individual wire diameter			High Strength Grade	Extra High Strength Grade	UTILITY GRADE
mm²	No.	mm	mm	Kg/km	KN	KN	KN
31.91	3	3.68	7.94	255.00	-	-	28.90
38.32	7	2.64	7.94	305.00	35.60	49.8	-
51.14	7	3.05	9.52	407.00	48.00	68.4	51.20
74.45	7	3.68	11.11	595.00	64.50	92.5	-
96.52	7	4.19	12.70	770.00	83.60	119.6	-

GALVANIZED STEEL WIRE EARTHWIRE / STAYWIRE / GUYWIRE / SPACER CABLE (GSW)

REF. SPECIFICATION -ASTM A 475

Sectional Area	Stranding		Diameter of EARTHWIRE	Weight	Rated Strength				
	No. of Wires	Individual wire diameter			Common Grade	Siemens Martin Grade	High Strength Grade	Extra High Strength Grade	UTILITY GRADE
mm²	No.	mm	mm	Kg/km	KN	KN	KN	KN	KN
5.95	7	1.04	3.18	48.00	2.402	4.048	5.916	8.140	-
9.58	7	1.32	3.97	76.00	3.870	6.539	6.539	13.078	-
13.55	7	1.57	4.76	109.00	5.115	8.452	12.677	17.748	-
14.97	7	1.65	4.76	119.00	-	-	-	-	10.676
16.42	3	2.64	5.56	131.00	6.228	10.409	15.569	21.796	-
18.41	7	1.83	5.56	146.00	6.850	11.387	17.126	24.020	-
21.92	3	3.05	6.35	174.00	8.274	13.523	21.040	29.981	14.01
21.92	3	3.05	6.35	174.00	-	-	-	-	20.02
22.66	7	2.03	6.35	180.00	8.452	14.012	21.129	29.581	-
25.66	3	3.30	7.14	204.00	9.252	15.035	23.398	33.362	-
30.62	7	2.36	7.14	244.00	11.432	18.905	28.469	39.812	20.46
31.91	3	3.68	7.94	255.00	11.076	18.193	28.246	40.479	26.91
38.32	7	2.64	7.94	305.00	14.234	23.798	35.586	49.820	-
42.18	7	2.77	7.94	335.00	-	-	-	-	26.69
41.37	3	4.19	9.52	328.00	14.813	24.732	37.187	52.489	37.81
51.14	7	3.05	9.52	407.00	18.905	30.915	48.040	68.503	51.16
74.45	7	3.68	11.11	595.00	25.355	41.591	64.499	92.523	80.07
96.52	7	4.19	12.70	770.00	32.917	53.823	83.627	119.657	111.21
96.27	19	2.54	12.70	751.00	33.895	56.492	84.961	118.768	-
125.62	7	4.78	14.29	1000.00	42.703	69.837	108.981	155.688	-
122.92	19	2.87	14.29	949.00	42.881	71.616	107.202	149.905	-
152.11	7	5.26	15.88	1211.00	51.599	84.961	131.667	188.605	-
150.90	19	3.18	15.88	1186.00	48.930	80.513	124.995	178.819	-
216.62	19	3.81	19.05	1721.00	71.172	116.543	181.487	259.331	-
302.18	19	4.50	22.22	2356.00	97.416	159.691	248.211	354.523	-
385.10	19	5.08	25.40	3089.00	127.664	209.07	325.61	464.8	-

REF. SPECIFICATION -DIN 48201

Nominal Area	Sectional Area	Stranding		Diameter of EARTHWIRE	Weight	Rated Strength			
		No. of Wires	Individual wire diameter			ST I	ST II	ST III	ST IV
mm²	mm²	No.	mm	mm	Kg/km	KN	KN	KN	KN
25	24.25	7	2.10	6.30	192.00	8.98	15.90	30.18	36.17
35	34.36	7	2.50	7.50	272.00	12.73	22.52	42.76	51.25
50	49.48	7	3.00	9.00	391.00	18.33	32.43	61.58	73.80
50	48.35	19	1.80	9.00	384.00	17.91	31.69	60.17	72.11
70	65.81	19	2.10	10.50	522.00	24.38	43.14	81.90	98.16
95	93.27	19	2.50	12.50	741.00	34.56	61.14	116.07	139.11
120	116.99	19	2.80	14.00	929.00	43.34	76.69	145.59	174.49