All Aluminum Alloy Medium Voltage Covered Conductor (MVCC)

Conductor- AL-59/AAAC/ACSR/AL59ACS (Watertight)
Conductor Screen- Semi-Conductive / Inner Covering- XLPE compound / Outer Covering- Anti Tracking
as per EN-50397-I/ BSEN-50182/ IEC: 61089/ AS-NZS-3675/ IS 398 PART II PART IV/IEC 6/232/BSEN IEC 63248



AAAC :: 55, 80 and 100 mm^2



AAAC :: 148, 173, 232,241 288 mm^2

11KV All Aluminum Alloy Medium Voltage Covered Conductor (MVCC)
(Reference Standard - IS 398 Part 4 & EN 50397-1)

Cross Section	Lay up of conductor	Conductor Diameter, Bare	Inner Semi Conductive layer (Nom.)	Inner Insulation (nom.)	Outer UV-Resistant, Anti Tracking (Nom.)	Approx. Overall Diameter	Rated Operating Voltage	DC Resistance at 20'C (Max.)	Current Carrying Capacity	Tensile Strength of Conductor (Min.)
Sqmm	-	mm	mm	mm	mm	mm	KV	Ohm/Km	A	KN
55	7 x 3.15	9.45	0.3	1.2	1.1	14.65	11	0.621	188	16.03
80	7 x 3.81	11.43	0.3	1.2	1.1	16.63	11	0.425	237	23.41
100	7 x 4.26	12.78	0.3	1.2	1.1	17.98	11	0.339	271	29.26
148	19 x 3.15	15.75	0.3	1.2	1.1	20.95	11	0.229	345	43.5
173	19 x 3.40	17	0.3	1.2	1.1	22.2	11	0.1969	378	50.54
232	19 x 3.94	19.7	0.3	1.2	1.1	24.9	11	0.1471	451	68.05
241	19 x 4.02	20.1	0.3	1.2	1.1	25.3	11	0.1412	462	70.8

33KV All Aluminum Alloy Medium Voltage Covered Conductor (MVCC)
(Reference Standard - IS 398 Part 4 & EN 50397-1)

Cross Section	Lay up of conductor	Conductor Diameter, Bare	Inner Semi Conductive layer (Nom.)	Inner Insulation (nom.)	Outer UV-Resistant, Anti Tracking (Nom.)	Approx. Overall Diameter	Rated Operating Voltage	DC Resistance at 20'C (Max.)	Current Carrying Capacity	Tensile Strength of Conductor (Min.)
Sqmm	-	mm	mm	mm	mm	mm	KV	Ohm/Km	A	KN
80	7 x 3.81	11.43	0.4	2.43	1.2	19.49	33	0.425	237	23.41
100	7 x 4.26	12.78	0.4	2.43	1.2	20.84	33	0.339	271	29.26
148	19 x 3.15	15.75	0.4	2.43	1.2	23.81	33	0.229	345	43.5
173	19 x 3.40	17	0.4	2.43	1.2	25.06	33	0.1969	378	50.54
232	19 x 3.94	19.7	0.4	2.43	1.2	27.76	33	0.1471	451	68.05
288	37 x 3.15	22.05	0.4	2.43	1.2	30.11	33	0.1182	515	84.71
241	19.4.02	20.1	0.4	2.43	1.2	28.2	33	0.1412	462	70.8

AL-59 - ACS
Medium Voltage Covered Conductor (MVCC)

Conductor- AL-59/AAAC/ACSR/AL59ACS (Watertight)
Conductor Screen-Semi-Conductive / Inner Covering-XLPE compound / Outer Covering-Anti Tracking
as per EN-50397-I/ BSEN-50182/ IEC: 61089/ AS-NZS-3675/ IS 398 PART II PART IV/IEC 6/232/BSEN IEC 63248



AL-59-ACS :: 31.6,52.88,78.82,
2 104.98mm, 80 and 100 mm^2



AL-59-ACS :: 102,160,241 mm^2

11KV AL-59 - ACS Medium Voltage Covered Conductor (MVCC)

Cross Section	No. of Wires/ Diameter - AL-59 Wires	No. of Wires/ Diameter - ACS Wires	Conductor Diameter, Bare	Inner Semi Conductive layer (Nom.)	Inner Insulation (nom.)	Outer UV-Resistant, Anti Tracking (Nom	Approx. Overall Diameter	Rated Operating Voltage	DC Resistance at 20'C (Max.)	Tensile Strength of Conductor (Min.)	Tensile Strength of Conductor (Min.)
Sqmm	Nos./mm	Nos./mm	mm	mm	mm	mm	mm	KV	Ohm/Km	A	KN
31.6	6 / 2.59	1 / 2.59	7.77	0.3	1.2	1.1	13	11	0.923	155	14.23
52.88	6 / 3.35	1 / 3.35	10.05	0.3	1.2	1.1	15.3	11	0.551	215	23.62
78.82	6 / 4.09	1 / 4.09	12.27	0.3	1.2	1.1	17.5	11	0.37	278	32.58
104.98	6 / 4.72	1 / 4.72	14.16	0.3	1.2	1.1	19.4	11	0.278	335	41.64
120	26 / 2.44	7 / 1.90	15.46	0.3	1.2	1.1	20.7	11	0.239	383	52.69
160	30 / 2.59	7 / 2.59	18.13	0.3	1.2	1.1	23.3	11	0.18	445	81.7
241	30 / 3.20	7 / 3.20	22.4	0.3	1.2	1.1	27.6	11	0.118	630	120

33KV AL-59 - ACS Medium Voltage Covered Conductor (MVCC)

Cross Section	No. of Wires/ Diameter - AL-59 Wires	No. of Wires/ Diameter - ACS Wires	Conductor Diameter, Bare	Inner Semi Conductive layer (Nom.)	Inner Insulation (nom.)	Outer UV-Resistant, Anti Tracking (Nom	Approx. Overall Diameter	Rated Operating Voltage	DC Resistance at 20'C (Max.)	Current Carrying Capacity	Tensile Strength of Conductor (Min.)
Sqmm	Nos./mm	Nos./mm	mm	mm	mm	mm	mm	KV	Ohm/Km	A	KN
78.82	6 / 4.09	1 / 4.09	12.27	0.4	2.43	1.2	20.3	33	0.37	278	32.58
104.98	6 / 4.72	1 / 4.72	14.16	0.4	2.43	1.2	22.2	33	0.278	335	41.64
120	26 / 2.44	7 / 1.90	15.46	0.4	2.43	1.2	23.5	33	0.239	383	52.69
160	30 / 2.59	7 / 2.59	18.13	0.4	2.43	1.2	26.2	33	0.18	445	81.7
241	30 / 3.20	7 / 3.20	22.4	0.4	2.43	1.2	30.5	33	0.118	630	120