



Hollow Concrete Block Production Training for Producers



info@minergynepal.com

Introduction

Start of HCB in Nepal: More than 40 years in Nepal by introduction of GMP, a fabricator of HCB machine




Application of HCB




Types and Shapes




4" Block



6" Block



8" Block



4" Corner Block



6" Corner Block




8" Lintel Block



4" Pillar Block



6" Lintel Block



Foundation Block

Existing Quality





Standards & Specifications

Sieve Size (mm)	Recommended Range
12.5 – 10	10-15
10 – 4.75	20-25
4.75 – 0.3	50-55
0.3 – 0.075	5-10

Physical Features	Requirements
Density	Minimum = 1600 kg/m ³
Compressive strength	Minimum = 50 kg/cm ²
Water absorption	Maximum = 10% by weight

Common Name	Nominal Block Size (L x B x H)	Actual Block Size (L x B x H)
8 inch block	400 x 100 x 200	390 x 100 x 190
6 inch block	400 x 150 x 200	390 x 150 x 190
4 inch block	400 x 200 x 200	390 x 200 x 190

Size (mm)	Recommended range
10-20 mm	25-55
5-10 mm	5-45
0.5-5 mm	3-42
<0.5	8-27

Training Package

Method - theoretical and practical session on the production yard

Major contents

- Benefits and various types of HCB
- Introduction of raw materials for HCB production
- How to recognize quality of raw materials?
- Basic of concrete mix design
- Practical mix design approaches
- What is the right mix of raw materials for quality production?
- Introduction of various tools and equipment used in HCB production (Handmade and machine-made)
- Costs of tools and equipment
- Cost of HCB factory set up
- HCB machines and its fabricators in Nepal
- How to produce quality HCB
- Challenges and strategies to cope the challenges of HCB
- HCB standards and specifications in Nepal
- Dos and Don'ts for the HCB production

Duration

- 3, 5 or 7 days (customized based on target participants)

Training Experiences

Since 2006 – based on research and training experiences

District coverage –

- Rupandehi, Kapilavastu, Nawalparasi, Kathmandu Valley during SDC project period
- Makwanpur, Chitwan, Nawalparasi, Dhading, Tanahu, Kaski, lamjung Kathmandu Valley During European Union (EU) support project SCP
- After Earthquake – Sindupalchowk

Target coverage –More than 200 HCB producers

The way to get noticed..



..is to do **QUALITY WORK!**

Thank
you