

Supplemental material : Theoretical study on the possibility of high T_c $s\pm$ -wave superconductivity in the heavily hole-doped infinite layer nickelates

Hirofumi Sakakibara,^{1,*} Ryota Mizuno,² Masayuki Ochi,^{3,2} Hidetomo Usui,⁴ and Kazuhiko Kuroki³

¹*Advanced Mechanical and Electronic System Research Center(AMES), Faculty of Engineering,
Tottori University, 4-10 Koyama-cho, Tottori, Tottori 680-8552, Japan*

²*Forefront Research Center, Osaka University, 1-1 Machikaneyama-cho, Toyonaka, Osaka 560-0043, Japan*

³*Department of Physics, Osaka University, 1-1 Machikaneyama-cho, Toyonaka, Osaka 560-0043, Japan*

⁴*Department of Physics and Materials Science, Shimane University,
1060 Nishikawatsu-cho, Matsue, Shimane 690-8504, Japan*

(Dated: July 30, 2024)

PHONON DISPERSION OF $\text{La}_{1-x}\text{Sr}_x\text{NiO}_2$

In Fig. 1, we present the calculated phonon dispersion of $\text{La}_{1-x}\text{Sr}_x\text{NiO}_2$ for all the cases (combination of the Sr content and the substrate) considered in the present study. As seen from these results, imaginary frequencies do not appear in any of the cases, indicating that the $P4/mmm$ symmetry of the original LaNiO_2 is dynamically stable.




FIG. 1. The phonon dispersion of $\text{La}_{1-x}\text{Sr}_x\text{NiO}_2$ with the in-plane lattice constant fixed to that of SrTiO_3 ((a)-(c)), LSAT ((d)-(f)), or LaAlO_3 ((g)-(i)) substrates. The Sr content is $x = 0$ ((a),(d),(g)), $x = 0.5$ ((b),(e),(h)), or $x = 1$ ((c),(f),(i)).

ELECTRONIC BAND DISPERSION OF $\text{La}_{1-x}\text{Sr}_x\text{NiO}_2$

In Fig. 2, we present the calculated electronic band dispersion of $\text{La}_{1-x}\text{Sr}_x\text{NiO}_2$. The Ni- d bands other than the $d_{x^2-y^2}$ band become incipient at $x \sim 0.5-0.7$ for SrTiO_3 and LSAT substrates and $x \sim 0.7$ for LaAlO_3 substrate.




FIG. 2. The electronic band dispersion of $\text{La}_{1-x}\text{Sr}_x\text{NiO}_2$ with the in-plane lattice constant fixed to that of SrTiO_3 ((a)-(c)), LSAT ((d)-(f)), or LaAlO_3 ((g)-(i)) substrates. The Sr content is $x = 0.3$ ((a),(d),(g)), $x = 0.5$ ((b),(e),(h)), or $x = 0.7$ ((c),(f),(i)). The strength of the Wannier orbital characters are shown with the thickness of the color coded line.