

Supplmental material : Theoretical study on the possibility of high T_c $s\pm$ -wave superconductivity in the heavily hole-doped infinite layer nickelates

Hirofumi Sakakibara,^{1,*} Ryota Mizuno,² Masayuki Ochi,^{2,3} Hidetomo Usui,⁴ and Kazuhiko Kuroki³

¹*Advanced Mechanical and Electronic System Research Center(AMES), Faculty of Engineering,
Tottori University, 4-10 Koyama-cho, Tottori, Tottori 680-8552, Japan*

²*Forefront Research Center, Osaka University, 1-1 Machikaneyama-cho, Toyonaka, Osaka 560-0043, Japan*

³*Department of Physics, Osaka University, 1-1 Machikaneyama-cho, Toyonaka, Osaka 560-0043, Japan*

⁴*Department of Applied Physics, Shimane University,
1060 Nishikawatsu-cho, Matsue, Shimane 690-8504, Japan*

(Dated: April 29, 2025)

PHONON DISPERSION OF $\text{La}_{1-x}\text{Sr}_x\text{NiO}_2$

In Fig. S1, we present the calculated phonon dispersion of $\text{La}_{1-x}\text{Sr}_x\text{NiO}_2$ for all the cases (combination of the Sr content and the substrate) considered in the present study. As seen from these results, imaginary frequencies do not appear in any of the cases, indicating that the $P4/mmm$ symmetry of the original LaNiO_2 is dynamically stable.




FIG. S1. The phonon dispersion of $\text{La}_{1-x}\text{Sr}_x\text{NiO}_2$ with the in-plane lattice constant fixed to that of SrTiO_3 ((a)-(c)), LSAT ((d)-(f)), or LaAlO_3 ((g)-(i)) substrates. The Sr content is $x = 0$ ((a),(d),(g)), $x = 0.5$ ((b),(e),(h)), or $x = 1$ ((c),(f),(i)).

ELECTRONIC BAND DISPERSION OF $\text{LA}_{1-x}\text{SR}_x\text{NIO}_2$

In Fig. S2, we present the calculated electronic band dispersion of $\text{La}_{1-x}\text{Sr}_x\text{NiO}_2$. The Ni-*d* bands other than the $d_{x^2-y^2}$ band become incipient at $x \sim 0.5-0.7$ for SrTiO_3 and LSAT substrates and $x \sim 0.7$ for LaAlO_3 substrate.




FIG. S2. The electronic band dispersion of $\text{La}_{1-x}\text{Sr}_x\text{NiO}_2$ with the in-plane lattice constant fixed to that of SrTiO_3 ((a)-(c)), LSAT ((d)-(f)), or LaAlO_3 ((g)-(i)) substrates. The Sr content is $x = 0.3$ ((a),(d),(g)), $x = 0.5$ ((b),(e),(h)), or $x = 0.7$ ((c),(f),(i)). The strength of the Wannier orbital characters are shown with the thickness of the color coded line.

LATTICE MISMATCH BETWEEN $\text{LA}_{1-x}\text{SR}_x\text{NIO}_2$ THIN FILM AND SUBSTRATES

In Fig. S3(a), we present the lattice constants of a and c of $\text{La}_{1-x}AE_x\text{NiO}_2$ ($AE = \text{Ba}, \text{Sr}$) against the substitution ratio x . The lattice constant a becomes smaller because of the smaller ionic radius of Sr ion than that of La. In contrast, the constant c in the $AE = \text{Ba}$ case becomes larger, probably affected by the ionic radius of Ba.

In Fig. S3(b), we present the mismatch of the lattice constants between thin film and substrates against the ratio x . It can be seen that the mismatch is below 2% for the SrTiO_3 and LSAT cases throughout the range of x . Even for the case of LaAlO_3 , for the higher substitution ratio, the mismatch is below 2%.

EFFECTS OF GGA+ U METHOD

In Fig. S4, we present the band dispersion calculated by GGA+ U method. Compared to Fig. S2, the splittings between the $d_{x^2-y^2}$ bands and the other d -bands are larger. This is because that the energy of a filled (not filled) orbital goes up (down) in the GGA+ U calculations.

In Fig. S5, we plot the eigenvalues λ against the substitution ratio x for comparison with the GGA case. The change of λ is probably caused by that of the band splitting. Namely, since the lower d -bands lie farther away from the Fermi level, the larger amount of holes is required to make these bands incipient. This is the reason why the




FIG. S3. (a) The lattice constants of a and c of $\text{La}_{1-x}\text{AE}_x\text{NiO}_2$ ($\text{AE} = \text{Ba}, \text{Sr}$) against the ratio x and (b) the mismatch of the lattice constants between the thin film and substrates. Here, the legends indicate the three substrates (with the lattice constants 3.905, 3.868, 3.790 Å for SrTiO_3 , LSAT , LaAlO_3 , respectively). In panel (b), the $\text{AE}=\text{Ba}$ case is indicated by open symbols, while the other cases ($\text{AE}=\text{Sr}$) are indicated by filled symbols.




FIG. S4. The electronic band dispersion of $\text{La}_{1-x}\text{Sr}_x\text{NiO}_2$ obtained by GGA+ U method with the in-plane lattice constant fixed to that of SrTiO_3 . The substitution ratio x is written at the top of each panel. Here we have chosen the value of $U = 3.5$ eV and $J = 0.65$ eV, adopting the cRPA values. The blue lines indicate the first principles band dispersion, while the red lines are the band dispersion of the five-orbital model (Wannier interpolated).

higher doped region is advantageous for superconductivity for the GGA+ U case.

* sakakibara@tottori-u.ac.jp




FIG. S5. The eigenvalue of the Eliashberg equation plotted against the Sr/Ba content x for the three substrates. The pairing symmetry having the largest λ is d -wave in the small x regime (calculated only for SrTiO₃ substrate), while it is $s\pm$ -wave for $x > 0.3$. The purple filled circle indicate λ of the GGA+ U case.