

Energy and cell parameters (per ton Ti, single-potential CaO basis)

gross electrolysis 12 625 kWh | net equivalent 12 933 kWh | cell voltage 4.23 V

η_I = 0.75 (unvalidated) | interelectrode gap $L \lesssim 1.1$ cm at κ = 1.4 S/cm, $\delta \approx$ 200 μm

current efficiency is the dominant uncertainty