

Watertight and weathertight closures

NES-109 Issue 4

RESTRICTED

Part 3, Clause 12

Watertight doors below the damage control deck shall be of the quick-acting clip type, operable from both sides, and shall be proof tested to a head of water equal to the distance from the sill to the bulkhead deck plus 1 m. Weathertight hatches on exposed decks shall be fitted with coamings of not less than 380 mm on the freeboard deck and 230 mm on superstructure decks.

Annex D

Where an aluminium superstructure meets a steel hull, the joint shall be made with an explosion-bonded bimetallic transition strip. Direct bolted connections between aluminium and steel are not permitted. The transition strip shall be protected from standing water on both faces.

3.3 Impressed current system

An impressed current cathodic protection system shall maintain hull potential between -0.80 and -1.05 V against a silver/silver chloride reference cell. Anode positions shall be kept clear of the propeller aperture and of sonar transducer faces by not less than 3 m. The underwater coating scheme shall be a glass flake epoxy system of 400 micrometre nominal dry film thickness.