ATMY ANALYTICAL LABS PVT. LTD.
I-30, DLF Industrial Area, Phase 1, Faridabad-121003 (Haryana) INDIA
Phone: +91-129-4019544
info@atmylabs.com , www.atmylabs.com

• Testing
• Research
• Innovation

TEST REPORT

Report No.: **M2610010003**

Date: 08-10-2026

Issued To:

M/s KONCAVE ANCHOR FASTENERS PVT . LTD .
Village Ismaila, 11B Ismaila, Near Rana Batta, Tehsil Sampla,
Rohtak, Haryana – 124501,

Sample Description	:	GALVANIZED WEDGE ANCHOR, SIZE-M10X100MM LONG, MAKE-**KONCAVE ANCHOR FASTENERS PVT . LTD .**
Sample Received Date	:	01-10-2026
Sample Drawn By	:	Client
Specification	:	--
Test Requested	:	SHEAR STRENGTH, TENSILE
Test Method	:	Refer to Attached Pages.
Test Result	:	Refer to Attached Pages.

SAMPLE PICTURE



Authentication: To Check authenticity of Test report (s), Scan **QR** code to get original data.

Terms & Conditions

1. Sample will not be retained more than one month for chemical and three months for mechanical unless specified instructed. 2.Samples analysis conducted on as received basis and followed by customer description, unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. The statement of conformity furnished herewith based on decision rule AAL/DRCS of our laboratory 5. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 6 The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 7. Total liability of our laboratory is limited to the invoiced amount only. 8. This report cannot be used as and evidence in a court of law without the written approval of the laboratory.

ATMY ANALYTICAL LABS PVT. LTD.
I-30, DLF Industrial Area, Phase 1, Faridabad-121003 (Haryana) INDIA
Phone: +91-129-4019544
info@atmylabs.com , www.atmylabs.com

• Testing
• Research
• Innovation

TEST REPORT

Report No.: **M2610010003**

Date: 08-10-2026

I. Mechanical

1. Mechanical Properties of Metals

TENSILE TEST	**Test performed on : 01-10-2026 to 08-10-2026**
Test Method : IS 1608 ,Part-1:2022	
Test Parameter	**Result**
Tensile Strength (N/mm²)	669

2.

SHEAR STRENGTH	**Test performed on : 08-10-2026 to 08-10-2026**
Test Method : IS 800:2007	
Test Parameter	**Result**
Shear strength (kN)	24.97

ATMY ANALYTICAL LABS PVT. LTD. FARIDABAD

D. Kumar
QUALITY MANAGER

Reviewed and Authorized By

----------End of Report----------

Authentication: To Check authenticity of Test report (s), Scan **QR** code to get original data.

Terms & Conditions

1. Sample will not be retained more than one month for chemical and three months for mechanical unless specified instructed. 2.Samples analysis conducted on as received basis and followed by customer description, unless specified otherwise. 3. The laboratory will not be liable for sample destroy/damage during testing, unless instructed otherwise. 4. The statement of conformity furnished herewith based on decision rule AAL/DRCS of our laboratory 5. Any complaints matter about this report should be communicated in written, within 7 days of issue of this report. 6 The result listed refer only to the tested samples and applicable parameters as described by customer. Endorsement of product is neither inferred nor implies. 7. Total liability of our laboratory is limited to the invoiced amount only. 8. This report cannot be used as and evidence in a court of law without the written approval of the laboratory.