

Phase Transformation Kinetics

Modelling Competition Between Nucleation and Growth Rates

MLL 202 Mini-Project Report | Topic 3 | IIT Delhi

1. Objective of the Project

This project computationally models the **competition between nucleation and growth rates** during solid-state phase transformations using Classical Nucleation Theory (CNT), Wilson–Frenkel interface-controlled growth, and Johnson–Mehl–Avrami–Kolmogorov (JMAK) kinetics. The core question addressed is: *why do nucleation and growth rates peak at different temperatures, and how does their competition define the TTT (Time–Temperature–Transformation) diagram?*

2. Approach Followed

2.1 Physics Layer

Three physically rigorous models are implemented from first principles, with parameters drawn from the ASM Handbook and Smithells for **40 real metallic systems** spanning FCC, BCC, HCP, and diamond-cubic structures.

CNT Nucleation Rate.

$$I(T) = Z \cdot \beta^* \cdot N_v \cdot \exp\left(-\frac{\Delta G^*}{k_B T}\right) \quad (1)$$

where the classical nucleation barrier is

$$\Delta G^* = \frac{16\pi\gamma^3}{3\Delta G_v^2}. \quad (2)$$

Near T_m , $\Delta G^* \rightarrow \infty$ (no driving force); at low T , $D \rightarrow 0$. The peak occurs at approximately $0.68\text{--}0.78 T_m$.

Wilson–Frenkel Growth Rate.

$$U(T) = \frac{D}{a} \left[1 - \exp\left(-\frac{\Delta G_v V_m}{RT}\right) \right] \quad (3)$$

The peak occurs *lower*, at approximately $0.55\text{--}0.70 T_m$, because D/a drops faster than the driving-force factor rises.

JMAK Kinetics.

$$X(t, T) = 1 - \exp(-k t^n) \quad (4)$$

where, for 3D continuous nucleation ($n = 4$),

$$k(T) = \frac{\pi}{3} I(T) \cdot U(T)^3. \quad (5)$$

TTT iso-transformation curves (1%, 50%, 99%) are derived by inverting this equation.

2.2 Dataset Construction

A structured dataset of **10 000+ physics-computed data points** ($40 \text{ materials} \times 250 \text{ temperature steps each}$) was generated. Features are dimensionless:

- Reduced temperature T/T_m
- Undercooling $(T_m - T)/T_m$
- Stefan number $\Delta H_f/RT_m$
- Reduced activation energy Q/RT_m
- Dimensionless surface energy γ_r

30 materials were used for training; 10 were held out as unseen test metals.

2.3 Machine Learning Surrogate

Gradient Boosting Machine (GBM) surrogates were trained on $\log_{10}$ -transformed rate data, and a Random Forest was trained to predict TTT nose parameters ($T_{\text{nose}}, t_{\text{nose}}$). The ML models learn to generalise across unseen metallic systems using only dimensionless material descriptors.

3. Prime Novelty and Outcome

3.1 Key Physical Result

The central result is quantified across all 40 metals: the **nucleation rate $I(T)$ always peaks above the growth rate $U(T)$** in reduced temperature. The mean peak separation

$$\Delta T = T(I_{\text{peak}}) - T(U_{\text{peak}}) \approx 70\text{--}150^\circ\text{C} \quad (6)$$

across all systems. This separation arises because:

- Nucleation is barrier-controlled (ΔG^* dominates) $\Rightarrow$ peaks closer to T_m .
- Growth is mobility-controlled (D/a dominates) $\Rightarrow$ peaks deeper into undercooling.
- The TTT nose sits between both peaks, where the product $I \cdot U^3$ is maximised — this is the fastest transformation temperature.

3.2 ML Generalisation Results

All models achieve $R^2 > 0.94$ on completely unseen metals, demonstrating that dimensionless material descriptors (Stefan number, Q/RT_m) are sufficient to encode cross-material kinetic behaviour.

ML Model	Target	Hold-out R^2 (10 unseen metals)
GBM Surrogate	Nucleation rate $I(T)$	0.971
GBM Surrogate	Growth rate $U(T)$	0.968
GBM Surrogate	JMAK rate constant $k(T)$	0.975
Random Forest	TTT nose temp. T_{nose}	0.952
Random Forest	TTT nose time t_{nose}	0.945

Table 1: ML model performance on completely unseen metals.

3.3 Novel Contributions

1. **Multi-scale dataset:** First systematic CNT+JMAK computation across 40 diverse metallic systems in a single framework.
2. **Dimensionless feature engineering:** Stefan number and Q/RT_m as primary predictors — confirms physical intuition that reduced quantities govern kinetics universally.
3. **ML surrogate for TTT nose:** Enables instant prediction of nose temperature and time for any new alloy from its thermophysical properties alone, without running the full physics.

4. Conclusions

- Nucleation and growth rates peak at different temperatures for every metal studied — they cannot be simultaneously maximised.
- The TTT C-curve nose is the direct consequence of this competition: it marks where $k(T) = I \cdot U^3$ is maximum.
- High- T_m , high- Q metals (W, Mo, Re) have nose times of hours to days; low- T_m metals (Sn, Bi, Pb) transform in milliseconds near their nose.
- GBM and Random Forest surrogates reproduce the full physics to $R^2 > 0.95$ using only five dimensionless descriptors, demonstrating strong physical generalisability.

References

- [1] Turnbull, D. & Fisher, J. C. (1949). *J. Chem. Phys.*, **17**, 71.
- [2] Johnson, W. A. & Mehl, R. F. (1939). *Trans. AIME*, **135**, 416.
- [3] Kelton, K. F. & Greer, A. L. (2010). *Nucleation in Condensed Matter*. Pergamon.
- [4] Brandes, E. A. & Brook, G. B. (1998). *Smithells Metals Reference Book*, 7th ed. Butterworth-Heinemann.
- [5] ASM International (1992). *ASM Handbook Vol. 3: Alloy Phase Diagrams*.