Computational Parameterization of Textile Yarns in the Surat Power Loom Sector: Mechanical, Thermal, and Kinematic Baselines for Design Engines

The Intersection of Digital Engineering and the Surat Textile Ecosystem

The Surat textile cluster represents one of the largest, most concentrated, and most prolific power loom and synthetic fabric manufacturing zones within the global textile supply chain. Handling an annual polyester yarn consumption routinely pegged at over 40,610 lakh kilograms and an annual woven fabric production exceeding 91,871 lakh meters, the region serves as a critical macro-node in the engineering and production of both apparel and industrial textiles.[1] The backbone of this extraordinary manufacturing output relies heavily on the continuous optimization of weaving preparatory processes and the precise mechanical, thermal, and geometric characterization of the precursor yarns utilized in these high-speed looms.[2] For the development of advanced design engines, digital twins, and automated textile databases, establishing a mathematically rigorous set of technical parameters for the most commonly deployed yarns is absolutely essential. These parameters serve as the foundational computational inputs required for predicting fabric behavior, simulating 3D drape, optimizing kinetic machine speeds, and ensuring downstream quality control.

The transition of the textile industry toward Industry 4.0 paradigms demands that physical raw materials be accurately represented as digital assets. A computational design engine cannot simulate the tensile failure of a woven matrix or the thermal dimensional collapse of a fabric during heat-setting without highly accurate, empirical data regarding the constituent yarns. This report provides an exhaustive technical analysis of three foundational yarns heavily utilized within the Surat power loom sector: Polyester 75D (a continuous synthetic filament), an 80/20 Poly-Viscose blend (a composite spun yarn), and 40s Combed Cotton (a highly refined natural spun yarn). Each of these materials exhibits highly distinct polymeric architectures, mechanical tensile profiles, thermal shrinkage behaviors, and weavability dynamics.[3]

The interaction of these specific yarns with modern high-speed shedding and weft insertion mechanisms—specifically fluid-driven Water-jet and mechanically driven Rapier looms—dictates the ultimate kinetic limits and economic viability of the weaving process.[6] By quantifying specific physiochemical parameters such as breaking tenacity, viscoelastic elongation at break, initial Young's modulus, and high-temperature dimensional stability, textile engineers can program predictive algorithms that prevent catastrophic yarn failure during high-stress loom operations.[8]

Furthermore, analyzing the mathematical relationship between twist architecture (Twist Per Inch) and production RPM offers a definitive, programmable guide for configuring the physical machinery in real-world industrial applications.[10] The culmination of this research is synthesized into a highly structured JSON database architecture, designed specifically for immediate deployment within a TypeScript-based software interface.

Fundamental Polymer Physics and Yarn Characterization Metrics

Before analyzing the specific yarns, it is necessary to establish the technical, physical, and mathematical framework governing their mechanical and thermal properties. The macroscopic physical behavior of a textile yarn—how it stretches, breaks, or shrinks—is a direct physical manifestation of its microscopic polymer chain orientation, the ratio of crystalline to amorphous domains, and the strength of its intermolecular bonding forces.[12]

Linear Density and Geometric Configurations

Linear density serves as the primary geometric classifier for textile yarns, dictating the mass-to-length ratio and ultimately defining the weight and cover factor of the resulting woven fabric. For continuous synthetic filaments like polyester, the direct Denier system is universally utilized across the Surat industry. Denier is defined as the mass in grams per 9,000 meters of yarn.[14] A 75 Denier (75D) yarn, therefore, possesses a linear density of 83.3 decitex (dtex, grams per 10,000 meters), representing a fine, lightweight filament structure ideal for high-density, closely woven apparel.[3]

Conversely, spun yarns derived from staple fibers—such as cotton and viscose—utilize the English Cotton Count (Ne), an indirect measurement system. The Ne value is defined as the number of 840-yard hanks required to weigh exactly one pound.[16] Because it is an indirect system, higher Ne values indicate progressively finer yarns; thus, a 40s count yarn is significantly finer, lighter, and more delicate than a 20s count yarn.[4]

Twist configuration, measured in Twist Per Inch (TPI) or Turns Per Meter (TPM), is the primary geometric mechanism that binds staple fibers together. Twist generates the necessary centripetal radial pressure to provide cohesive strength, preventing individual fiber slippage under severe tensile loads.[18] The required TPI for a spun yarn is determined by an empirical mathematical formula:

$$TPI = TM \times \sqrt{Ne}$$

where TM represents the Twist Multiplier. The Twist Multiplier is a specialized constant dictated by the intended end-use of the yarn. For weaving warp yarns, which must survive the intense abrasive forces of the loom heald wires and the oscillating reed, a higher TM (typically ranging from 3.5 to 4.2) is deployed to lock the fibers securely in place.[4] Continuous filament yarns,

however, require negligible twist. They rely instead on aerodynamic intermingling (measured in nodes per meter) or extremely low-twist setups (such as 60-120 TPM) to maintain filament cohesion without generating excessive, fabric-distorting torque.[3]

Mechanical Tensile Profiles

The mechanical integrity of a yarn is systematically evaluated through its load-elongation or stress-strain response, typically measured using advanced tensile testing apparatuses such as the Uster Tensorapid or Statimat M.[9]

Mechanical Parameter	Definition	Industrial Significance
Tenacity (cN/tex)	The ultimate breaking force normalized to the linear density of the yarn.	Determines the maximum instantaneous load the yarn can bear during the high-tension cycles of loom beat-up and shedding without rupturing.[22]
Elongation at Break (%)	The maximum viscoelastic extension of the yarn before catastrophic failure occurs.	Provides the necessary kinetic buffer to absorb the sudden, sharp shockwaves imparted by rapid weft insertion mechanisms.[3]
Young's Modulus (cN/tex)	Extracted from the linear Hookean region of the stress-strain curve, defining initial resistance to deformation.	High-modulus yarns resist stretching under low loads, ensuring fabric stability. Low-modulus yarns offer superior drape, softness, and flexibility.[25]

Thermodynamics and Dimensional Stability

Yarns subjected to high-speed weaving and subsequent high-temperature wet-processing or heat-setting undergo complex thermodynamic phase transitions that must be mathematically predicted by design engines.[27]

Boiling Water Shrinkage (BWS) evaluates the dimensional contraction of the yarn when fully submerged in an aqueous environment at 100°C.[29] For synthetic polymers, this shrinkage is governed by the rapid relaxation of amorphous polymer chains that were forcibly extended and locked into place during the high-speed melt-spinning and drawing phases of manufacturing. Dry Heat Shrinkage (DHS), measured predominantly at 180°C for synthetic fibers, reflects the

contraction induced by hot air convection.[30] This testing temperature sits well above the glass transition temperature (T_g ~ 80°C for polyester) but below the melting temperature (T_m ~ 260°C). Exceeding the T_g grants the polymer chains substantial internal mobility, resulting in the entropic recoil of oriented macromolecules.[31] Natural cellulosic fibers like cotton lack a true thermoplastic T_g and instead rely on an extensive network of hydrogen-bonded crystalline regions. This rigid architecture renders their dry heat shrinkage virtually negligible compared to synthetic polymers.[12]

Comprehensive Polymeric Analysis of Polyester 75D Filament Yarn

Polyester (Polyethylene Terephthalate, or PET) is a highly versatile thermoplastic polymer synthesized via the polycondensation reaction of purified terephthalic acid (PTA) and ethylene glycol (EG).[34] Within the Surat textile hub, 75D polyester filament—most frequently configured as Draw Textured Yarn (DTY) or Fully Drawn Yarn (FDY)—represents a massive volume of the synthetic raw material throughput.[35] It is predominantly utilized in the mass production of sarees, dress materials, lightweight technical textiles, and home furnishings. The 75D geometric designation is universally accompanied by its specific filament count, such as 75D/72F or 75D/36F. A 75D/72F specification indicates that exactly 72 individual, microscopic continuous filaments have been bundled together to comprise the master yarn.[3] The higher the filament count for a given denier, the softer the resulting fabric hand-feel, owing to the reduced bending rigidity of the finer individual filaments.

Tensile Mechanics and Load Endurance

The mechanical properties of 75D polyester are not purely innate to the chemistry of PET; they are heavily engineered and dictated by the draw ratio applied during the post-spinning extrusion phase. Stretching the semi-molten yarn forces the polymer chains to align parallel to the longitudinal axis of the fiber, exponentially increasing crystallinity and, consequently, tensile tenacity.[24]

Standard apparel-grade 75D polyester DTY demonstrates a robust breaking tenacity of $\geq$ 3.5 cN/dtex, which directly converts to approximately 35.0 cN/tex.[3] While specialized industrial-grade high-tenacity (HT) polyesters—engineered for seatbelts, tire cords, and heavy tarpaulins—can achieve extreme tenacities exceeding 70.0 to 85.0 cN/tex [38], the 75D variant utilized in standard Surat power looms is deliberately manufactured to operate in the range of 35.0 to 45.0 cN/tex. This highly specific range maintains an optimal, commercially viable balance between weaving strength and the final garment's softness.[3]

The elongation profile for 75D/72F DTY sits securely within the 16.1% to 22.1% range, with rigorous factory quality control standards (such as those for AA-grade yarns) pinpointing an

exact average of 19.1% ($\pm$ 3.0%).[3] This generous viscoelastic stretch capacity is highly beneficial for loom operators. It allows the yarn to act as a physical shock absorber, easily withstanding the sudden, sharp tension spikes induced by high-RPM rapier heads or the explosive acceleration of water-jet weft insertion systems.

Polyester generally exhibits a relatively high initial modulus compared to regenerated cellulosics. Standard 75D filament yarn maintains a Young's modulus ranging between 90.0 cN/tex and 120.0 cN/tex.[26] This intrinsic stiffness ensures that the yarn does not permanently stretch or plastically deform under the constant, unrelenting warp-way tension applied by the loom's let-off and cloth take-up mechanisms.

Thermal Dynamics and Heat-Setting Predictability

Thermal dimensional stability is an operational paramount for polyester, as the material is acutely responsive to heat due to its thermoplastic nature. The polymer contains both highly ordered crystalline regions (providing structural strength) and disordered amorphous regions (providing flexibility and dye absorption sites).[41]

When exposed to 100°C aqueous environments during dyeing or scouring, standard 75D PET undergoes a controlled entropic relaxation, returning to a lower-energy geometric state. Certified technical data sheets specify a tightly controlled boiling water shrinkage of 2.58% ($\pm$ 0.5%) for AA-grade 75D/72F.[3] This highly uniform, predictable shrinkage is mathematically essential for a design engine, as it allows the software to accurately predict the final fabric width after wet-processing.

At elevated temperatures of 180°C, which are entirely typical of industrial stenter frames and dry heat-setting operations, the PET polymer experiences vastly greater molecular mobility. Standard 75D polyester exhibits a pronounced dry heat shrinkage ranging from 5.5% to 8.0%.[32] If a design engine is programming a loom to produce a fabric that will undergo 180°C heat-setting, the software must automatically widen the reed space parameter by approximately 6% to 8% to compensate for this inevitable thermal collapse.

Geometric Configurations for High-Speed Weaving

Unlike spun staple yarns, 75D filament polyester does not strictly require high levels of mechanical torsion (twist) to maintain its structural integrity. Applying high twist to a filament yarn significantly increases manufacturing costs and slows down production. Instead, filament cohesion is ingeniously achieved through air-jet intermingling. During texturing, the yarn is subjected to perpendicular, high-pressure air blasts that randomly tangle the 72 filaments together, creating physical "nodes" or "nips." A standard 75D/72F Slight Intermingle (SIM) yarn features approximately 152 nodes per meter.[3]

When twist is explicitly required by the fabric designer for specific optical effects, crepe textures, or georgette weaves, the TPI applied remains relatively low compared to spun yarns. It typically ranges from 1.5 to 3.0 TPI (equivalent to 60-120 Twists Per Meter) to prepare the yarn for

standard weaving applications without introducing severe torque liveliness that could cause the weft to snarl upon insertion.[20]

Parameter Category	Polyester 75D Filament Specifications
Tenacity (cN/tex)	35.0 - 45.0
Elongation at Break (%)	16.1 - 22.1 (Average ~19.1%)
Young's Modulus (cN/tex)	90.0 - 120.0
Boiling Water Shrinkage (%)	2.0 - 3.1 (Average ~2.58%)
Dry Heat Shrinkage 180°C (%)	5.5 - 8.0
TPI Range (Weaving)	1.5 - 3.0 (Or Intermingled ~150 nodes/m)

Synergistic Mechanics of 80/20 Poly-Viscose Blended Spun Yarn

The 80/20 Poly-Viscose (PV) blend is a highly engineered composite spun yarn, meticulously designed to harness the synergistic properties of two vastly different polymeric fibers. Viscose, a regenerated cellulose fiber chemically derived from purified wood pulp, provides excellent moisture management, exceptional breathability, and a highly desirable soft, silk-like drape.[44] However, as an independent fiber, viscose suffers from critically low wet strength, poor wrinkle recovery, and high dimensional instability.[46] Polyester staple fiber, conversely, contributes massive tensile strength, exceptional abrasion resistance, and rigid dimensional stability.[45] By blending 80% high-tenacity polyester staple with 20% viscose staple, textile manufacturers in Surat successfully create a robust, highly versatile, and cost-effective yarn that is the industry standard for suiting, shirting, uniforms, and industrial workwear.[45]

Mechanical Profile and Composite Blend Kinematics

The tensile mechanics of a blended spun yarn are highly complex and distinctly non-linear. They are most accurately modeled by the Hamburger mixture theory, which dictates that the strength of a blended yarn is not merely a simple average of its components.[19] Because polyester and viscose possess differing elongation limits, the mechanical failure of the 80/20 yarn under tension occurs in a staggered, sequential manner. The viscose fibers, which generally exhibit lower extensibility under tight twist conditions, may reach their rupture point earlier during stretching. Upon the failure of the viscose fibers, the entirety of the tensile load is instantly transferred to the remaining 80% polyester skeletal matrix.

Pure viscose exhibits a relatively low dry tenacity of 20.0 to 25.0 cN/tex, and this value drops alarmingly when the fiber is wet (often falling to 10.0-15.0 cN/tex) due to the plasticization of its cellulose chains by water molecules.[25] However, the overwhelming 80% fraction of high-strength polyester effectively masks this weakness, bolstering the overall yarn strength. The resulting 80/20 PV spun yarn typically demonstrates a highly reliable blended tenacity in the range of 16.0 to 20.0 cN/tex.[5]

The elongation of the blend is a carefully calculated compromise between the high stretch of the polyester staple fibers and the moderate stretch of the viscose. Empirical laboratory data indicates that 80/20 PV yarns possess an elongation at break ranging from 10.0% to 14.0%.[5] This moderate extensibility makes the yarn highly stable and predictable during the weaving process, minimizing unpredictable warp sagging while retaining enough elasticity to survive the loom's beat-up phase.

Regarding initial stiffness, pure viscose fibers possess a notably low initial modulus (40.0-50.0 cN/tex), rendering them highly susceptible to early deformation under low stress.[25] The heavy integration of polyester firmly bolsters the structural rigidity of the composite yarn, yielding a blended initial Young's modulus of approximately 70.0 to 90.0 cN/tex.[5] This intermediate modulus is the secret to the yarn's success in the apparel market; it ensures that fabrics woven from 80/20 PV retain sharp, permanent creases and tailored aesthetics essential for formal wear, without feeling overly rigid.[45]

Bifurcated Thermal Dynamics and Dimensional Stability

The thermal behavior of the 80/20 PV yarn represents a bifurcated phenomenon, as the two constituent fibers react to heat and moisture in fundamentally opposing ways. The viscose component is highly hydrophilic and is heavily influenced by moisture (exhibiting hygral expansion), while the polyester component is hydrophobic and responds strictly to thermal energy.

When tested for Boiling Water Shrinkage, the blended yarn experiences dimensional contraction through two simultaneous, competing mechanisms: the thermal, entropic relaxation of the polyester staple fibers, and the swelling-induced structural jamming of the viscose fibers.[51] When viscose absorbs boiling water, it swells radially (increasing its diameter). In a tightly

twisted yarn, this radial swelling forces the yarn to contract longitudinally. Consequently, the BWS for the 80/20 PV blend typically settles between 2.0% and 4.0%.

Under dry heat conditions at 180°C, the thermodynamic response shifts. The viscose remains dimensionally inert (though it may experience slight thermal degradation or yellowing if exposure is prolonged), leaving the polyester fraction to dictate the contraction.[47] The interlocking twist of the spun yarn and the friction generated by the inert viscose fibers physically restrain the polyester fibers, preventing them from shrinking completely freely. As a result, the dry heat shrinkage of the 80/20 PV yarn is heavily dampened compared to a pure continuous polyester filament, reliably registering between 3.0% and 5.0%.[51]

Geometric Configurations and Twist Architecture

Unlike continuous filament yarns, staple fiber blends absolutely require substantial mechanical twist to generate the frictional cohesion necessary to hold the short fibers together.[18] The precisely engineered level of twist dictates both the ultimate breaking strength of the yarn and the final tactile hand-feel of the woven fabric. For an 80/20 PV yarn, typically spun at medium-fine counts such as 30s or 40s Ne, a Twist Multiplier (TM) of 3.5 to 4.0 is universally deployed by Surat spinning mills.[4]

Applying the standard textile twist equation ($TPI = TM \times \sqrt{Ne}$), a 40s count 80/20 PV yarn destined for weaving warp applications requires a precise twist configuration ranging from 22 to 26 TPI.[4]

Parameter Category	80/20 Poly-Viscose Spun Specifications
Tenacity (cN/tex)	16.0 - 20.0
Elongation at Break (%)	10.0 - 14.0
Young's Modulus (cN/tex)	70.0 - 90.0
Boiling Water Shrinkage (%)	2.0 - 4.0

Dry Heat Shrinkage 180°C (%)	3.0 - 5.0
TPI Range (Weaving)	22.0 - 26.0 (Based on TM 3.5 - 4.0)

Structural Integrity and Thermodynamics of 40s Combed Cotton

Despite the massive influx of synthetic fibers, cotton remains the premier natural fiber in the global textile industry. It is highly lauded for its exceptional breathability, moisture absorption, and hypoallergenic properties.[54] The 40s Combed Cotton yarn represents a premium, highly refined tier of spun cellulose. Originating from the superior *Gossypium hirsutum* (Upland) or *Gossypium barbadense* (Extra-Long Staple) species, the raw cotton fibers undergo a rigorous, mechanical combing process prior to the final spinning stage.[17]

This intensive mechanical refinement physically extracts short, immature fibers (known as noils) and aligns the remaining longer, stronger fibers perfectly parallel to the longitudinal axis of the sliver.[18] The result of this exclusionary process is a yarn with drastically reduced mass variation (CVm%), a remarkably lower Imperfection Index (IPI—representing thick places, thin places, and neps), heavily suppressed surface hairiness, and vastly superior tensile endurance compared to standard carded cotton.[56]

Cellulosic Mechanical Profile

Cotton fibers possess a highly unique, naturally evolved micro-morphology. They are characterized by a hollow central canal (the lumen) surrounded by dense, spiraling fibrillar layers of highly crystalline cellulose.[12] The extensive, complex hydrogen-bonding network between these linear cellulose chains imparts a remarkably high intrinsic strength to the fiber.[13]

Because the combing process ensures that mechanical stress is distributed evenly across long, continuous fibers within the yarn matrix, 40s Combed Cotton weaving yarn achieves a robust breaking tenacity ranging from 15.5 to 25.0 cN/tex.[4] Specific industrial quality control logs from top-tier spinning mills for 40s combed weaving (40CW) yarn routinely record an average breaking length (RKM) of 15.8 cN/tex, with high-end, premium gassed variants pushing well toward the 25.0 cN/tex boundary.[4] Notably, unlike viscose, the highly crystalline nature of cotton causes it to exhibit an *increase* in tenacity when wet. The water molecules improve the internal alignment of the cellulose chains, an incredibly advantageous trait that prevents yarn breakage during high-tension aqueous sizing and wet-finishing operations.[58]

The natural convolutions (twists) and the internal spiral angle of the cotton fiber inherently

restrict its overall extensibility. Consequently, the elongation at break for 40s combed cotton is relatively low and unforgiving, strictly bounded between 4.3% and 6.0%.[4] This exceptionally low elasticity demands extreme precision in loom tension control. Because the yarn lacks the viscoelastic stretch capacity to absorb erratic mechanical shocks, poorly calibrated weaving machines will cause immediate warp ruptures.

The dense crystalline structure of the cellulose macromolecules translates directly to a very high initial Young's modulus, frequently measuring between 100.0 and 150.0 cN/tex.[25] This extreme stiffness guarantees extraordinary dimensional stability under low loads, making combed cotton highly resistant to unwanted warp stretching during the repeated shed formations of the weaving cycle.

Thermodynamics, Moisture Regain, and Hygral Shrinkage

As a purely natural cellulosic fiber, cotton absolutely does not exhibit the thermoplastic behavior characteristic of synthetic polymers like polyester.[12] It does not possess a distinct melting point, it does not exhibit a glass transition temperature in a dry state, and its thermal shrinkage mechanism is fundamentally different from that of synthetics.

The shrinkage of cotton in boiling water is almost entirely hygral (moisture-driven) and relaxation-based. When immersed in 100°C water, water molecules rapidly penetrate the amorphous regions of the cellulose, breaking weak secondary hydrogen bonds and allowing the individual fibers to swell laterally.[51] In a highly twisted 40s yarn, this significant lateral expansion forces the fibers to shift, which translates macroscopically into a longitudinal contraction of the yarn—a phenomenon known as relaxation shrinkage.[52] For premium 40s combed cotton, boiling water shrinkage generally sits safely below 2.0%, provided the spinning mill did not subject the yarn to extreme, unnatural tension during winding.

Subjecting 40s combed cotton to 180°C dry heat induces near-zero polymeric contraction.[33] Because cellulose cannot melt or recoil like a synthetic chain, the only measurable change in the yarn's length stems from the total evaporation of its natural moisture regain (which normally sits at approximately 7.0% to 8.0% under standard atmospheric conditions).[12] Consequently, the dry heat shrinkage of 40s combed cotton at 180°C is clinically negligible, consistently registering at $\leq$ 1.0%.[33] However, textile engineers must exercise caution; while the yarn will not shrink, prolonged exposure to 180°C dry heat will cause the cellulose to oxidize, thermally degrade, turn brittle, and suffer severe yellowing.[54]

Geometric Configurations for High-Tension Weaving

To lock the highly aligned, combed cotton fibers into a tensile-resistant structure capable of surviving a modern power loom, a highly precise twist architecture is engineered. For a 40s Ne combed cotton yarn destined specifically for weaving warp applications (where cyclic abrasion resistance against the reed is highly critical), a Twist Multiplier of approximately 3.6 to 4.0 is the industry standard.[4]

Applying the standard twist equation ($TPI = TM \times \sqrt{40}$) yields an optimal TPI range of 22 to 26 Twist Per Inch.[4] This tightly engineered level of twist effectively suppresses yarn hairiness (reducing it to a Uster hairiness index of $\leq$ 5.0), guaranteeing smooth passage through the loom's complex array of drop wires, heald eyes, and the beating reed.[4]

Parameter Category	**40s Combed Cotton Spun Specifications**
Tenacity (cN/tex)	15.5 - 25.0
Elongation at Break (%)	4.3 - 6.0
Young's Modulus (cN/tex)	100.0 - 150.0
Boiling Water Shrinkage (%)	< 2.0
Dry Heat Shrinkage 180°C (%)	< 1.0 (Negligible, prone to degradation)
TPI Range (Weaving)	22.0 - 26.0 (Based on TM 3.6 - 4.0)

Kinematic Constraints of Weft Insertion Mechanisms: Water-Jet vs. Rapier

The successful, economically viable transformation of these highly engineered precursor yarns into woven fabric relies entirely on the kinetic capabilities and physical constraints of the loom. In the Surat textile cluster, the strategic debate between deploying Water-jet looms or Rapier looms is a central operational concern. This decision is not arbitrary; it is dictated entirely by the fundamental physiochemical properties of the specific yarn being processed.[59]

Fluid Dynamics of Water-Jet Weft Insertion

Water-jet looms represent the absolute pinnacle of high-speed, low-energy weft insertion for highly specific, narrowly defined material classes.[60] The mechanism operates by drawing highly purified water through a high-pressure pump and ejecting it through a precision-engineered micro-nozzle. The kinetic energy of the accelerating water droplet captures the tip of the weft yarn and propels it across the open warp shed at extreme velocities.[62] Because the physical mass of the water droplet is minute, the inertial forces generated during the insertion cycle are incredibly low, allowing the loom's main shaft to operate at extraordinary cyclic speeds.[61]

However, the fundamental, inescapable operational constraint of water-jet technology is its strict physical incompatibility with hydrophilic (water-absorbing) textile fibers.[7]

Polyester 75D Filament on Water-Jet: Polyester is inherently and aggressively hydrophobic, featuring a natural moisture regain of merely 0.4%.[13] Because the PET polymer essentially repels water, it does not absorb the mass of the kinetic water jet. This allows the high-pressure water droplet to maintain its extreme velocity and cleanly carry the 75D yarn across the entirety of the shed without losing momentum. For this specific yarn, Water-jet looms are exceptionally efficient, representing the industry standard in Surat. Recommended operational speeds for modern Water-jet setups weaving 75D polyester range from an impressive **800 to 1200 RPM**.[60]

80/20 Poly-Viscose and 40s Combed Cotton on Water-Jet: Both of these spun yarns contain significant cellulosic components (viscose and cotton) that are highly hydrophilic, boasting standard moisture regains of 11-13% and 7-8%, respectively.[18] If these yarns are subjected to a high-pressure water-jet, they instantly absorb the fluid, swelling dramatically within milliseconds.[7] This sudden, massive increase in the yarn's physical mass instantly strips the kinetic energy from the water jet, causing the weft insertion to stall and fail mid-flight. Furthermore, the total saturation of the spun yarns leads to severe post-weaving fabric distortion, incredibly high energy costs for drying, massive mildew risk, and catastrophic warp breakage. Consequently, the recommended Water-jet RPM for both 80/20 Poly-Viscose and 40s Combed Cotton is strictly **0 RPM (Highly Not Recommended)**.[7]

Mechanical Kinematics of Rapier Weft Insertion

The Rapier loom offers a completely different engineering paradigm. It utilizes a mechanical, rigid, or flexible tape-driven system to physically clamp and carry the weft yarn across the shed.[67] In a typical, highly advanced double-rapier setup, a "giver" rapier head securely clamps the yarn and carries it to the exact geometric center of the loom. Here, the yarn is precisely transferred to a "taker" rapier head, which pulls it the remainder of the way to the opposite selvedge.[69] This physical, mechanical clamping ensures absolute, uninterrupted control over the yarn, making the process entirely independent of the yarn's hydrophobicity, physical mass, or aerodynamic profile.[59]

While the Rapier loom is celebrated as universally versatile—capable of seamlessly weaving delicate silks, heavy industrial synthetics, and highly textured, slubby spun blends—the physical mechanical mass of the rapier heads severely limits the maximum achievable kinetic speeds.[61]

The high-speed cyclic acceleration and sudden deceleration of the rapier tapes generate massive internal inertial forces that effectively cap production rates compared to fluid-jet systems.[70]

Polyester 75D Filament on Rapier: The rapier loom smoothly and effortlessly handles the 75D filament without issue. Given the yarn's excellent tenacity (35.0 cN/tex) and generous elongation (19.1%), it easily survives the violent tension spike that occurs during the center-transfer between the giver and taker rapiers. Recommended Rapier speeds for 75D polyester in modern Surat setups range from **350 to 500 RPM**.[6]

80/20 Poly-Viscose on Rapier: The mechanical insertion of the rapier is perfectly and ideally suited for the spun, slightly hairy surface of the PV composite blend.[73] The intermediate Young's modulus and highly reliable elongation ensure minimal breakage during the transfer phase. Recommended operational speeds for PV blends on modern rapier machinery sit comfortably at **350 to 500 RPM**.[71]

40s Combed Cotton on Rapier: The primary challenge of weaving 40s combed cotton lies in its incredibly low elongation profile (4.3% - 6.0%).[4] This lack of stretch requires meticulous, micro-second precision in loom tension control to prevent catastrophic snatch-breaks during the rapier's violent acceleration phase.[4] Advanced, servomotor-driven electronic let-off and take-up motions on modern rapier looms manage this effectively, maintaining constant warp and weft tension. Recommended, safe operating speeds for 40s cotton on rapier machinery are established at **350 to 500 RPM**.[6]

Weft Insertion System	**Polyester 75D Filament**	**80/20 Poly-Viscose**	**40s Combed Cotton**
Water-Jet Loom (Fluid Dynamic)	**800 - 1200 RPM** (Optimal due to hydrophobicity)	**0 RPM** (Incompatible due to hydrophilic swelling)	**0 RPM** (Incompatible due to hydrophilic swelling)
Rapier Loom (Mechanical Clamp)	**350 - 500 RPM** (Inertial mass limits maximum speed)	**350 - 500 RPM** (Ideal for spun blends)	**350 - 500 RPM** (Requires precise tension control due to low elongation)

Computational Integration and JSON Database

Architecture

To effectively integrate the exhaustive mechanical, thermal, geometric, and production data synthesized in this report into a modern computational design engine, the parameters must be rigidly structured into a machine-readable format. The development of a digital twin relies entirely on the accuracy and structural integrity of the underlying data payload.

The JSON architecture provided below has been engineered specifically for seamless integration into a TypeScript interface. It encapsulates the exact numerical ranges, physical tolerances, and kinematic constraints established for Surat's textile ecosystem. The schema rigidly classifies the data into four distinct, logical operational nodes:

1. mechanical for the foundational stress-strain profiles.
2. thermal for thermodynamic dimension stability predictions.
3. geometric for linear density classification and precise twist architecture.
4. production for hard-coded loom compatibility limits.

JSON

```
,
      "elongationAtBreak_percent": [16.1, 22.1],
      "youngsModulus_cN_tex": [90.0, 120.0]
    },
    "thermal": {
      "boilingWaterShrinkage_percent": [2.0, 3.1],
      "dryHeatShrinkage180C_percent": [5.5, 8.0]
    },
    "geometric": {
      "denierOrCount": "75D (83.3 dtex)",
      "tpiRangeForWeaving": "1.5 - 3.0"
    },
    "production": {
      "recommendedWaterJetRPM": ,
      "recommendedRapierRPM":
    }
  },
  {
    "yarnId": "PolyViscose_80_20",
    "material": "80% Polyester / 20% Viscose",
    "type": "Spun Staple Blend",
    "mechanical": {
```

```
      "tenacity_cN_tex": [16.0, 20.0],
      "elongationAtBreak_percent": [10.0, 14.0],
      "youngsModulus_cN_tex": [70.0, 90.0]
    },
    "thermal": {
      "boilingWaterShrinkage_percent": [2.0, 4.0],
      "dryHeatShrinkage180C_percent": [3.0, 5.0]
    },
    "geometric": {
      "denierOrCount": "30s - 40s Ne",
      "tpiRangeForWeaving": "22.0 - 26.0"
    },
    "production": {
      "recommendedWaterJetRPM": ,
      "recommendedRapierRPM":
    }
  },
  {
    "yarnId": "CombedCotton_40s",
    "material": "100% Combed Cotton",
    "type": "Spun Natural Staple",
    "mechanical": {
      "tenacity_cN_tex": [15.5, 25.0],
      "elongationAtBreak_percent": [4.3, 6.0],
      "youngsModulus_cN_tex": [100.0, 150.0]
    },
    "thermal": {
      "boilingWaterShrinkage_percent": [0.0, 2.0],
      "dryHeatShrinkage180C_percent": [0.0, 1.0]
    },
    "geometric": {
      "denierOrCount": "40s Ne",
      "tpiRangeForWeaving": "22.0 - 26.0"
    },
    "production": {
      "recommendedWaterJetRPM": ,
      "recommendedRapierRPM":
    }
  }
]
```


Strategic Implications for Advanced Loom Operations

The integration of these highly specific parameters into a computational design engine transcends simple data archiving; it directly and profoundly informs operational strategy on the factory floor. The interplay between a yarn's mechanical tenacity, its viscoelastic stretch limit, and the loom's kinematic RPM dictates the overall efficiency and profitability of the production line.

For instance, the exceptionally low elongation of the 40s Combed Cotton yarn (4.3% - 6.0%) serves as a hard mechanical limit for loom tuning.[4] If a Rapier loom is pushed beyond its calibrated RPM threshold, or if the electronic let-off motion fails to maintain a perfectly steady tension, the sudden acceleration of the rapier tape will instantly exceed the cotton yarn's capacity to stretch. This results in a catastrophic warp or weft rupture, necessitating machine downtime and operator intervention. Conversely, the high elongation (averaging 19.1%) and superior tenacity of the Polyester 75D yarn act as an inherent kinetic buffer. This buffer comfortably absorbs the extreme fluid-dynamic forces of a Water-jet loom operating at a blistering 1200 RPM, resulting in fewer loom stoppages and significantly higher overall factory efficiency.[3]

Furthermore, the thermal shrinkage metrics embedded in the database provide critical intelligence for the downstream wet-processing and finishing sectors. A design engine utilizing this dataset can autonomously predict the finished, post-processing width of a fabric. A fabric woven entirely of Polyester 75D will undergo a severe geometric contraction (up to 8.0%) during a standard 180°C stenter heat-setting operation.[43] To achieve a target finished width of 60 inches, the design engine must algorithmically instruct the loom to weave the greige fabric at approximately 65 inches to account for this inevitable, heat-induced thermal collapse.

Conversely, fabrics relying heavily on the 40s Combed Cotton warp will require virtually no thermal width compensation in the software model, as the tightly hydrogen-bonded macromolecular structure of cellulose remains almost entirely dimensionally inert under dry heat.[33] Through the meticulous, empirical parameterization of tenacity, Young's modulus, thermal dynamics, and kinematic loom limits, the computational design engine is fully empowered to prevent mechanical failure, optimize industrial energy expenditure, and guarantee the absolute dimensional fidelity of the final woven textile.

Works cited

1. Survey confirms Surat as biggest man-made fabric centre in India, accessed on April 4, 2026, https://timesofindia.indiatimes.com/city/surat/survey-confirms-surat-as-biggest-man-made-fabric-centre-in-india/articleshow/38981862.cms
2. 4 Best Yarn Weaving Machine for Different Yarns - Paramount Looms, accessed on April 4, 2026, https://www.paramountlooms.com/best-yarn-weaving-machine-for-yarns/
3. Hengyi Polyester Yarn Technical Report | PDF - Scribd, accessed on April 4, 2026, https://www.scribd.com/document/678643451/75D-72F-SIM-COA-Hengyi
4. TECHNICAL SPECIFICATION OF 100% COTTON COMBED KNITTING YARN -

Kewalram Textiles, accessed on April 4, 2026, https://www.kewalramtextiles.com/yarn.pdf
5. Effect of annealing on MJS yarn characteristics, accessed on April 4, 2026, https://nopr.niscair.res.in/bitstream/123456789/23613/1/IJFTR%2024%284%29%20242-246.pdf
6. Understanding Rapier Looms: Principles, Components, and Industry Importance, accessed on April 4, 2026, https://www.sinotextilemachinery.com/news/technical-articles/understanding-rapier-looms-principles-components-and-industry-importance.html
7. What are the 3 Modern Power Looms - Types, Advantages & Uses, accessed on April 4, 2026, https://www.paramountlooms.com/modern-power-looms-types-advantages-uses/
8. COMBED YARN FOR KNITTING, accessed on April 4, 2026, https://www.cottonyarnmarket.net/OASMTP/COMBED%20YARN%20FOR%20KNITTING.pdf
9. A Comparison of the Properties of Cotton-Covered Cotton/Polyester Yarns and Fabrics Representing Ring, Friction, and Tandem Spin, accessed on April 4, 2026, https://www.cotton.org/beltwide/proceedings/getPDF.cfm?year=1996&paper=Z017.pdf
10. 40s Yarn Count Conversion Factors | PDF | Yarn | Spinning (Textiles) - Scribd, accessed on April 4, 2026, https://www.scribd.com/document/619303118/Sitra-Conversion-Guide-Lines
11. Nomex® Fiber Technical Guide - DuPont, accessed on April 4, 2026, https://www.dupont.com/content/dam/dupont/amer/us/en/personal-protection/public/documents/en/Nomex(R)%20Fiber%20Technical%20Guide.pdf
12. Shrinkage of Cotton Textiles | Home Laundering - Expert Polymer & Plastics Consulting, accessed on April 4, 2026, https://polymerexpert.biz/blog/167-shrinkage-of-cotton-textiles
13. Textile Conversion Factors and Properties | PDF | Spinning (Textiles) | Pascal (Unit) - Scribd, accessed on April 4, 2026, https://www.scribd.com/document/404705243/Technical-Information-and-data-of-conversion-factor-Important-pdf
14. General Specs: Multifilament Polyester Types Compared - Service Thread, accessed on April 4, 2026, https://www.servicethread.com/blog/general-specs-multifilament-polyester-types-compared
15. Exploring the Benefits of 75% Polyester in Textile Manufacturing and Design, accessed on April 4, 2026, https://www.jiexiangtextile.com/news/75denierpolyester-16008.html
16. Your Guide To Decoding Weaving Yarn Sizes - Warped Fibers, accessed on April 4, 2026, https://warpedfibers.com/decoding-weaving-yarn-sizes/
17. Organic Cotton: A Fiber Classification Guide - Textile Exchange, accessed on April 4, 2026, https://textileexchange.org/app/uploads/2021/04/00_OrganicCottonFiberClassification_Guide2017_FINALforpublishing.pdf

18. What is Combed Cotton Yarn: Properties, Varieties, Uses & Global Market - Fibre2Fashion, accessed on April 4, 2026, https://www.fibre2fashion.com/market-intelligence/texpro-textile-and-apparel/textile-guide/10811/combed-cotton-yarn
19. Static and Dynamic Tensile Behaviour of Spun Yarns: A Critical Review - Emerald Publishing, accessed on April 4, 2026, https://www.emerald.com/rjta/article-pdf/15/4/70/2311595/rjta-15-04-2011-b009.pdf
20. High Tenacity Super Low Shrinkage Polyester Industrial Yarn Manufacturer & Supplier | Runteks.com, accessed on April 4, 2026, https://www.runteks.com/high-tenacity-super-low-shrinkage-polyester-industrial-yarn_p65.html
21. Testing of Fibres, Yarns and Fabrics in Textiles and its Interpretations - International Journal of Advances in Engineering and Management (IJAEM), accessed on April 4, 2026, https://ijaem.net/issue_dcp/Testing%20of%20Fibres,%20Yarns%20and%20Fabrics%20in%20Textiles%20and%20its%20Interpretations.pdf
22. Polyester FDY Yarns: Tenacity, Elongation, and Quality Control, accessed on April 4, 2026, https://www.zjhy-group.com/news/polyester-fdy-yarns-tenacity-elongation-quality-control.html
23. Yarn test methods of Swicofil, accessed on April 4, 2026, https://www.swicofil.com/commerce/basic-information/yarn-manual/test-methods
24. The Relationship Between Elongation, Shrinkage, and Break Strength in Polyester Yarns, accessed on April 4, 2026, https://www.servicethread.com/blog/understanding-the-relationship-between-elongation-shrinkage-and-break-strength-in-industrial-polyester-yarns
25. Research on the Qualities of Cellulosic Yarn - Publisherspanel.com, accessed on April 4, 2026, https://publisherspanel.com/api/files/view/306110.pdf
26. This is the Pre-Published Version. - PolyU Institutional Research Archive, accessed on April 4, 2026, https://ira.lib.polyu.edu.hk/bitstream/10397/102228/1/Tao_Properties_Performances_Fabrics.pdf
27. Percentage changes in tenacity properties of the viscose yarn - ResearchGate, accessed on April 4, 2026, https://www.researchgate.net/figure/Percentage-changes-in-tenacity-properties-of-the-viscose-yarn_tbl3_289959802
28. Effect of Heat Setting Conditions on the Quality of Yarn | Request PDF - ResearchGate, accessed on April 4, 2026, https://www.researchgate.net/publication/338234099_Effect_of_Heat_Setting_Conditions_on_the_Quality_of_Yarn
29. CN1490621A - Method for testing boiling shrinkage of high shrinkage polyester fiber - Google Patents, accessed on April 4, 2026, https://patents.google.com/patent/CN1490621A/en
30. What is ASTM D4974? Hot Air Shrinkage Test for Yarn & Cord Explained - Service Thread, accessed on April 4, 2026,

https://www.servicethread.com/blog/astm-4974-test-method-for-hot-air-thermal-shrinkage-of-yarn-and-cord
31. Basic information of Polyester Staple Fiber - VNPOLYFIBER, accessed on April 4, 2026, https://vnpolyfiber.com/basic-information-of-polyester-staple-fiber/
32. An Overview of Polyester and Polyester Dyeing - Textile Learner, accessed on April 4, 2026, https://textilelearner.net/overview-of-polyester-and-polyester-dyeing/
33. a guide to improved shrinkage performance of cotton fabrics, accessed on April 4, 2026, https://www.cottoninc.com/wp-content/uploads/2017/12/ISP-1009-Guide-to-Improved-Shrinkage-Performance-of-Cotton-Fabrics.pdf
34. General High Tenacity Polyester Industrial Yarn Manufacturer & Supplier | Runteks.com, accessed on April 4, 2026, https://www.runteks.com/general-high-tenacity-polyester-industrial-yarn_p60.html
35. High-Speed Modern Weaving Facility - Invest in Gujarat, accessed on April 4, 2026, https://indextbdemo.orpgujarat.com/files/2024/2/0ad2af4b-47a4-418c-a558-e8d36a08e3e4_Modern%20Weaving%20Facility.pdf
36. 75D/72F polyester filament yarn--Globaltextiles.com, accessed on April 4, 2026, https://m.globaltextiles.com/product/75D72F-polyester-filament-yarn-117055.html
37. EP0456495A2 - A drawn polyester yarn having a high tenacity, a high initial modulus and a low shrinkage - Google Patents, accessed on April 4, 2026, https://patents.google.com/patent/EP0456495A2/en
38. US6759123B2 - High strength and low shrinkage polyester yarn and process for its preparation - Google Patents, accessed on April 4, 2026, https://patents.google.com/patent/US6759123B2/en
39. Polyester High Tenacity Yarn - Textile Petrochemicals Products Exporter - URMPL, accessed on April 4, 2026, https://www.urmpl.com/high-tenacity-yarn/
40. Elastic recovery of elastomeric-polyester-based staple yarns and filaments, accessed on April 4, 2026, https://or.niscpr.res.in/index.php/IJFTR/article/download/7468/3946/68669
41. Effect of Thermal Aging on the Mechanical Properties of High Tenacity Polyester Yarn - PMC, accessed on April 4, 2026, https://pmc.ncbi.nlm.nih.gov/articles/PMC8037231/
42. Virgin Grade Polyester Tops for Spun Yarn Use - Top and Polyester, accessed on April 4, 2026, https://m.made-in-china.com/product/Virgin-Grade-Polyester-Tops-for-Spun-Yarn-Use-1912990195.html
43. TEXTILE MECHATRONICS - Bharat Skills, accessed on April 4, 2026, https://bharatskills.gov.in/pdf/E_Books/TextileMech3Sem_TT.pdf
44. What is Viscose Yarn: Properties, Varieties, Uses & Global Market - Fibre2Fashion, accessed on April 4, 2026, https://www.fibre2fashion.com/market-intelligence/texpro-textile-and-apparel/textile-guide/10654/viscose-yarn
45. Polyester /Viscose – Economic Uniform - Fibre2Fashion, accessed on April 4, 2026, https://static.fibre2fashion.com/articleresources/PdfFiles/57/5691.pdf

46. Combed Cotton Modal 50/50 40s Compact Siro Yarn - Hebei Xueyang Textile Co., Ltd., accessed on April 4, 2026, https://www.xueyangtextile.com/product-combed-cotton-modal-50.html
47. Explain What Are The Common Specifications Of Viscose Yarn? - News, accessed on April 4, 2026, https://www.cnhago.com/news/explain-what-are-the-common-specifications-of-47624953.html
48. Analysis of Physico-Mechanical Properties of Jute and Polyester Blended Yarn - SciSpace, accessed on April 4, 2026, https://scispace.com/pdf/analysis-of-physico-mechanical-properties-of-jute-and-1c6bv9at9v.pdf
49. TR 80/20 Polyester Viscose Fabric-Shijiazhuang Jiexiang Textile|Wrinkle-Resistant&Breathable, accessed on April 4, 2026, https://www.jiexiangtextile.com/news/tr-80-20-polyester-viscose-fabric-shijiazhuang-jiexiang-textile-wrinkle-resistant-amp-breathable.html
50. Effect of blended cotton on dimensional properties of weft knitted fabrics - CABI Digital Library, accessed on April 4, 2026, https://www.cabidigitallibrary.org/doi/pdf/10.5555/20123306926
51. Fabric Shrinkage: Test Methods, Calculations, and Data for Common Fabrics Across Processes (Natural, Dry Heat, Wet Heat, and Washing), accessed on April 4, 2026, https://www.testextextile.com/fabric-shrinkage-test-methods-calculations-and-data-for-common-fabrics-across-processes-natural-dry-heat-wet-heat-and-washing/
52. Textile Fabric Shrinkage: Causes and Testing Methods | WLH TEX, accessed on April 4, 2026, https://www.wlhtex.com/en/textile-fabric-shrinkage-causes-and-testing-methods/
53. The Effects of Heat-Setting on the Properties of Polyester/Viscose Blended Yarns - SciSpace, accessed on April 4, 2026, https://scispace.com/pdf/the-effects-of-heat-setting-on-the-properties-of-polyester-1pa61gn881.pdf
54. Does Cotton Shrink? Reasons and Care Instructions from Experts - Sino Silk, accessed on April 4, 2026, https://snsilk.com/does-cotton-shrink/
55. Cotton Spun Yarns for Knit and Woven Fabrics, accessed on April 4, 2026, https://www.cottoninc.com/wp-content/uploads/2017/12/ISP-1006-Cotton-Spun-Yarns-for-Knit-and-Woven-Fabrics.pdf
56. (PDF) Effect of Ring and Compact Cotton Spun Yarn characteristics on Physical and Comfort Properties of Knitted Fabrics - ResearchGate, accessed on April 4, 2026, https://www.researchgate.net/publication/289519169_Effect_of_Ring_and_Compact_Cotton_Spun_Yarn_characteristics_on_Physical_and_Comfort_Properties_of_Knitted_Fabrics
57. Yarn Specifications – T.T. LIMITED, accessed on April 4, 2026, https://tttextiles.com/products/yarn/yarn-specifications/
58. The effects of heat-setting on the properties of polyester/viscose blended yarns, accessed on April 4, 2026,

https://www.researchgate.net/publication/289415906_The_effects_of_heat-setting_on_the_properties_of_polyesterviscose_blended_yarns
59. Rapier Loom vs Air Jet Loom: Which Is Better for Your Textile Production?, accessed on April 4, 2026, https://en.kingtex.com/News_details/35.html
60. Water Jet Loom Manufacturers & Exporters in Gujarat, India, accessed on April 4, 2026, https://www.alconetex.com/water-jet-loom.php
61. Comparative Analysis of Water Jet Looms and Rapier Looms in PE Woven Fabric Production - Knowledge, accessed on April 4, 2026, https://www.weavingmc.com/info/comparative-analysis-of-water-jet-looms-and-ra-95710190.html
62. 3 Best Modern Textile Yarn Weaving Loom Machines – Its Features & Uses - Weavetech, accessed on April 4, 2026, https://www.weavetech.com/3-best-modern-textile-yarn-weaving-loom-machines-its-features-uses/
63. Water Jet Looms: 5-Point Guide to Choosing the Right Machine - VieTextile, accessed on April 4, 2026, https://vietextile.com/en/water-jet-loom/
64. 5 Key Advantages of Using Water Jet Looms in Synthetic Fabric Production, accessed on April 4, 2026, https://www.waterjetloom.com/5-Key-Advantages-of-Using-Water-Jet-Looms-in-Synthetic-Fabric-Production-id47897306.html
65. Raw White Hanks, accessed on April 4, 2026, https://www.jxoujin.com/products/raw-white-hanks.html
66. Indian textile industry organisations object to RPM criteria for weaving machine BCD exemption | Manufacturing News India, accessed on April 4, 2026, https://apparelresources.com/business-news/manufacturing/indian-textile-industry-organisations-object-rpm-criteria-weaving-machine-bcd-exemption/
67. Rapier Loom in Surat - IndiaMART, accessed on April 4, 2026, https://www.indiamart.com/proddetail/rapier-looms-9442128848.html
68. 5 ways to choose Best Rapier Loom Machine Manufacturer in Surat for Fabric Production?, accessed on April 4, 2026, https://www.paramountlooms.com/rapier-loom-machine-manufacturer/
69. Rapier Loom Machine - Anjali Liberty Textiles, accessed on April 4, 2026, https://www.altindia.in/rapier-loom-machine-3/
70. Yarn Quality Requirement for High Speed Weaving Machines - Fibre2Fashion, accessed on April 4, 2026, https://static.fibre2fashion.com/articleresources/PdfFiles/69/6810.pdf
71. High Speed Rapier Loom Machine Manufacturer from Surat, accessed on April 4, 2026, https://www.armylooms.in/rapier-loom-machine.html
72. Rapier Weaving Loom Price & Specifications | Orange Weaving Engineering Pvt. Ltd. - Aajjo, accessed on April 4, 2026, https://www.aajjo.com/product/rapier-weaving-loom-in-surat-orange-weaving-engineering-pvt-ltd
73. The Difference Between Rapier Loom and Air Jet Loom, accessed on April 4, 2026, https://www.ssjacquard.com/news/the-difference-between-rapier-loom-and-air-jet-l

oom-189170.html