

## **ScienceDirect**



## **Review Article**

# A roadmap of battery separator development: Past and future



Junghyun Choi<sup>1</sup> and Patrick Joohyun Kim<sup>2</sup>

#### **Abstract**

The battery separator is one of the most essential components that highly affect the electrochemical stability and performance in lithium-ion batteries. In order to keep up with a nationwide trend and needs in the battery society, the role of battery separators starts to change from passive to active. Many efforts have been devoted to developing new types of battery separators by tailoring the separator chemistry. In this article, the overall characteristics of battery separators with different structures and compositions are reviewed. In addition, the research directions and prospects of separator engineering are suggested to provide a solid guideline for developing a safe and reliable battery system.

#### Addresses

<sup>1</sup> Energy Storage Materials Center, Korea Institute of Ceramic Engineering and Technology, Jinju, 52851, South Korea

<sup>2</sup> Department of Applied Chemistry, Kyungpook National University, Daegu, 41566, South Korea

Corresponding author: Kim, Patrick Joohyun (pjkim@knu.ac.kr)

## Current Opinion in Electrochemistry 2022, 31:100858

This review comes from a themed issue on Energy Storage (2022)

Edited by Jang Wook Choi and Yan Yao

For complete overview about the section, refer Energy Storage (2022)

Available online 10 November 2021

https://doi.org/10.1016/j.coelec.2021.100858

2451-9103/© 2021 Elsevier B.V. All rights reserved.

#### Keywords

Battery separator, Next-generation batteries, Battery safety, Polyolefin separator, Surface-modified separator, Ceramic-coated separator, Solid-state electrolyte.

#### Introduction

With the increasing demand for high-performing electronic devices and a global mission to reduce greenhouse gases created by fossil fuels, tremendous attention has been paid to the development of rechargeable energy storage systems, especially for lithium-ion batteries (LIBs) [1–4]. Since the advent of practical LIBs in our everyday life, numerous researches have been performed by replacing each of the battery components with new types of materials in order to improve the energy/power density, electrochemical stability, and

cyclability of LIBs [5–9]. Among the essential components, a battery separator is the main component responsible for the overall safety of batteries [10–12]. The major role of the battery separator is to physically isolate the anode from the cathode while allowing mobile Li-ions to transport back and forth [13]. Unfortunately, two technical challenges associated with separator puncture and significant thermal shrinkage of polymer separators threaten the overall safety of batteries. In addition, most researches have mainly focused on reducing the total thickness of the battery separator and increasing the size of battery packs, i.e. putting large amount of active materials into the battery [14,15]. This approach also raises serious safety concerns with respect to short circuits [14,15].

In order to keep up with the recent needs from industries and improve the safety issues, the battery separator is now required to have multiple active roles [16,17]. Many tactical strategies have been proposed for the design of functional separators [10]. One of the representative approaches is to coat a functional material onto either side (or both sides) of the battery separator [18–21]. This conceptual idea has been already attempted by battery industries (Samsung SDI, LG Chem., etc.) in order to strengthen the mechanical—thermal properties, as well as improve the electrolyte wettability of polyolefin separators [22–24]. With the adoption of the ceramic-coated-separator (CCS), LIBs have delivered improved electrochemical performances even at elevated temperatures. In addition, the thermal stability and mechanical strength of CCSs are dramatically enhanced in comparison with a pristine polyethylene separator [22]. In this regard, the approach of tailoring the surface of the polyolefin separator can be an efficient and effective way to improve both electrochemical performance and stability of LIBs.

However, there are remaining issues to be resolved in the current battery system paired with CCSs. Furthermore, there would be more potential problems when moving on to an advanced battery system with Li anode. For instance, when metallic Li is introduced as an anode in the battery, unexpected events (e.g. Li dendrite growth) could result in even more serious safety issues [25,26]. In addition, it is no longer useful to use the CCS after hundreds of cycles since the ceramic layer is fully covered by Li. The deposited Li would play a part as another Li source inside the cell. Considering these points, it is of importance to develop a stable and reliable battery separator compatible with high-performance LIBs. For a clear insight into the next-generation separator, the categories of membranes are classified into three phases according to the technological paradigm.

## Separator design


Figure 1 illustrates how each phase of the battery separators plays a role in affecting the morphology of the deposited Li on the electrode and thus protecting the battery from safety hazards. Polyolefin separators (termed 'first-phase membrane') have high porosity and insulative properties [13]. But these are easily deformed by thermal or mechanical stress, which makes the polyolefin separator vulnerable to the penetration of growing Li dendrites (Figure 1a) [27]. Compared with the polyolefin separator, the surface-modified separator (termed 'second-phase membrane') is physically/thermally more stable and strong, which significantly reduces the risk of Li dendrite penetration (Figure 1b)

[22]. However, since the fundamental causes of dendritic Li growth are not eliminated, and the penetration of Li dendrite across the surface-modified separator is realistically inevitable, it would eventually put the cell in danger after hundreds of cycles. In this regard, the utilization of solid-state electrolyte (termed 'third-phase membrane') served as an electrolyte and separator would be the feasible strategy to reduce potential safety issues originating from Li metal-based batteries (Figure 1c) [28].

## First-phase membrane: polyolefin separator

Two representative polyolefins, i.e. polypropylene (PP) and polyethylene (PE), are typically used for fabricating battery separators [13]. Methodologies to fabricate battery separators are sorted into two methods: (1) wet method and (2) dry method [13]. The separator prepared by the wet method has interconnected pores through the entire area (Figure 2a). On the other hand, the separator fabricated by dry method has plenty of slit-like pores (Figure 2b). In general, the extensive uses of the polyolefin separator are limited by three major drawbacks. The first one is the huge thermal shrinkage at high temperatures (Figure 2e) [29]. The internal short-circuit


Figure 1



Schematics illustrating the roles of each membrane on Li deposition and battery safety. The categories of membranes are classified into three phases according to the technological paradigm: (a) first-phase membrane (Polyolefin separator), (b) second-phase membrane (Surfaced-modified separator), (c) third-phase membrane (Solid-state electrolyte).

caused by the contraction of the separator places the cell in a dangerous event such as a battery explosion [30]. For improving the thermal shrinkage problem of typical polyolefin separators, the tri-layered separator with PP/ PE/PP architecture has been utilized (Figure 2c-d) [13,31]. The second one is the poor liquid electrolyte absorption and wettability, which affects the internal resistance of LIBs (Figure 2f) [32]. The last one is that the minimum modulus (6.4 GPa) to suppress the penetration of Li dendrite is larger than the elastic modulus of PP separators (2.1 GPa), inevitably allowing the piercing of Li dendrite across the separator [33]. Therefore, it

Figure 2



Polyolefin separators. Top-view scanning electron microscopy (SEM) images of separators made by (a) a wet method and (b) a dry method. (c) Top view and (d) cross-sectional SEM images of a tri-layered separator with PP/PE/PP architecture (Reproduced with permission from Ref. [13]. Copyright 2004 American Chemical Society). (e) Thermal shrinkage tests of a pristine PP separator and a tri-layer PP/PE/PP separator (Reproduced with permission from Ref. [29]. Copyright 2020 Multidisciplinary Digital Publishing Institute). (f) Poor wettability of a polyolefin-based separator with liquid electrolyte (Reproduced with permission from Ref. [34]. Copyright 2016 Elsevier).

would be highly desirable to develop a new membrane with improved thermal/mechanical properties and electrolyte wettability.

## Second-phase membrane: surface-modified separator


In order to address the latent issues with regard to thermal shrinkage and electrolyte wettability, a number of strategies have been proposed by coating a ceramic layer, depositing a metal layer, and forming a polymeric layer on the surface of polyolefin separators (Figure 3a) [35-41].

Nitrides, oxides, carbons, etc., can be employed as surface-coating materials for manufacturing surfacemodified separators. A few research groups have demonstrated the effect of a nitride layer comprising either BN or AlN on managing the localized heat generated inside the cell and homogenizing Li<sup>+</sup> flux (Figure 3b-d) [21,42-44]. Under these influences, the formation of dendritic Li was noticeably suppressed, and the efficiency of Li plating/stripping was dramatically improved [42,43]. Oxides are known to be effective in improving the surface wettability with liquid electrolyte and the mechanical/thermal stability against high temperature when it is formed on the polymer separators [18,35,45]. For example, the CCS prepared by coating either Al<sub>2</sub>O<sub>3</sub> or Mg(OH)<sub>2</sub> on the PE separator has exhibited improved thermal/mechanical stability and electrolyte wettability (Figure 3e-f) [22]. All these kinds of approaches have shown promising results in improving both stability and performance of LIBs.

#### Third-phase membrane: solid-state electrolytes

The adoption of solid-state electrolytes is the most promising option to eliminate the safety concerns with regard to the combination system of a polymer separator and liquid electrolyte [46,47]. The two basic roles of solid-state electrolytes are as follows: (1) a separator between electrodes and (2) a medium to transfer Li<sup>+</sup> between cathode and anode. For the practical use of solid-state electrolytes, it needs to meet the basic requirements for high mechanical/electrochemical stability and ionic conductivity [48]. Typically, solid-state electrolytes satisfying the above-described specifications can be classified into two major categories: (1) solid-polymer-electrolyte (SPE) and (2) solid-inorganicelectrolyte (SIE). Although there are numerous advantages of SPE (especially polyethylene oxide-based electrolyte), it could not circumvent fundamental safety issues (e.g. thermal runaway), which typically occur in the liquid-electrolyte system [48,49]. On the contrary, SIE is a strong candidate that can ameliorate many safety problems in terms of thermal/electrochemical stability [50-52]. The configuration and thermal/electrochemical stability of each battery with each polymer separator, oxide-based solid electrolytes,

Figure 3




**Surface-modified separators.** (a) Schematic illustration of separator coating process and configuration of the surface-modified separator. Cross-sectional SEM images of nitride material-coated separator: (b) a BN-coated separator (Reproduced with permission from Ref. [43]. Copyright 2015 American Chemical Society), (c) a BN|PP|Carbon separator (Reproduced with permission from Ref. [21]. Copyright 2017 Springer Nature), and (d) an AlN-coated separator (Reproduced with permission from Ref. [42]. Copyright 2019 American Chemical Society). Cross-sectional SEM images of (e) an Al<sub>2</sub>O<sub>3</sub>-coated separator and (f) an Mg(OH)<sub>2</sub>-coated separator (Reproduced with permission from Ref. [22]. Copyright 2019 Elsevier).

and sulfide-based solid electrolytes are illustrated in Figure 4a-d.

Among oxide-based solid electrolytes, LiPON and garnet-type lithium electrolytes are considered the promising solid electrolytes for practical all-solid-state-batteries (ASSBs), due to their excellent thermal stability and decent ionic conductivity [50]. Lithium phosphorous oxynitride (LiPON) is an amorphous-type oxide-based solid electrolyte [53,54]. The main features of LiPON are its high stability against metallic lithium, a wide potential window of 0-5.5 V vs. Li/Li<sup>+</sup>, and an extremely high shear modulus of 77 GPa. However, it has relatively low ionic conductivity ( $1-3 \times 10^{-6} \text{ S cm}^{-1}$  at R.T.), which limits its application to thin-film micro-batteries [47,55]. Garnet-type lithium

electrolyte is a crystalline oxide-based solid electrolyte. It has a decent ionic conductivity  $(0.1-1 \text{ mS cm}^{-1})$ , excellent compatibility with Li, a wide potential window, and high stability under chemical/electrochemical conditions [56-58]. Unfortunately, garnettype solid electrolytes have several critical issues inhibiting the practical use for commercial batteries, such as a poor solid—solid interface contact and a phase transformation from cubic to tetragonal [52,59]. In addition, the polycrystalline microstructure of SIE undermines the battery safety because it allows the propagation of Li dendrites through structural heterogeneities [60,61]. The high manufacturing cost and the sample preparation steps, i.e. sintering at high temperatures, also restrict the mass production of ASSBs [62].

Figure 4



Schematic illustration of the configuration of each battery with different membrane. (a) Polymer-based separator (Reproduced with permission from Ref. [74]. Copyright 2019 Elsevier), (b) amorphous thin-film solid-state electrolyte (LiPON) (Reproduced with permission from Ref. [54]. Copyright 2012 American Chemical Society), and (c) crystalline solid-state electrolyte (Sulfide, oxide, etc.) (Reproduced with permission from Ref. [75]. Copyright 2014 Elsevier). (d) Comparison of each separator/membrane in terms of thermal/electrochemical stability.

Sulfide-based solid electrolytes have been regarded as the most practical solid-state electrolyte for high-power applications (e.g., EVs) because of a high ionic conductivity comparable to typical liquid electrolyte and a high Li transference number [63]. In addition, the soft and deformable feature and relatively favorable manufacturing process (i.e., cold pressing) of sulfidebased electrolytes would be able to overcome the inherent weaknesses of oxide-based solid electrolytes [64,65]. Basically, sulfide-based solid electrolytes suffer from a rapid decomposition at the interface between Li metal and sulfide electrolyte, giving rise to the formation of an interphase layer [66]. Among sulfide-based electrolytes, Li-argyrodites (Li<sub>6</sub>PS<sub>5</sub>X (X = Cl, Br, I)) have drawn special attention due to a relatively slow reaction at the Li metal-solid electrolyte interface, a high ionic conductivity  $(10^{-5} - 10^{-3} \text{ S cm}^{-1})$ , and a wide potential window (up to 7 V vs. Li/Li<sup>+</sup>), rendering it as a practical solid electrolyte close to commercialization [67–70]. However, these are particularly vulnerable to the exposure of moisture in the air, leading to the generation of toxic H<sub>2</sub>S gas, and thus, the breakup of metal-sulfide bonds [63]. In addition, it is observed that Li dendrites are formed even in the sulfide electrolyte system [71-73]. All these unwanted events would cause serious safety issues like battery explosion and require a rigorous battery assembly process, i.e., processing and handling of sulfide electrolytes under a strictly controlled inert atmosphere [28]. To address the challenges of sulfide electrolytes, further studies would be inevitable as follow-up works.

#### Conclusion and outlook

Despite the remarkable advancement of separator technology, it is still not able to eliminate the root cause of unexpected threats such as dendritic Li formation. The adoption of solid-state electrolytes would be the feasible solution to circumvent most of the safety hazards with regard to thermal runaway and short-circuit. However, the relatively low ionic conductivity and high interfacial resistance of solid-state electrolytes are the two biggest obstacles for facilitating the operation of high-power electronic devices. Considering these points, it would be necessary to sort each type of the batteries in terms of specific purposes of use. For instance, solid-state batteries would be more suitable for applications requiring high energy density and longterm durability. In contrast, liquid-electrolyte LIBs with an advanced separator would be more appropriate for applications requiring high-power densities. In this regard, extensive researches on both surface-modified separator (second-phase membrane) and solid-state electrolyte (third-phase membrane) should be conducted in parallel to meet each of the requirements from the different applications.

In the future, the most important part of the advanced separator research is how to reduce the thickness of the coating-layer on the separator without sacrificing the electrochemical performance and stability. The studies on scaling-up the solid-state electrolyte from laboratory industrial level, establishing a cost-effective manufacturing process, and exploring the fundamental solution to safety problems in the liquid-electrolyte LIB would become even more important. To keep up with this trend and make the current LIB system safer and better, a concerted effort has to be made for advanced separator development.

## **Funding**

This research was supported by Basic Science Research Program through the National Research Foundation of Korea (NRF), funded by the Ministry of Education (2021R1F1A1059892), and the National R&D Program through the National Research Foundation of Korea (NRF) funded by the Ministry of Science and ICT (2021M3C1C3097516).

#### **Author contributions**

All authors wrote the manuscript. All authors have given approval to the final version of the manuscript.

## **Declaration of competing interest**

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

## References

- Dresselhaus MS, Thomas IL: Alternative energy technologies. Nature 2001, 414:332–337.
- Scrosati B: History of lithium batteries. J Solid State Electrochem 2011, 15:1623–1630.
- 3. Yoshino A: The birth of the lithium-ion battery. Angew Chem Int Ed 2012, 51:5798–5800.

Prof. Yoshino is one of the battery inventors. This paper describes the history of rechargeable lithium-ion batteries. It inspires many researchers to explore new types of advanced materials for better batteries.

- 4. Hu Y-S: Batteries: getting solid. Nature Energy 2016, 1:1-2.
- Zeng W, Xia F, Tian W, Cao F, Chen J, Wu J, Song R, Mu S: Single-crystal high-nickel layered cathodes for lithium-ion batteries: advantages, mechanism, challenges and approaches. Current Opinion in Electrochemistry 2022, 31:100831.
- Ue M, Uosaki K: Recent progress in liquid electrolytes for lithium metal batteries. Current Opinion in Electrochemistry 2019, 17:106–113.
- Ren W-F, Zhou Y, Li J-T, Huang L, Sun S-G: Si anode for nextgeneration lithium-ion battery. Current Opinion in Electrochemistry 2019, 18:46–54.
- Song T, Choi J, Paik U: Freestanding rGO-SWNT-STN composite film as an anode for Li ion batteries with high energy and power densities. Nanomaterials 2015, 5:2380–2390.
- Choi J, Lee S, Ha J, Song T, Paik U: Sol-gel nanoglues for an organic binder-free TiO2 nanofiber anode for lithium ion batteries. Nanoscale 2013, 5:3230–3234.
- 10. Kim PJ: Surface-functionalized separator for stable and reliable lithium metal batteries: a review. Nanomaterials 2021, 11:2275. This paper describes the strategy of modifying the surface nature of polymer-based separators with functional materials. The surface-coating materials are described into six categories according to the material characteristics.
- Ren W, Zheng Y, Cui Z, Tao Y, Li B, Wang W: Recent progress of functional separators in dendrite inhibition for lithium metal batteries. Energy Storage Mater 2020.

- Lagadec MF, Zahn R, Wood V: Characterization and performance evaluation of lithium-ion battery separators. Nature Energy 2019, 4:16–25.
- Arora P, Zhang ZJ: Battery separators. Chem Rev 2004, 104: 4419–4462.

This paper describes the general characteristics and fabrication methods of battery separators. Most of the papers refer to this paper when designing new types of separators.

- Orendorff CJ: The role of separators in lithium-ion cell safety. Electrochem Soc Interface 2012. 21:61.
- Zhang SS: A review on the separators of liquid electrolyte Liion batteries. J Power Sources 2007, 164:351–364.
- Luiso S, Fedkiw P: Lithium-ion battery separators: recent developments and state of art. Current Opinion in Electrochem 2020, 20:99–107.
- Costa CM, Lanceros-Mendez S: Recent advances on battery separators based on poly(vinylidene fluoride) and its copolymers for lithium-ion battery applications. Current Opinion in Electrochem 2021, 29:100752.
- Kim PJ, Kim K, Pol VG: Uniform metal-ion flux through interface-modified membrane for highly stable metal batteries. Electrochim Acta 2018, 283:517–527.

This paper proved the concept that inorganic materials with high porosity are able to homogenize Li+ and prevent the piercing of Li dendrite across the polyolefin separator.

- Kim PJ, Narayanan S, Xue J, Thangadurai V, Pol VG: Li-lon-Permeable and electronically conductive membrane comprising garnet-type Li6La3Ta1. 5Y0. 5O12 and graphene toward ultrastable and high-rate lithium sulfur batteries. ACS Appl Energy Mater 2018, 1:3733-3741.
- Kim PJ, Fontecha HD, Kim K, Pol VG: Toward highperformance lithium-sulfur batteries: upcycling of LDPE plastic into sulfonated carbon scaffold via microwavepromoted sulfonation. ACS Appl Mater Interfaces 2018, 10: 14827-14834.
- Kim PJH, Seo J, Fu K, Choi J, Liu Z, Kwon J, Hu L, Paik U: Synergistic protective effect of a BN-carbon separator for highly stable lithium sulfur batteries. NPG Asia Mater 2017, 9: 375.
- 22. Jung B, Lee B, Jeong Y-C, Lee J, Yang SR, Kim H, Park M: Thermally stable non-aqueous ceramic-coated separators with enhanced nail penetration performance. *J Power Sources* 2019, 427:271–282.

This is a paper showing how to analyze battery safety, using a variety of techniques. Also, the advantages of ceramic-coated separators are described in the paper.

- Alamgir M, Ketkar S, Yoo K: Recent progresses of LG Chem's large-format Li ion polymer batteries. In IEEE power and energy society general meeting. IEEE; 2011:1–4.
- 24. Ryu S, Sugimoto T, Kim J, Park K, Im D, Lee Y-G, Choi JW: Synergistic composite coating for separators in lithium metal batteries. ACS Appl Energy Mater 2021, 4:5237–5245.
- Liu D-H, Bai Z, Li M, Yu A, Luo D, Liu W, Yang L, Lu J, Amine K, Chen Z: Developing high safety Li-metal anodes for future high-energy Li-metal batteries: strategies and perspectives. Chem Soc Rev 2020, 49:5407–5445.
- Lin D, Liu Y, Cui Y: Reviving the lithium metal anode for highenergy batteries. Nat Nanotechnol 2017, 12:194–206.

This paper describes why the Li metal anode is important for future applications. Inherent issues of Li metal as an anode are well described as well. This work has opened a new avenue to overcome the limits of current battery systems.

- Martinez-Cisneros C, Antonelli C, Levenfeld B, Varez A, Sanchez J: Evaluation of polyolefin-based macroporous separators for high temperature Li-ion batteries. Electrochim Acta 2016, 216:68–78.
- Kim KJ, Balaish M, Wadaguchi M, Kong L, Rupp JL, Li Solid-State: Metal batteries: challenges and horizons of oxide and sulfide solid electrolytes and their interfaces. Adv Energy Mater 2021, 11:2002689.

- 29. Hao W, Kong D, Xie J, Chen Y, Ding J, Wang F, Xu T: Selfpolymerized dopamine nanoparticles modified separators for improving electrochemical performance and enhancing mechanical strength of lithium-ion batteries. Polymers 2020, 12:
- 30. Wang M, Chen X, Wang H, Wu H, Jin X, Huang C: Improved performances of lithium-ion batteries with a separator based on inorganic fibers. J Mater Chem 2017, 5:311-318.
- 31. Venugopal G, Moore J, Howard J, Pendalwar S: Characterization of microporous separators for lithium-ion batteries. J Power Sources 1999. 77:34-41.
- 32. Zheng H, Zhou X, Cheng S, Xia R, Nie S, Liang X, Sun Y, Xiang H: High-voltage LiNi0. 5Mn1. 5O4 cathode stability of fluorinated ether based on enhanced separator wettability. *J Electrochem Soc* 2019, **166**:A1456.

This paper provided the result that polyolefin-based separators have poor wettability with liquid electrolyte, which is proved by contact angle measurement. To address this issue, many researches are carried out by functionalizing the surface of the separator.

- Hao Z, Zhao Q, Tang J, Zhang Q, Liu J, Jin Y, Wang H: Functional separators towards the suppression of lithium dendrites for rechargeable high-energy batteries. Materials Horizons 2021, 8:12-32.
- 34. Xie Y, Zou H, Xiang H, Xia R, Liang D, Shi P, Dai S, Wang H: Enhancement on the wettability of lithium battery separator toward nonaqueous electrolytes. J Membr Sci 2016, 503: 25-30.
- Liu K, Zhuo D, Lee HW, Liu W, Lin D, Lu Y, Cui Y: **Extending the** life of lithium-based rechargeable batteries by reaction of lithium dendrites with a novel silica nanoparticle sandwiched separator. Adv Mater 2017, 29:1603987.
- Liu Y, Xiong S, Wang J, Jiao X, Li S, Zhang C, Song Z, Song J: Dendrite-free lithium metal anode enabled by separator engineering via uniform loading of lithiophilic nucleation sites. Energy Storage Materials 2019, 19:24-30.
- 37. Chen X. Zhang R. Zhao R. Qi X. Li K. Sun Q. Ma M. Qie L. Huang Y: A "dendrite-eating" separator for high-areal-capacity lithium-metal batteries. Energy Storage Mater 2020,
- 38. Ryou MH, Lee DJ, Lee JN, Lee YM, Park JK, Choi JW: Excellent cycle life of lithium-metal anodes in lithium-ion batteries with mussel-inspired polydopamine-coated separators. *Adv Energy Mater* 2012, **2**:645–650.

This is the paper showing how to improve the electrolyte wettability and cycle stabilit of lithium-ion batteries, using polydopamine. Dopamine was polymerized on the polyolefin separator. This approach opens an avenue to functionalize the surface of the polymer separator using aqueous ink/slurry.

- Kim PJ, Pol VG: High performance lithium metal batteries enabled by surface tailoring of polypropylene separator with a polydopamine/graphene layer. Adv Energy Mater 2018, 8: 1802665.
- Kim PJ, Kim K, Pol VG: A comparative study of cellulose derived structured carbons on the electrochemical behavior of lithium metal-based batteries. Energy Storage Mater 2019, **19**:179-185.
- 41. Kim K, Kim PJ, Chowdhury RA, Kantharaj R, Candadai A, Marconnet A, Pol VG, Youngblood JP: Structural orientation effect of cellulose nanocrystals (CNC) films on electrochemical kinetics and stability in lithium-ion batteries. Chem Eng J 2021, 417:128128.
- 42. Kim PJH, Pol VG: Surface functionalization of a conventional polypropylene separator with an aluminum nitride layer toward ultrastable and high-rate lithium metal anodes. ACS Appl Mater Interfaces 2019, 11:3917-3924.

  This is the first paper using AIN nanoparticles to alter the surface

nature of polyolefin separators. It also proved that nitride-based materials have an effect on suppressing the formation of sharp Li dendrite.

43. Luo W, Zhou L, Fu K, Yang Z, Wan J, Manno M, Yao Y, Zhu H, Yang B, Hu L: A thermally conductive separator for stable Li metal anodes. *Nano Lett* 2015, **15**:6149–6154.

Prof. Hu first demonstrated the use of nitride materials for controlling the growth of Li dendrite. Temperature analysis using an IR camera proved that BN is able to distribute the localized heat formed over the polyolefin separator.

- 44. Rodriguez JR, Kim PJ, Kim K, Qi Z, Wang H, Pol VG: Engineered heat dissipation and current distribution boron nitride graphene layer coated on polypropylene separator for high performance lithium metal battery. J Colloid Interface Sci 2021,
- 45. Jeon H, Jin SY, Park WH, Lee H, Kim H-T, Ryou M-H, Lee YM: Plasma-assisted water-based Al2O3 ceramic coating for polyethylene-based microporous separators for lithium metal secondary batteries. Electrochim Acta 2016, 212:649-656.
- 46. Cheng X-B, Zhao C-Z, Yao Y-X, Liu H, Zhang Q: Recent advances in energy chemistry between solid-state electrolyte and safe lithium-metal anodes. Inside Chem 2019, 5:74-96.
- 47. Zheng F, Kotobuki M, Song S, Lai MO, Lu L: Review on solid electrolytes for all-solid-state lithium-ion batteries. *J Power* Sources 2018, 389:198-213.
- 48. Zhao Q, Stalin S, Zhao C-Z, Archer LA: Designing solid-state electrolytes for safe, energy-dense batteries. Nature Rev Mater 2020, 5:229-252.
- 49. Zhao S, Wu Q, Ma W, Yang L: Polyethylene oxide-based composites as solid-state polymer electrolytes for lithium metal batteries: a mini review. Front in Chem 2020:8.
- Reddy MV, Julien CM, Mauger A, Zaghib K: Sulfide and oxide inorganic solid electrolytes for all-solid-state Li batteries: a Review. Nanomaterials 2020, 10:1606.
- 51. Shoji M, Cheng EJ, Kimura T, Kanamura K: Recent progress for all solid state battery using sulfide and oxide solid electrolytes. J Phys Appl Phys 2019, 52:103001.
- Manthiram A, Yu X, Wang S: Lithium battery chemistries enabled by solid-state electrolytes. Nature Rev Mater 2017, 2:1-16.
- Zhu Y, He X, Mo Y: First principles study on electrochemical and chemical stability of solid electrolyte-electrode interfaces in all-solid-state Li-ion batteries. *J Mater Chem* 2016, 4:3253-3266
- 54. Koo M, Park K-I, Lee SH, Suh M, Jeon DY, Choi JW, Kang K, Lee KJ: Bendable inorganic thin-film battery for fully flexible electronic systems. *Nano Lett* 2012, **12**:4810–4816.

This is the most interesting paper demonstrating the possibility of LIPON as a solid-state electrolyte for thin-film batteries. Since the publishing of this paper, a number of researchers have researched solid-state electrolytes to make better and safer all-state-state batteries.

- Dudney NJ: Thin film micro-batteries. Electrochem Society Interface 2008, 17:44.
- Murugan R, Thangadurai V, Weppner W: Fast lithium ion conduction in garnet-type Li7La3Zr2O12. Angew Chem Int Ed 2007, 46:7778-7781.

This is the first paper showing the possibility of garnet-type electrolyte as an innovative solid-state electrolyte. The prepared garnet-type electrolyte (Li7La3Zr2O12) exhibits high lithium-ion conductivity and good thermal and chemical stability.

- Zhao N, Khokhar W, Bi Z, Shi C, Guo X, Fan L-Z, Nan C-W: Solid garnet batteries. Joule 2019, 3:1190-1199.
- Thangadurai V, Narayanan S, Pinzaru D: Garnet-type solidstate fast Li ion conductors for Li batteries: critical review. Chem Soc Rev 2014, 43:4714-4727.
- Fu KK, Gong Y, Liu B, Zhu Y, Xu S, Yao Y, Luo W, Wang C, Lacey SD, Dai J: Toward garnet electrolyte-based Li metal batteries: an ultrathin, highly effective, artificial solid-state electrolyte/metallic Li interface. Sci Adv 2017, 3:1601659.

- Sastre J, Futscher MH, Pompizi L, Aribia A, Priebe A, Overbeck J, Stiefel M, Tiwari AN, Romanyuk YE: Blocking lithium dendrite growth in solid-state batteries with an ultrathin amorphous Li-La-Zr-O solid electrolyte. Commun Mater 2021, 2:76.
- Hatzell KB, Chen XC, Cobb CL, Dasgupta NP, Dixit MB, Marbella LE, McDowell MT, Mukherjee PP, Verma A, Viswanathan V, et al.: Challenges in lithium metal anodes for solid-state batteries. ACS Energy Letters 2020, 5:922–934.
- Dai J, Yang C, Wang C, Pastel G, Hu L: Interface engineering for garnet-based solid-state lithium-metal batteries: materials, structures, and characterization. Adv Mater 2018, 30:1802068.
- Lee J, Lee T, Char K, Kim KJ, Choi JW: Issues and advances in scaling up sulfide-based all-solid-state batteries. Acc Chem Res 2021.
- Kato Y, Hori S, Saito T, Suzuki K, Hirayama M, Mitsui A, Yonemura M, Iba H, Kanno R: High-power all-solid-state batteries using sulfide superionic conductors. Nature Energy 2016, 1:1–7.
- Lau J, DeBlock RH, Butts DM, Ashby DS, Choi CS, Dunn BS: Sulfide solid electrolytes for lithium battery applications. Adv Energy Mater 2018, 8:1800933.
- Wenzel S, Sedlmaier SJ, Dietrich C, Zeier WG, Janek J: Interfacial reactivity and interphase growth of argyrodite solid electrolytes at lithium metal electrodes. Solid State Ionics 2018. 318:102-112.
- Zhou L, Park K-H, Sun X, Lalère F, Adermann T, Hartmann P, Nazar LF: Solvent-engineered design of argyrodite Li6PS5X (X = Cl, Br, l) solid electrolytes with high ionic conductivity. ACS Energy Letters 2019, 4:265–270.

- Lee Y-G, Fujiki S, Jung C, Suzuki N, Yashiro N, Omoda R, Ko D-S, Shiratsuchi T, Sugimoto T, Ryu S, et al.: High-energy long-cycling all-solid-state lithium metal batteries enabled by silver-carbon composite anodes. Nature Energy 2020, 5: 299–308.
- Bai X, Duan Y, Zhuang W, Yang R, Wang J: Research progress in Li-argyrodite-based solid-state electrolytes. J Mater Chem 2020, 8:25663–25686.
- Boulineau S, Courty M, Tarascon J-M, Viallet V: Mechanochemical synthesis of Li-argyrodite Li6PS5X (X=Cl, Br, I) as sulfur-based solid electrolytes for all solid state batteries application. Solid State Ionics 2012, 221:1-5.
- Garcia-Mendez R, Mizuno F, Zhang R, Arthur TS, Sakamoto J: Effect of processing conditions of 75Li2S-25P2S5 solid electrolyte on its DC electrochemical behavior. Electrochim Acta 2017, 237:144–151.
- Han F, Yue J, Zhu X, Wang C: Suppressing Li dendrite formation in Li2S-P2S5 solid electrolyte by Lil incorporation. Adv Energy Mater 2018, 8:1703644.
- Wu J, Liu S, Han F, Yao X, Wang C: Lithium/sulfide all-solidstate batteries using sulfide electrolytes. Adv Mater 2021, 33: 2000751.
- Zhu J, Li W, Wierzbicki T, Xia Y, Harding J: Deformation and failure of lithium-ion batteries treated as a discrete layered structure. Int J Plast 2019, 121:293–311.
- Ito S, Fujiki S, Yamada T, Aihara Y, Park Y, Kim TY, Baek S-W, Lee J-M, Doo S, Machida N: A rocking chair type all-solid-state lithium ion battery adopting Li2O-ZrO2 coated LiNio.8-Coo.15Al0.05O2 and a sulfide based electrolyte. J Power Sources 2014, 248:943-950.