

For HC use 10 mm graphite die (R7710) and 5 g of powder

For HD use 20 mm graphite die (R7710)

Recycled content	0%	25%	50%	75%	100%
HC	8 min to 650°C (ca. 75°C /min) 1 min to 725°C (ca. 75°C /min) 1 min @ 725°C press to 45MPa (3.9kN)	8 min to 650°C (ca. 75°C /min) 1 min to 740°C (ca. 75°C /min) 1 min @ 740°C press to 45MPa (3.9kN)	8 min to 650°C (ca. 75°C /min) 1.5 min to 760°C (ca. 75°C /min) 1 min @ 760°C press to 45MPa (3.9kN)	8 min to 650°C (ca. 75°C /min) 1.5 min to 780°C (ca. 75°C /min) 1 min @ 780°C press to 45MPa (3.9kN)	8 min to 650°C (ca. 75°C /min) 2 min to 800°C (ca. 75°C /min) 1 min @ 800°C press to 45MPa (3.9kN)
HD	8 min to 600°C (ca. 75°C /min) 2 min to 750°C and press to 50MPa (ca. 75°C /min) 2 min @ 750°C press to 70MPa	8 min to 600°C (ca. 75°C /min) 2.5 min to 765°C and press to 50MPa (ca. 75°C /min) 2 min @ 765°C press to 70MPa	8 min to 600°C (ca. 75°C /min) 3 min to 785°C and press to 50MPa (ca. 75°C /min) 2 min @ 785°C press to 70MPa	8 min to 600°C (ca. 75°C /min) 3.5 min to 805°C and press to 50MPa (ca. 75°C /min) 2 min @ 805°C press to 70MPa	8 min to 600°C (ca. 75°C /min) 2 min to 750°C (ca. 75°C /min) 2 min to 800°C press to 50MPa 2 min @ 825°C press to 70MPa