



RHODES
ARCHITECTURAL
STONE
NATURAL STONE EXPERTS

MANDALAY LIMESTONE

Mandalay is a proprietary organic finish for the RAS New Yangtze Limestone. Applied over any of the NYL textures, it may be used to soften the visual pallet. The result is visually clean, with same subtle stone to stone variation that nature provides.

The finish is lasting and permanent. It will not fade or alter under the toughest natural conditions. This exciting development extends the New Yangtze Limestone's excellent technical properties into new projects that require a lighter tonality.



RECOMMENDED USES

PAVERS	COPINGS/ CAPS
VENEER	CURBS
QUOINS	SILLS/ LINTELS



55 BELL STREET, SUITE 100
SEATTLE, WA 98121, USA
TEL 206.709.3000 FAX 206.709.3004
www.rhodes.org

58-74 STATION STREET
NUNAWADING VIC 3131, AUSTRALIA
TEL +61 3 8199-9555 FAX +61 3 9894-1804

57 HU BIN BEI LU, XIAMEN
FUJIAN, CHINA
TEL +86 592-533-0273
FAX +86 592-537-6000 EXT. 93181



MANDALAY LIMESTONE



COLOR - TEXTURE
EXAMPLE



COLOR - TEXTURE
EXAMPLE



COLOR - TEXTURE
EXAMPLE



COLOR - TEXTURE
EXAMPLE



COLOR - TEXTURE
EXAMPLE



COLOR - TEXTURE
EXAMPLE

MATERIAL SPECIFICATIONS

- COUNTRY OF ORIGIN : China
- COLOR RANGE : driftwood-donkey
- STANDARD BLOCK SIZE : 1500 x 600 x 450 mm
- MAX SPECIAL BLOCK SIZE : 2500 x 500 x 330 mm
- STANDARD VENEER SIZES : 75 x 75 mm min to 400 x 65 mm max; 50 -75 mm thick
- STANDARD PAVING SIZES : 300 x 300 mm min to 600 x 750 mm max; 30 - 75 mm thick
- 100 x 100 mm; 60 - 100 mm thick cobblestones
- 200 x 100 mm; 60 - 100 mm thick cobblestones



TECHNICAL DATA

ASTM C666	freeze thaw %	0.35
ASTM C97	absorption %	1.43
ASTM C97	bulk gravity lbs/ft3	159.9
ASTM C99	mod. of rupture psi	2,600
ASTM C170	compressive strength psi	8,800
ASTM C880	flexural strength psi	1,000
ASTM C241	abrasion resistance	8.1 Ha



Imperial



Metric