



RHODES
ARCHITECTURAL
STONE
NATURAL STONE EXPERTS



GOLDEN DUNE GRANITE


Golden Dune Granite has long been prized for its durability and its warm tonality. Quarried in the coastal provinces of China, this large-grained stone has been the choice of Chinese builders for centuries. This granite's warm color varies with the depth of the quarry, ranging from a dark golden color to a near off-white, showing specks of cardinal, bright ochre, and black. Delightful color variations occur within individual pieces, especially those cut in extra-large formats. Our fine hand-finishes complement and enhance the

natural texture of the exposed minerals in this timeless and versatile material. Typically, tool marks lighten the stone, creating a cool ivory color that offers a striking contrast to the warmer, toasted, unmarked surface. Golden Granite's most popular finishes are split-face, point stalk, and bush hammer. It is ideal for both large and small scale applications including paving, veneer, one-piece sinks and tubs, tabletops, and decorative pieces. Golden Granite pavers are often installed sand-set.



RECOMMENDED USES

PAVERS	DRAIN GRATES
VENEER	CARVED OBJECTS
STAIR BLOCKS	COLUMNS
QUOINS	SINKS / TUBS
COPING / CAPS	SLABS
CURBS	COBBLESTONES
SILLS / LINTELS	




55 BELL STREET, SUITE 100
SEATTLE, WA 98121, USA
TEL 206.709.3000 FAX 206.709.3004
www.rhodes.org

58-74 STATION STREET
NUNAWADING VIC 3131, AUSTRALIA
TEL +61 3 8199-9555 FAX +61 3 9894-1804

57 HU BIN BEI LU, XIAMEN
FUJIAN, CHINA
TEL +86 592-533-0273
FAX +86 592-537-6000 EXT. 93181



GOLDEN DUNE GRANITE



HONED
0.75" min thickness



FINE ADZE
1" min thickness



COARSE ADZE
2" min thickness



MECHANICAL BUSH HAMMER
1" min thickness



SPLIT
3" min thickness



PINEAPPLE
3" min thickness



MATERIAL SPECIFICATIONS

COUNTRY OF ORIGIN : China

COLOR RANGE : golden color

MAX BLOCK SIZE : 78" x 52" x 30"

STANDARD VENEER SIZES :
3" x 3" min to 16" x 26" max; 3" thick

STANDARD PAVING SIZES :
12" x 12" to 24" x 30"; 0.75" to 3" thick
4" x 4" x 2.5" or 4"; 8" x 4" x 2.5" or 4" cobblestones



TECHNICAL DATA

ASTM C97	absorption %	0.45
ASTM C97	bulk gravity lbs/ft ³	161
ASTM C97	bulk gravity kg/m ³	2,596
ASTM C99	mod. of rupture psi	1,218
ASTM C170	compressive strength psi	20,880
ASTM C880	flexural strength psi	1,610

