We Will Create a Nice Future Together

TAI COUNTY

TQCSI ISO 9001:2015
Quality Certified
TA2474-QC

RX-4066

Block Copolymerized Trifunctional Co-polyhydroxyalkyl Silicone Oil for Staple Fibers

2026/10/08 Draft. **PDS**

Description

RX-4066 is a segmented terpolymer hydrophilic silicone softener specially designed for staple fibers. It imparts a fluffy, smooth, down-like hand feel with elastic resilience, excellent moisture absorption, and rapid drying, particularly on cotton and cotton-blended fabrics.
It is suitable for softening processes in both padding and exhaust dyeing applications.

Characteristics

- Provides excellent moisture management, wicking, and ultra-fast drying properties.
- Specially designed for staple fibers. For synthetic fiber blends, it can be used in combination with our RX-4088.
- 1% temperature resistant up to 95˚C, returning to a light blue transparent liquid after
- Permissible pH range: 3.5~11.5
- Compatible with cationic and anionic softeners
- Suitable for secondary processing such as re-adhesion
- Antistatic effects

Properties

Appearance	Transparent to hazy yellowish liquid
Active ingredient(%)	90.0%
pH(1%Solution,25℃)	7.5±1.0
Ionic type	Nonionic
Diluent	Water

- **Can be mixed with most anionic components**

Safety

This document does not contain the safety information required for the product. Please read the safety data sheet for this product before use.

Storage & packaging

When stored in its originally sealed packaging at 5°C - 40°C, this product may be stored for up to 8 months from its manufacturing date. Comply with the storage instructions marked on the packaging. Once past this expiration date, TAI COUNTY CHEMICAL no longer guarantees that the product meets the sales specifications.

Product comes in 120kg HDPE blue drums loading 100KG(All breathable).

Applications

- RX-4066 is recommended to be diluted with water at a 20% ratio using the following procedure (using a paddle mixer):

RX-4066	:100 KG
Water(1)	:20 KG
Water(2)	:70 KG
Water(3)	:35 KG
Water(4)	:225 KG
Total	:450 KG

Processing

1. Add 100KG of RX-4066 product and slowly introduce 20KG of water (1), stirring until the liquid becomes gradually thickened (first turning point).
2. After the first turning point, add 70KG of water (2) and continue stirring until the consistency transitions from thickened to reduced viscosity resembling water (second turning point).
3. Following the second turning point, add 35KG of water (3) and continue stirring until thoroughly and uniformly mixed. This is the dilution method for a 40% emulsion.
4. **Diluted to 40%, the appearance is transparent to slightly turbid emulsion.**
5. **Adding an additional 225 kg of water (4) will dilute it to a 20% emulsion with a slightly blue-tinted translucent appearance.**
6. Filter the mixture before packaging, recommended usage is 2-5%.

(Depending on the actual conditions, you can adjust the usage amount.)

The information contained in this manual is given based on our current knowledge and good faith. It is indicative only and not binding, especially regarding the impact on third-party rights during product use. TAI COUNTY CHEMICAL ensures the products it sells conform to specifications. Only necessary preliminary tests can determine if a product is suitable for specific applications, and this information cannot replace such tests. Users are responsible for ensuring compliance with local legislation and obtaining necessary usage certificates and authorizations. Users are requested to check if they have the latest version of this document, and TAI COUNTY CHEMICAL is always ready to provide additional information to customers.

TAI COUNTY CHEMICAL

TAIPEI Factory: NO. 91, Museum Rd., Bali Township, Taipei County 24947, Taiwan
FACTORY REGISTRATION NO: 99.695614.00
YUNLIN Factory: NO. 1, Changqing St., Lunbei Township, Yunlin County 63745, Taiwan
FACTORY REGISTRATION NO: 09000892
Tel: 886-2-2610-4457
Fax: 886-2-2610-1363
E-MAIL：service@taicounty.com.tw
www.taicounty.com.tw