

Fermi arcs for generic nodal points hosting monopoles or dipoles

Ipsita Mandal*

*Department of Physics, Shiv Nadar Institution of Eminence (SNIOE),
Gautam Buddha Nagar, Uttar Pradesh 201314, India*

Surface-localised states in the form of Fermi arcs emerge at the interfaces between three-dimensional topological semimetals and their surrounding vacuum, serving as primary signatures of momentum-space topology accessible to modern spectroscopic methods. These arcs encode information about topological singularities — nodal points where multiple bands converge — through their geometric properties. Specifically, the arcs terminate tangentially at the edges of Fermi-surface projections, delineating where surface modes transition into bulk extended states. The arcs' multiplicity at each node corresponds directly to the underlying topological charge (Berry-curvature monopole magnitude), thereby offering a window into momentum-space invariants via angle-resolved photoemission experiments. This work establishes a systematic framework for computing surface state configurations applicable to arbitrary nodal degeneracies and band dispersions: (1) nodes with twofold through multifold band multiplicities; and (2) bands exhibiting diverse momentum-dependence patterns, including linear, nonlinear, isotropic, and anisotropic regimes. We additionally examine topologically distinct nodal types where monopole charges vanish but dipolar Berry-curvature distributions appear, clarifying the surface-state landscape in such unconventional scenarios.

CONTENTS

I. Introduction	1
II. Formulation of boundary conditions	2
A. Witten's formulation for an untilted Weyl node	3
B. Generic formulation applicable for any kind of nodes	3
III. Specific examples	4
A. Untilted nodes of a Weyl semimetal	5
B. Tilted nodes of a Weyl semimetal	6
C. Triple-point semimetal	6
D. Rarita-Schwinger-Weyl node in a chiral crystal	7
E. Double-Weyl semimetal	8
F. Triple-Weyl semimetal	9
G. Berry-dipole in a two-band model	10
H. Berry-dipole in a three-band model	10
I. Quadruple-Weyl node with monopole-charge 4	12
IV. Summary, discussions, and outlook	13
Acknowledgments	14
Appendix: Derivation of the boundary conditions	14
References	16

I. INTRODUCTION

Three-dimensional (3d) semimetals containing degeneracies in the Brillouin zone (BZ) — points where $(2\zeta + 1)$ bands converge [cf. Fig. 1(a)] — offer a testbed for observing topological concepts embedded in condensed matter systems [1–10]. Near a nodal point, the effective low-energy band structure follows the form $\mathbf{d}(\mathbf{k}) \cdot \mathbf{S}$, with $\mathbf{d}(\mathbf{k}) = \{d_x(\mathbf{k}), d_y(\mathbf{k}), d_z(\mathbf{k})\}$. Here, $\mathbf{k} = \{k_x, k_y, k_z\}$ denotes momentum coordinates in the 3d BZ, and $\mathbf{S}$ is the vector operator with components $\{S_x, S_y, S_z\}$ acting as angular-momentum operators. The band eigenvalues, spanning from $-\zeta$ to ζ , serve as pseudospin quantum numbers, distinguishing them from intrinsic electron spin. An isotropic Weyl node in Weyl semimetals (WSMs) [1,

* ipsita.mandal@snu.edu.in




FIG. 1. (a) Dispersion (E) in isotropic twofold (viz. Weyl node) and fourfold (viz. Rarita-Schwinger-Weyl node) band-crossings against the $k_x k_y$ -plane. (b) Schematics of BC-flux lines in the $k_x = 0$ planes for a monopole and an ideal dipole. Here, the dipole-axis is oriented along the k_z -axis and, hence, the BC goes to zero on the $k_z = 0$ plane in the 3d BZ.

3, 5] exemplifies the simplest case with $\varsigma = 1/2$. Higher pseudospin analogs have been discovered and characterized: triple-point semimetals (with $\varsigma = 1$) and Rarita-Schwinger-Weyl (RSW) nodes ($\varsigma = 3/2$) [7, 9, 11–18]. The topological character emerges from Berry-phase effects: closed-loop accumulation of geometric phases generates vector fields in momentum space, including Berry curvature (BC) and orbital magnetic moment (OMM). Nodes function as topological defects — sources and sinks — of the BC field [cf. Fig. 1(b)]. The BC singularity's strength is quantified by the Chern number ($\mathcal{C}$) of any closed oriented two-dimensional (2d) surface enclosing the node. Theoretical advances now extend beyond simple monopole configurations, revealing that nodes can exhibit higher-order multipolar character [19–22] (such as dipoles and quadrupoles), echoing multipole hierarchies from classical electrostatics.

Momentum-space topology manifests in numerous experimentally measurable properties accessible through contemporary techniques. Transport measurements reveal a spectrum of topological responses with well-established theoretical underpinnings [6, 10, 16, 17, 23–28]. These encompass anomalous Hall conductivity [29–31], planar Hall phenomena [10, 16, 17, 23–27, 32–45], Magnus forces [46–48], optical dichroism [49, 50], and photocurrent generation [51–54]. Yet among these signatures, Fermi arcs represent the most direct topological observable [55–62], being clearly visualized via angle-resolved photoemission spectroscopy (ARPES). Fermi arcs are surface-localised states in a 2d surface Brillouin zone (SBZ), geometrically constrained to terminate at the boundaries of bulk Fermi-surface (FS) projections, where they merge into extended bulk states.

Surface-localised Fermi arcs appear when considering semi-infinite slabs of topological semimetals with a surface normal $\hat{n}$. These states emerge from the presence of topologically-protected edge modes in 2d momentum slices, which exist when open boundary conditions are imposed [1, 2, 4]. While the momentum component parallel to the surface normal becomes ill-defined, the in-plane components $\mathbf{k}_{\parallel}$ perpendicular to $\hat{n}$ retain their character as good quantum numbers in the large-slab limit. Consequently, a single interface defines an SBZ spanned by $\mathbf{k}_{\parallel}$ components, within which Fermi arcs reside. For Weyl semimetals, analytical surface-state solutions are well-established [63–66]. However, in more complex systems with multifold degeneracies or nonlinear dispersions, derivations remain largely case-by-case [63, 67–71], lacking systematic applicability across diverse dispersion landscapes and band configurations. This work develops a uniform computational scheme for deriving Fermi-arc configurations across arbitrary nodal geometries, establishing how these surface states encode the Chern numbers of underlying 2d momentum slices through bulk-boundary correspondence [1, 2, 4].

The paper is organised as follows: In Sec. II, we lay out our formulation of the boundary conditions, which leads to the solution for the surface states for a generic nodal-point semimetal. Sec. III is devoted to the application of our method to diverse systems, spanning twofold to multifold ones, linear-in-momentum to quadratic- and cubic-in-momentum ones, and isotropic to anisotropic ones. Furthermore, we also consider two cases where the nodal points represent ideal BC-dipoles rather than monopoles. Finally, we end with a summary and outlook in Sec. IV.

II. FORMULATION OF BOUNDARY CONDITIONS

Let us take a single surface at $x = 0$ such that the $x < 0$ region represents a semi-infinite semimetal, with the bulk Hamiltonian $H(\mathbf{k})$, where $\mathbf{k} \equiv \{k_x, k_y, k_z\}$ and $k = \sqrt{k_x^2 + k_y^2 + k_z^2}$. The translation symmetry is broken along the x -axis, and we use the Hamiltonian,

$$H_x = H(k_x \rightarrow -i\partial_x, k_y, k_z). \quad (1)$$

Demanding that H_x be Hermitian in the region $x \in [0, \infty)$, we have the physical condition that

$$\int_0^\infty dx \psi^\dagger(x) H_x \phi(x) = \int_0^\infty dx [H_x \psi(x)]^\dagger \phi(x), \quad (2)$$

while considering two bonafide boundary-states, ψ and ϕ . The current-density operator is defined as

$$j_x \equiv \partial_{k_x} H(\mathbf{k})|_{k_x \rightarrow -i \partial_x}. \quad (3)$$

Consequently, Eq. (2) also translates into a physically-sensible boundary condition (bc) which prohibits the current transmission through the boundary via $(\psi^\dagger j_x \psi)|_{x=0} = 0$, alternatively known as the hard-wall bc. The boundary modes must behave as decaying wavefunctions of the form of

$$\psi(x) = \psi_0 e^{-\kappa x} \text{ with } \text{Re}(\kappa) > 0, \quad (4)$$

such that the surface states are bound to the boundary at $x = 0$. Here, ψ_0 is independent of x and any x -dependence of $\psi(x)$ is assumed to be contained in the $e^{-\kappa x}$ factor.

To avoid any confusion, we emphasise that $\psi(x)$ and $\phi(x)$ appearing in Eq. (2) denote two independent and arbitrary decaying functions on $[0, \infty)$. They are introduced solely as test functions in the conventional sense of self-adjoint-extension theory, as previously employed for WSM boundaries in Ref. [65]. Demanding the Hermiticity identity of Eq. (2) for arbitrary independent $\{\psi, \phi\}$ is what fixes the admissible, energy-independent boundary condition [see also Eq. (7) below]. This defines a genuinely self-adjoint domain for H_x on the half-space ($x < 0$), analogous to fixing self-adjoint extensions of a differential operator via von Neumann's deficiency-index construction. Once this domain is fixed, any candidate surface-bound eigenstate must satisfy the same relation with ψ set equal to itself, in order to belong to it. The resulting single-field current condition, $\psi_0^\dagger j_x \psi_0|_{x=0} = 0$, used throughout this paper, is thus not a distinct or weaker requirement. It is precisely this general boundary condition evaluated on the specific physical solution at hand – the standard hard-wall statement that the constructed surface state carries no probability current through the boundary.

A. Witten's formulation for an untitled Weyl node

The effective Hamiltonian in the vicinity of a single Weyl node [cf. Fig. 1(a)] is captured by

$$H_W(\mathbf{k}) = \boldsymbol{\sigma} \cdot \mathbf{k}. \quad (5)$$

For this Hamiltonian, Eq. (2) translates into

$$\psi^\dagger(x) \sigma_x \phi(x)|_{x=0} = 0 \Rightarrow j_x|_{x=0} \equiv \psi_0^\dagger \sigma_x \phi_0 = 0. \quad (6)$$

An energy-independent boundary condition can be formulated as a local linear restriction on the components of the spinor wave function at the boundary, captured by [63]

$$\Psi_0 = M \Psi_0, \text{ where } M = \cos \alpha \sigma_y + \sin \alpha \sigma_z. \quad (7)$$

This is a good boundary condition because σ_x anticommutes with M , leading to

$$\psi_0^\dagger \sigma_x \phi_0 = \frac{1}{2} \left[\psi_0^\dagger \sigma_x M \phi_0 + (M \psi_0)^\dagger \sigma_x \phi_0 \right] = 0. \quad (8)$$

The variable α acts as a parameter and, by changing α , we get Fermi arcs of various shapes and orientations with the restriction that they originate tangentially from the boundary of the projection of the FS on the $k_y k_z$ -plane.

B. Generic formulation applicable for any kind of nodes

For generic nodes with multifold nodes and/or nonlinear powers of the components of $\mathbf{k}$, Witten's trick will not work, which we will explicitly see why considering some specific examples. Hence, we need an unambiguous generic method applicable to derive the equations describing the curves representing the relevant Fermi arcs, which we describe here. Suppose we have an N -fold degeneracy at a node, described by the $N \times N$ Hamiltonian, $H_N(\mathbf{k})$ in the bulk BZ. Let us look for surface states where the surface-normal is along the direction denoted by the unit vector, $\hat{\mathbf{n}}$, and located at $r_\perp = 0$, where $r_\perp \equiv \mathbf{r} \cdot \hat{\mathbf{n}}$. We set our convention that the region $r_\perp < 0$ represents the region occupied by the semimetallic material, while $r_\perp > 0$ represents the adjoining non-topological region (e.g., vacuum). Dividing up the momentum components along and perpendicular to $\hat{\mathbf{n}}$ as $k_\perp$ and $\mathbf{k}_\parallel$, the boundary Hamiltonian is obtained as

$$H_{r_\perp} = H_N(k_\perp \rightarrow -i \partial_{r_\perp}, \mathbf{k}_\parallel). \quad (9)$$

The imposition of the Hermiticity condition on $H_{r_\perp}$ leads to

$$\int_0^\infty dr_\perp \psi^\dagger(r_\perp) H_{r_\perp} \phi(r_\perp) = \int_0^\infty dr_\perp [H_{r_\perp} \psi(r_\perp)]^\dagger \phi(r_\perp), \quad (10)$$

analogous to Eq. (2). Let us parametrise a solution as

$$\psi(r_\perp) = \psi_0 e^{-\kappa r_\perp} \text{ with } \text{Re}(\kappa) > 0 \text{ and } \psi_0^T = [1 \ a_1 + i b_1 \ a_2 + i b_2 \ \cdots \ a_{N-1} + i b_{N-1}]. \quad (11)$$

As argued earlier, (after some manipulations involving integration by parts to convert the integrands into total derivatives) Eq. (10) will turn out to be equivalent to the condition of

$$\psi^\dagger(r_\perp) j_{r_\perp} \psi(r_\perp)|_{r_\perp=0} = 0, \text{ where } j_{r_\perp} \equiv \partial_{k_\perp} H_N(k_\perp, \mathbf{k}_\parallel)|_{k_\perp \rightarrow -i \partial_{r_\perp}} \quad (12)$$

represents the current-density operator perpendicular to the surface. Next, we need to solve for the eigenvalue equation,

$$H_{r_\perp} \psi(r_\perp) = E \psi(r_\perp), \quad (13)$$

which leads to N complex-valued equations involving the $(2N + 1)$ unknown variables E , $\kappa_r \equiv \text{Re}(\kappa)$, $\kappa_i \equiv \text{Im}(\kappa)$, a_1 , b_1 , a_2 , b_2 , $\cdots$, a_{N-1} , and b_{N-1} . This implies that we have $(2N + 1)$ real equations [on including the real equation coming from Eq. (12)] at our disposal, which we can use to solve for the same number of unknown variables. More details about intermediate steps can be found in the Appendix. There, we demonstrate explicitly that the general boundary term can be obtained by applying a Lagrange/Wronskian identity for higher-order derivative operators [cf. Eq. (45)] to each monomial order present in $H_N(k_\perp, \mathbf{k}_\parallel)$ in turn, and summing. The bulk contributions cancel identically, leaving the pure boundary functional $\Xi[\psi, \phi]$ [defined in Eq. (46)] evaluated at $r_\perp = 0$, with the $r_\perp \rightarrow \infty$ contribution vanishing by the exponential decay of ψ, ϕ . Specialising to the actual candidate surface state, $\phi = \psi = \psi_0 e^{-\kappa r_\perp}$, and using that this same state solves the eigenvalue problem, $H_N(\lambda) \psi_0 = E \psi_0$ with $\lambda \equiv i \kappa$ [cf. Eq. (13)], the boundary functional collapses – exactly, and order by order in the momentum expansion of H_N , with no assumption that κ is real – onto $\Xi[\psi_0, \psi_0]|_{r_\perp=0} = \text{Im}(E) |\psi_0|^2 / \kappa_r$. Eq. (10) is therefore equivalent, for the exponentially decaying eigenstate ansatz of Eq. (11) satisfying Eq. (13) and, for arbitrary finite polynomial order in $k_\perp$, to the single real requirement that the surface-state energy be real [viz. $\text{Im}(E) = 0$]. This is precisely the self-adjointness statement that a genuine surface-bound state must have a real eigenvalue. This reduces to the familiar single-field current condition of Eq. (12), $\psi_0^\dagger j_{r_\perp} \psi_0|_{r_\perp=0} = 0$, whenever H_N is at most linear in $k_\perp$, as for the WSMs. In the next section, we will study a variety of systems to see that the above procedure works generically.

III. SPECIFIC EXAMPLES

In this section, we will take some specific systems spanning generic features like nonlinear dispersion and multifold band-crossings. In the process, we will also observe how the emergent Fermi arcs reflect the underlying Chern numbers (or, equivalently, monopole charges) of the associated nodes. Additionally, we resolve the issue whether Fermi arcs can appear in nodes harbouring ideal BC-dipoles.

Before dealing with the individual systems, some comments are in order. For a non-interacting Hamiltonian in the vicinity of a nodal point, the relevant Matsubara Green's function is $G(i\omega, \mathbf{k}) = [i\omega - H_N(\mathbf{k})]^{-1}$, and the invariant protecting the point node against gap opening under continuous deformations is Volovik's N_3 [72], defined as the degree of the map from a three-sphere S^3 surrounding the singularity in $(\omega, \mathbf{k})$ -space into the space of Green's functions,

$$N_3 = \frac{1}{24\pi^2} \epsilon^{\mu\nu\rho\sigma} \text{tr} \oint_{S^3} dS^\mu G \partial_\nu G^{-1} G \partial_\rho G^{-1} G \partial_\sigma G^{-1}. \quad (14)$$

The integration is performed over S^3 . For the effective low-energy Hamiltonians considered throughout the manuscript, N_3 reduces identically to the integral of the BC-flux over any Gaussian surface (e.g., S^2) enclosing the node, where the BC of the s -th band is

$$\mathbf{\Omega}_s(\mathbf{k}) = i [\nabla_{\mathbf{k}} \psi_s(\mathbf{k})]^\dagger \times [\nabla_{\mathbf{k}} \psi_s(\mathbf{k})]. \quad (15)$$

Here, $\{\psi_s(\mathbf{k})\}$ is the set of normalised eigenvectors of the parent Hamiltonian. We can now use this to compute N_3 directly as the flux of $\mathbf{\Omega}_s(\mathbf{k})$ through any closed surface enclosing the node. Equivalently, this is the BC-monopole charge or Chern number that we invoke to count the number of Fermi arcs, and has already been computed over and over in the literature (e.g., Refs. [16–18, 26, 27, 41–43, 49, 73]). The reduction from the frequency-momentum S^3 -integral to the equal-time S^2 -integral is standard for gapless free-fermion Green's functions and can be computed using Eq. (15). Having made this identification explicit, we now tabulate N_3 for every variety of node discussed in this paper:




FIG. 2. A pair of conjugate Weyl nodes: The Fermi arcs represent modes with $E = \mu$, where $\mu = 0.5$ and $k_w = 1$. Each arc corresponds to a distinct value of b_1 , colour-coded as shown in the plot-legends. The dashed red curves represent the projections of the bulk FSs on the $k_y k_z$ -plane.

Type of node	Band-multiplicity (N)	$ N_3 = \mathcal{C} $
Untilted Weyl node	2	1
Tilted Weyl node	2	1
Triple-point node	3	2
RSW node	4	4
Double-Weyl node	2	2
Triple-Weyl node	2	3
Berry-dipole (two-band)	2	0
Berry-dipole (three-band)	3	0
Quadruple-Weyl node	2	4

The two BC-dipole cases carry vanishing net monopole charge, $N_3 = 0$, since an ideal BC-dipole has equal and opposite monopole charge on its two poles. Nonetheless, as we discuss below, they still support Fermi arcs, since our boundary-condition construction is sensitive to more than the net charge alone.

A. Untilted nodes of a Weyl semimetal

Let us consider the one-node model given by Eq. (5), where we want to consider a boundary at $x = 0$, indicating $\hat{n} = \hat{x}$. Using $\psi_0^T = [1 \ a_1 + i b_1]$, Eq. (6) yields $a_1 = 0$. Next, the two components of the matrix equation in Eq. (13) take the forms of

$$b_1(-i\kappa_i + k_y - \kappa_r) - E + k_z = 0 \text{ and } -b_1(E + k_z) + i\kappa_i + k_y + \kappa_r = 0 \\ \Rightarrow b_1(k_y - \kappa_r) - E + k_z = 0, \quad b_1\kappa_i = 0, \quad \kappa_i = 0, \text{ and } -b_1(E + k_z) + k_y + \kappa_r = 0, \quad (16)$$

after decomposing them into real and imaginary parts. We obtain the solutions as $E = \frac{2b_1 k_y + (1-b_1^2)k_z}{1+b_1^2}$, $\kappa_r = \frac{(b_1^2-1)k_y + 2b_1 k_z}{1+b_1^2}$, and $\kappa_i = 0$. We find that b_1 plays the role of a parameter, just like α in Eq. (7). The range of the Fermi arc is determined by the region where $\kappa_r > 0$, i.e., $(b_1^2 - 1)k_y + 2b_1 k_z > 0$. The arcs end tangentially on the projections of the bulk FSs, mixing with the bulk states, which is the point whose k_y - and k_z -coordinates are obtained as the solutions of the simultaneous equations, $E(k_y, k_z) = \mu$ and $\sqrt{k_y^2 + k_z^2} = \mu$. One can check that at this point, $\{k_y, k_z\} = \frac{\mu}{1+b_1^2} \{2b_1, 1-b_1^2\} \Rightarrow \kappa_r = 0$. Therefore, the surface state ceases to exist at this point, merging with the bulk states.

For the case of two nodes, separated along the k_z -direction (for example) by an amount $2k_w$, we can easily get the nature of the Fermi arcs by the replacement $k_z \rightarrow (k_z^2 - k_w^2)$. Fig. 2 illustrates the Fermi arcs for four distinct values of b_1 , when the chemical potential μ cuts the bandstructure of the surface bands.

B. Tilted nodes of a Weyl semimetal

The bulk Hamiltonian in the vicinity of a node, tilted with respect to the k_x -axis, is captured by

$$H_W(\mathbf{k}) = \boldsymbol{\sigma} \cdot \mathbf{k} + \eta k_x \mathbb{I}_{2 \times 2}. \quad (17)$$

For this case, on using $\psi_0^T = [1 \ a_1 + i b_1]$, Eq. (12) yields

$$\psi_0^\dagger \sigma_x \psi_0 + \eta \psi_0^\dagger \psi_0 = 0 \Rightarrow 2 a_1 + \eta (1 + a_1^2 + b_1^2) = 0. \quad (18)$$

Next, the two components of the matrix equation shown in Eq. (13) take the forms of

$$\begin{aligned} & i \kappa_r (a_1 + i b_1 + \eta) - a_1 \kappa_i - i a_1 k_y - i b_1 \kappa_i + b_1 k_y - E - \eta \kappa_i + k_z = 0 \\ & \text{and } i (\kappa_i + k_y + \kappa_r) - (a_1 + i b_1) [E + \eta (\kappa_i - i \kappa_r) + k_z] = 0 \\ \Rightarrow & - (a_1 + \eta) \kappa_i + b_1 (k_y - \kappa_r) - E + k_z = 0, \quad -a_1 k_y + (a_1 + \eta) \kappa_r - b_1 \kappa_i = 0, \\ & -a_1 (E + \eta \kappa_i + k_z) - b_1 \eta \kappa_r - \kappa_i = 0, \quad a_1 \eta \kappa_r - b_1 (E + \eta \kappa_i + k_z) + k_y + \kappa_r = 0. \end{aligned} \quad (19)$$

We obtain the solutions as $E = \frac{b_1 [\sqrt{1-(1+b_1^2)\eta^2+1}] k_y + [\sqrt{1-(1+b_1^2)\eta^2-b_1^2}] k_z}{1+b_1^2}$, $\kappa_r = \frac{(b_1^2-1)k_y+2b_1k_z}{1+b_1^2}$, $\kappa_i = 0$, and $a_1 = \frac{\sqrt{1-(1+b_1^2)\eta^2}-1}{\eta}$. While for the untilted case (i.e., $\eta = 0$), the projection is the locus of the curve $k = \mu$ at $k_x = 0$, for the tilted case (i.e., $\eta \neq 0$), it is the locus of the curve $k = \mu$ at $k_x = -\eta \sqrt{(k_y^2 + k_z^2)/(1-\eta^2)}$ (or, equivalently, $k \sqrt{1-\eta^2} = \mu$ at $k_x = 0$). This is because, for $\mu \neq 0$, the anisotropic FS (shaped like a spheroid elongated along the k_x -direction) has its largest radius of projection at a negative value of k_x . Consequently, the arcs end tangentially on the surface $\sqrt{(k_y^2 + k_z^2)} \sqrt{1-\eta^2} = \mu$. Solving for k_y and k_z using $E(k_y, k_z) = \mu$ in conjunction, we obtain the coordinates of the Fermi-arc's ending as $\{k_y, k_z\} = \frac{\mu}{(1+b_1^2)(1-\eta^2)} \left\{ b_1 \left[1 + \sqrt{1-(1+b_1^2)\eta^2} \right], \sqrt{1-(b_1^2+1)\eta^2} - b_1^2 \right\}$, where of course κ_r goes to zero. Again, for the case of two nodes, separated along the k_z -direction (for example) by an amount $2k_w$, we can easily get the nature of the Fermi arcs by the replacement $k_z \rightarrow (k_z^2 - k_w^2)$. Fig. 2 illustrates the Fermi arcs for the two-node case using four distinct values of b_1 , with η set to 0.35.

C. Triple-point semimetal

Let us now consider bands carrying pseudospin-1 quantum numbers crossing at threefold-degenerate nodes [7, 9, 41–43, 48, 74], representing the so-called triple-point semimetals (TSMs). These are three-band generalisations of the pseudospin-1/2 quasiparticles of WSMs, with the nodal points acting as BC-monopoles of magnitude 2. They can be realised in 3d tight-binding models for cold fermionic atoms in cubic optical lattices [75] and, via *ab initio* simulations, have been identified in materials like TaN, NbN, and WC-type ZrTe [74, 76–78]. The effective low-energy continuum Hamiltonian, in the vicinity of a threefold nodal point, is given by

$$\mathcal{H}_T(\mathbf{k}) = \mathbf{k} \cdot \boldsymbol{\mathcal{S}}. \quad (20)$$

Here, $\boldsymbol{\mathcal{S}}$ represents the vector spin-1 operator with three components,

$$\mathcal{S}_x = \frac{1}{\sqrt{2}} \begin{bmatrix} 0 & 1 & 0 \\ 1 & 0 & 1 \\ 0 & 1 & 0 \end{bmatrix}, \quad \mathcal{S}_y = \frac{1}{\sqrt{2}} \begin{bmatrix} 0 & -i & 0 \\ i & 0 & -i \\ 0 & i & 0 \end{bmatrix}, \quad \mathcal{S}_z = \begin{bmatrix} 1 & 0 & 0 \\ 0 & 0 & 0 \\ 0 & 0 & -1 \end{bmatrix}. \quad (21)$$

The Chern-number values of ± 2 indicate that we must have two distinct Fermi arcs associated with each node [58, 59].

Here we note that, although this is a straightforward generalisation of the isotropic Weyl node, we cannot apply Witten's method (outlined in Sec. II A) simply because of the fact that $\mathcal{S}_x$, $\mathcal{S}_y$, and $\mathcal{S}_z$ do not anticommute (unlike the Pauli matrices). Furthermore, the boundary-condition matching procedure of Ref. [79] relies on a heuristic model-specific reduction, namely, the boundary current happens to depend on only two of the three wave-function components for their particular choice of Hamiltonian. This renders their approach inadequate and non-generic for dealing with the present




FIG. 3. (a) A pair of triple-point nodes: The Fermi arcs represent modes with $E = \mu$, where $\mu = 0.5$ and $k_w = 1$. The dashed red curves represent the projections of the bulk FSs (of the non-flat bands) on the $k_y k_z$ -plane. The two Fermi arcs emanating tangentially from each FS-projection reflect the magnitude Chern number at each node equalling two. The cyan arc has been obtained by setting $b_1 = -1$. (b) RSW node: Four Fermi arcs emerging from the FS-projections of the two conduction bands, for $\mu = 0.5$ and $b_1 = 0$, indicating the Chern number to be four.

system. Hence, our generic method works seamlessly to explicitly derive the appearances of the Fermi arcs. We use the parametrisation $\psi_0^T = [1 \ a_1 + i b_1 \ a_2 + i b_2]$ and consider a boundary at $x = 0$. Plugging it in Eq. (12) yields

$$\psi_0^\dagger \mathcal{S}_x \psi_0 = 0 \Rightarrow a_1 + a_2 = 0. \quad (22)$$

Employing the matrix equation, viz. Eq. (13), we get

$$\begin{aligned} i \kappa_r - \sqrt{2} (a_1 + i b_1) (E - k_z) &= \kappa_i + i k_y, \quad -[a_1 + (1 + i) a_2 + i b_1] (\kappa_i - i \kappa_r) + [i a_1 + (1 - i) a_2 - b_1] k_y = \sqrt{2} E, \\ \text{and } \sqrt{2} (1 + i) a_2 (E + k_z) &= i (\kappa_i + k_y + \kappa_r) \\ \Rightarrow \kappa_i &= \sqrt{2} a_1 (k_z - E), \quad \sqrt{2} b_1 (k_z - E) + (\kappa_r - k_y) = 0, \quad (a_1 + a_2) \kappa_i + a_2 [\kappa_r - k_y + b_1 (k_y + \kappa_r)] = -\sqrt{2} E, \\ (a_2 + b_1) \kappa_i &= a_2 (\kappa_r - k_y) + a_1 (k_y + \kappa_r), \quad \kappa_i = -\sqrt{2} a_2 (E + k_z), \quad \kappa_r = \sqrt{2} a_2 (E + k_z) + k_y. \end{aligned} \quad (23)$$

The solutions indeed tell us that there are two Fermi arcs characterised by (1) $E = \frac{2\sqrt{2} b_1 k_y + 4 k_z}{2 + b_1^2} - k_z$, $\kappa_r = \frac{(b_1^2 - 2) k_y + 2\sqrt{2} b_1 k_z}{2 + b_1^2}$, $\kappa_i = 0$, $a_1 = 0$, $a_2 = -b_1^2/2$, $|b_1| > 0$, and $b_2 = 0$; and (2) $E = k_z$, $\kappa_r = -k_y$, $\kappa_i = 0$, $a_1 = 0$, $a_2 = 0$, $b_1 = 0$, and $b_2 = 0$. For the first arc, b_1 plays the role of a parameter and, hence, its shape changes as we vary b_1 . The points on the SBZ where κ_r goes to zero are found to be $\{k_y, k_z\} = \frac{2\mu}{2 + b_1^2} \{b_1 \sqrt{2}, b_1^2 - 2\}$ (where $|b_1| > 0$) and $\{k_y, k_z\} = \{0, \mu\}$, respectively, for the two Fermi arcs.

For the case of two nodes separated along the k_z -direction (for example) by an amount k_w , which is possible when the nodes are not pinned at high-symmetry points for a given crystal structure, we can easily determine the nature of the Fermi arcs by the replacement $k_z \rightarrow (k_z^2 - k_w^2)$. Fig. 3(a) illustrates the Fermi arcs for $\mu = 0.5$, $k_w = 1$, and $b_1 = -1$. Since the nodes carry Chern numbers equalling ± 2 , we observe two arcs emanating from each FS-projection.

D. Rarita-Schwinger-Weyl node in a chiral crystal

Here we focus on bands carrying pseudospin-3/2 quantum numbers crossing at fourfold-degenerate degeneracy-points [cf. Fig. 1(a)], widely known as the Rarita-Schwinger-Weyl (RSW) nodes. They appear at the Γ -points of chiral crystals with appreciable spin-orbit coupling (SOC) [9, 16, 17, 41, 60, 61], hosting a net BC-monopole of magnitude 4. The effective Hamiltonian, in the vicinity of an isotropic RSW node, takes the form of

$$\mathcal{H}(\mathbf{k}) = \mathbf{k} \cdot \mathcal{J}. \quad (24)$$

Here, $\mathcal{J} = \{\mathcal{J}_x, \mathcal{J}_y, \mathcal{J}_z\}$ represents the vector operator whose three components comprise the angular-momentum operators in the spin-3/2 representation of the SU(2) group. We choose the commonly-used representation with

$$\mathcal{J}_x = \begin{pmatrix} 0 & \frac{\sqrt{3}}{2} & 0 & 0 \\ \frac{\sqrt{3}}{2} & 0 & 1 & 0 \\ 0 & 1 & 0 & \frac{\sqrt{3}}{2} \\ 0 & 0 & \frac{\sqrt{3}}{2} & 0 \end{pmatrix}, \quad \mathcal{J}_y = \begin{pmatrix} 0 & \frac{-i\sqrt{3}}{2} & 0 & 0 \\ \frac{i\sqrt{3}}{2} & 0 & -i & 0 \\ 0 & i & 0 & \frac{-i\sqrt{3}}{2} \\ 0 & 0 & \frac{i\sqrt{3}}{2} & 0 \end{pmatrix}, \quad \mathcal{J}_z = \begin{pmatrix} \frac{3}{2} & 0 & 0 & 0 \\ 0 & \frac{1}{2} & 0 & 0 \\ 0 & 0 & -\frac{1}{2} & 0 \\ 0 & 0 & 0 & -\frac{3}{2} \end{pmatrix}. \quad (25)$$

Since the RSW node carries Chern number equalling 4, we must observe four arcs emanating from the FS-projections of the two bands being cut by μ . For this case, just for the ease of calculations, we consider a boundary at $z = 0$ (because the $\mathcal{J}_z$ matrix has fewer nonzero entries, leading to less cumbersome equations to be solved). Here again we note that, although this is a fourfold generalisation of the isotropic Weyl node, we cannot apply Witten's method since $\mathcal{J}_x$, $\mathcal{J}_y$, and $\mathcal{J}_z$ *do not anticommute* (unlike the Pauli matrices). Hence, we need to utilise our generic method to explicitly derive the equations of the Fermi arcs. We use the parametrisation $\psi_0^T = [1 \ a_1 + i b_1 \ a_2 + i b_2 \ a_3 + i b_3]$ because of the fourfold nature of the bands. Plugging it in Eq. (12) yields

$$\psi_0^\dagger \mathcal{J}_z \psi_0 = 0 \Rightarrow 3 - 3(a_3^2 + b_3^2) + a_1^2 + b_1^2 - (a_2^2 + b_2^2) = 0. \quad (26)$$

Employing the matrix equation, viz. Eq. (13), we get

$$\begin{aligned} 2E &= \sqrt{3}(a_1 + i b_1)(k_x - i k_y) - 3\kappa_i + 3i\kappa_r, \\ (a_1 + i b_1)(2E + \kappa_i - i\kappa_r) &= (2a_2 + 2i b_2 + \sqrt{3})k_x + (2b_2 - 2i a_2 + i\sqrt{3})k_y, \\ (a_2 + i b_2)(2E - \kappa_i + i\kappa_r) &= \sqrt{3}a_3(k_x - i k_y) + 2a_1(k_x + i k_y) + 2i b_1 k_x + i\sqrt{3}b_3 k_x - 2b_1 k_y + \sqrt{3}b_3 k_y, \\ \sqrt{3}(a_2 + i b_2)(k_x + i k_y) &= (a_3 + i b_3)(2E - 3\kappa_i + 3i\kappa_r) \\ \Rightarrow 2E &= \sqrt{3}a_1 k_x + \sqrt{3}b_1 k_y - 3\kappa_i, \quad \sqrt{3}a_1 k_y = \sqrt{3}b_1 k_x + 3\kappa_r, \quad a_1(2E + \kappa_i) = (2a_2 + \sqrt{3})k_x + 2b_2 k_y - b_1 \kappa_r, \\ 2a_2 k_y &= a_1 \kappa_r - b_1(2E + \kappa_i) + 2b_2 k_x + \sqrt{3}k_y, \quad 2b_1 k_y = a_2(\kappa_i - 2E) + 2a_1 k_x + \sqrt{3}a_3 k_x + \sqrt{3}b_3 k_y + b_2 \kappa_r, \\ a_2 \kappa_r &= 2a_1 k_y - \sqrt{3}a_3 k_y + b_2(\kappa_i - 2E) + 2b_1 k_x + \sqrt{3}b_3 k_x, \quad 2a_3 E = 3a_3 \kappa_i + \sqrt{3}a_2 k_x - \sqrt{3}b_2 k_y + 3b_3 \kappa_r, \\ 2b_3 E &= \sqrt{3}a_2 k_y - 3a_3 \kappa_r + 3b_3 \kappa_i + \sqrt{3}b_2 k_x. \end{aligned} \quad (27)$$

The explicit solutions are long and cumbersome. Hence, we do not write those explicitly. But, they can be parametrised in terms of one free parameter (which could be any of $\{a_1, a_2, a_3, b_1, b_2, b_3\}$). In place of the explicit expressions, we show the arcs in Fig. 3(b) for one single case by setting $\mu = 0.5$. The figure shows four Fermi arcs, in total, emanating outside the projection of the outer FS.

E. Double-Weyl semimetal

Double-Weyl nodes can be found in materials like HgCr₂Se₄ [80] and SrSi₂ [81, 82]), which exhibit a hybrid of linear dispersion (chosen to be the k_z -axis) and quadratic dispersion (in the $k_x k_y$ -plane). In the vicinity of such a nodal point, the low-energy effective continuum Hamiltonian is given by [7, 8, 24, 26, 27, 33, 38]

$$H_{dW} = \mathbf{d} \cdot \boldsymbol{\sigma}, \text{ where } \mathbf{d} \equiv \{d_x, d_y, d_z\} = \left\{ \frac{k_x^2 - k_y^2}{k_0}, \frac{2k_x k_y}{k_0}, k_z \right\}, \quad (28)$$

where k_0 is a material-dependent parameter. For simplicity, we assume the momenta to be scaled such that k_0 can be set to 1. Plugging in the parametrisation of $\psi_0^T = [1 \ a_1 + i b_1]$ in Eq. (12) leads to

$$\kappa_i \psi_0^\dagger \sigma_x \psi_0 = k_y \psi_0^\dagger \sigma_y \psi_0 \Rightarrow \kappa_i = \frac{b_1}{a_1} k_y. \quad (29)$$

Additionally, the two components of the matrix equation of Eq. (13) provide us with the following:

$$E = k_z - (a_1 + i b_1)(i\kappa_i - k_y + \kappa_r)^2 \text{ and } (a_1 + i b_1)(E + k_z) + (i\kappa_i + k_y + \kappa_r)^2 = 0. \quad (30)$$

The solutions are found easily after parametrisation $a_1 = a \cos t$ and $b_1 = a \sin t$: $E = \frac{\sqrt{k_z^2 \cos^2 t - 4k_y^4 \tan^2 t}}{\cos t}$, $\kappa_r = \frac{s k_y}{\cos(t)}$, where $a = s \frac{k_z \cos t - \sqrt{k_z^2 \cos^2 t - 4k_y^4 \tan^2 t}}{2k_y^2(1 + \frac{1}{\cos t})}$ and $s = \pm 1$. Thus, t serves an undetermined parameter, producing curves of varying shapes. The points on the SBZ where κ_r goes to zero are found to be $\{k_y, k_z\} = \{0, \pm\mu\}$.

For the case of two nodes separated along the k_z -direction by an amount k_w , we can easily determine the nature of the Fermi arcs by the replacement $k_z \rightarrow (k_z^2 - k_w^2)$. Fig. 4(a) illustrates the Fermi arcs for $\mu = 0.5$, $k_w = 1$, and $t = \pi/6$. Since the nodes carry Chern numbers equalling ± 2 , we observe two arcs emanating from the perimeter of each FS-projection.




FIG. 4. The Fermi arcs represent modes with $E = \mu$, where $\mu = 0.5$ and $k_w = 1$. (a) A pair of double-Weyl nodes sources two arcs from the perimeter of each FS- projection. Here, $t = \pi/6$ and $s = 1$. (b) A pair of triple-Weyl nodes sources three arcs from the perimeter of each FS-projection. Here, $t = 0$ and $s = 1$.

F. Triple-Weyl semimetal

Analogous to the double-Weyl nodes, there exist triple-Weyl nodes (in materials like transition-metal monochalcogenides [83]) from which bands with anisotropic dispersion emerge. The triple-Weyl case comprises a hybrid of linear dispersion (chosen to be the k_z -axis) and quadratic dispersion (in the $k_x k_y$ -plane). In the vicinity of such a nodal point, the low-energy effective continuum Hamiltonian is given by [7, 8, 24–27, 38]

$$H_{tW} = \mathbf{d} \cdot \boldsymbol{\sigma}, \text{ where } \mathbf{d} \equiv \{d_x, d_y, d_z\} = \left\{ \frac{k_x^3 - 3k_x k_y^2}{k_0^2}, \frac{3k_x^2 k_y - k_y^3}{k_0^2}, k_z \right\}, \quad (31)$$

where k_0 is a material-dependent parameter. Again, for simplicity, we set k_0 to 1. Since H_{tW} is cubic in k_x , Eq. (12) is understood here in the sense of the general boundary condition derived in the Appendix, $\Xi[\psi_0, \psi_0](0) = 0$ [equivalently, $\text{Im}(E) = 0$], rather than as a literal evaluation of the current operator $j_{r\perp}$ at the complex boundary-value $k_\perp \rightarrow \lambda$. As shown in the Appendix, the latter need not coincide with the correct condition beyond quadratic order in $k_\perp$. Plugging in the parametrisation of $\psi_0^T = [1 \ a_1 + i b_1]$ then leads to

$$\left[3k_y^2 + (\kappa_r - i\kappa_i)^2 + (\kappa_r + i\kappa_i)^2 - \kappa_r^2 - \kappa_i^2 \right] \psi_0^\dagger \sigma_x \psi_0 + 6\kappa_i k_y \psi_0^\dagger \sigma_y \psi_0 = 0 \Rightarrow a_1 (\kappa_r^2 - 3\kappa_i^2 + 3k_y^2) + 6b_1 \kappa_i k_y = 0. \quad (32)$$

Additionally, the two components of the matrix equation of Eq. (13) provide us with the following:

$$\begin{aligned} E &= k_z - (a_1 + i b_1) (\kappa_i + i k_y - i \kappa_r)^3 \text{ and } i a_1 (e + k_z) = b_1 (E + k_z) + (i \kappa_i + k_y + \kappa_r)^3 \\ \Rightarrow E &= k_z - a_1 \kappa_i \left[\kappa_i^2 - 3(k_y - \kappa_r)^2 \right] - b_1 (k_y - \kappa_r) \left[(k_y - \kappa_r)^2 - 3\kappa_i^2 \right], \quad b_1 (E + k_z) = (k_y + \kappa_r) \left[3\kappa_i^2 - (k_y + \kappa_r)^2 \right], \\ a_1 (k_y - \kappa_r) \left[(k_y - \kappa_r)^2 - 3\kappa_i^2 \right] &= b_1 \kappa_i \left[\kappa_i^2 - 3(k_y - \kappa_r)^2 \right], \quad \kappa_i \left[3(k_y + \kappa_r)^2 - \kappa_i^2 \right] = a_1 (E + k_z). \end{aligned} \quad (33)$$

Finding exact analytical solutions is cumbersome because of the cubic roots involved. Instead, we parametrise $a_1 = a \cos t$ and $b_1 = \sin t$, and we show here the solutions for $t = 0$: (1) $E = k_z$, $\kappa_r = \pm k_y$, $\kappa_i = 0$, and $a = 0$; (2) $E = \frac{1}{3} \sqrt{9k_z^2 - \frac{512k_y^6}{3}}$, $\kappa_r = s k_y$, $\kappa_i^2 = \tilde{s} \frac{2k_y}{\sqrt{3}}$, and $a = s \tilde{s} \frac{3\sqrt{3}k_z - \sqrt{27k_z^2 - 512k_y^6}}{64k_y^3}$, where $(s, \tilde{s}) = \pm 1$. The points on the SBZ, where κ_r for the three arcs goes to zero, are found to be $\{k_y, k_z\} = \{0, \pm \mu\}$.

For the case of two nodes separated along the k_z -direction by an amount $2k_w$, we can easily determine the nature of the Fermi arcs by the replacement $k_z \rightarrow (k_z^2 - k_w^2)$. Fig. 4(b) illustrates the Fermi arcs for $\mu = 0.5$, $k_w = 1$, and $s = 1$ (the value of $\tilde{s}$ does not matter) for the solution detailed above. Since the nodes carry Chern numbers equalling ± 3 , we observe three arcs emanating from the perimeter of each FS-projection.

G. Berry-dipole in a two-band model

In a specific two-band model, the low-energy effective Hamiltonian in the vicinity of a single node harbouring a BC-dipole [cf. Fig. 1(b)] is captured by [19]

$$H_{bd}(k_x, k_y, k_z) = 2 v v_z k_z (k_x \sigma_x + k_y \sigma_y) + [v^2 (k_x^2 + k_y^2) - k_z^2] \sigma_z. \quad (34)$$

Being an ideal dipole, this node carries vanishing BC-monopole charge. As such, one might think that there might be no Fermi arcs emerging on the SBZ. However, it turns out Fermi arcs do arise as surface states (on solving the relevant equations systematically using the generic method outlined in Sec. II B), representing paired edge states on 2d slices.

Since this is a two-band model, we again use $\psi_0^T = [1 \ a_1 + i b_1]$. Plugging it in Eq. (12) yields

$$v_p^2 \kappa_i \psi_0^\dagger \sigma_z \psi_0 + v_p k_z \psi_0^\dagger \sigma_x \psi_0 = 0 \Rightarrow 2 a_1 k_z - v_p (a_1^2 + b_1^2 - 1) \kappa_i = 0. \quad (35)$$

Next, the two components of the matrix equation of Eq. (13) take the forms of

$$\begin{aligned} E &= 2 (b_1 - i a_1) v_p v_z k_z (k_y - \kappa_r - \kappa_i) + v_p^2 [k_y^2 - (\kappa_i + \kappa_r)^2] - v_z^2 k_z^2 \\ \text{and } (a_1 + i b_1) &\left[v_z^2 k_z^2 - v_p^2 k_y^2 + v_p^2 (\kappa_i + \kappa_r)^2 - E \right] + 2 i k_z v_p v_z (k_y + \kappa_r + \kappa_i) = 0 \\ \Rightarrow E &= -2 b_1 v_p v_z k_z (\kappa_r + \kappa_i) + 2 b_1 v_p v_z k_y k_z - v_p^2 (\kappa_i + \kappa_r)^2 + v_p^2 k_y^2 - v_z^2 k_z^2, \quad a_1 k_z (\kappa_r + \kappa_i - k_y) = 0, \\ a_1 &\left(v_p^2 (\kappa_r + \kappa_i)^2 - v_p^2 k_y^2 + v_z^2 k_z^2 - E \right) = 0, \quad b_1 \left[v_p^2 (\kappa_r + \kappa_i)^2 - v_p^2 k_y^2 + v_z^2 k_z^2 - E \right] + 2 v_p v_z k_z (\kappa_r + \kappa_i + k_y) = 0. \end{aligned} \quad (36)$$

We obtain the solutions as $E = \frac{k_z v_z}{b_1^2} [2 b_1 v_p k_y + (b_1^2 - 1) k_z v_z]$, $\kappa_r = k_y - \frac{k_z v_z}{b_1 v_p}$, $\kappa_i = 0$, and $a_1 = 0$. The points on the SBZ where κ_r goes to zero (and the arc becomes tangential to the projection of the FS) are found to be $\{k_y, k_z\} = \pm \sqrt{\frac{\mu}{1+b_1^2}} \{ \frac{1}{v_p}, \frac{b_1}{v_z} \}$, denoting antipodal points on a FS-projection. In fact, these tangents are inward and outward to the projection, being proportional to $\pm \{b_1, -1\}$. If the BZ contains two BC-dipole nodes, separated along the k_z -direction by an amount $2k_w$, the answers are obtained by the replacement $k_z \rightarrow (k_z^2 - k_w^2)$. Fig. 5(a) shows the resulting Fermi arcs for a particular choice of the parameter-values. Evidently, two Fermi arcs graze past each FS-projection. This is tied to a finer-grained momentum-resolved structure, obtained by treating each constant- k_z slice of the BZ as an independent 2d Hamiltonian and examining its Chern number $\mathcal{C}(k_z)$. As shown in Ref. [19], this layer Chern number vanishes identically for every k_z lying between the two nodes. Because the Chern number is zero, no slice can host a single unpaired chiral edge mode — as in a quantum-spin-Hall insulator, the boundary states are forced to appear as a counter-propagating pair. Unlike a genuine quantum-spin-Hall edge, however, this protection is furnished not by time-reversal symmetry, which is absent here, but by a chiral symmetry along a high-symmetry line of each k_z -slice, characterised by a k_z -dependent winding number. A consequence of this distinct protection mechanism is that the pair of Fermi arcs on a given surface is found to carry the same spin-polarisation, rather than the opposite spin-textures expected of a time-reversal-related pair, as would occur in a genuine quantum-spin-Hall edge or in the Fermi arcs of a Dirac semimetal.

H. Berry-dipole in a three-band model

In Ref. [20], massless multifold Hopf semimetals (MMHSs) have been introduced which host BC-dipoles at nodes where linearly-dispersing bands cross. We consider the simplest case with a threefold-degenerate node, captured by the effective continuum Hamiltonian [20–22],

$$H_H = k_x \lambda_1 + k_y \lambda_2 + k_z \lambda_5, \quad (37)$$

where

$$\lambda_1 = \begin{bmatrix} 0 & 1 & 0 \\ 1 & 0 & 0 \\ 0 & 0 & 0 \end{bmatrix}, \quad \lambda_2 = \begin{bmatrix} 0 & -i & 0 \\ i & 0 & 0 \\ 0 & 0 & 0 \end{bmatrix}, \quad \lambda_5 = \begin{bmatrix} 0 & 0 & -i \\ 0 & 0 & 0 \\ i & 0 & 0 \end{bmatrix}. \quad (38)$$

For this 3-band model, we use the parametrisation $\psi_0^T = [1 \ a_1 + i b_1 \ a_2 + i b_2]$. For a boundary at $x = 0$, plugging it in Eq. (12) yields

$$\psi_0^\dagger \lambda_1 \psi_0 = 0 \Rightarrow a_1 = 0. \quad (39)$$




FIG. 5. A pair of nodes carrying ideal BC-dipoles using the model in (a) Eq. (34), with $v_p = v_z = 1$; (b) Eq. (37). In each case, Fermi arcs graze through each FS-projection at two distinct points, meeting tangentially along a FS-projection. The Fermi arcs represent modes with $E = \mu$, where $\mu = 0.5$ and $k_w = 1$. The dashed red closed contours represent the projections of the bulk FSs on the $k_y k_z$ -plane. Each arc corresponds to a distinct value of b_1 , colour-coded as shown in the plot-legends.

Employing the matrix equation, viz. Eq. (13), we get

$$\begin{aligned} (b_2 - i a_2) k_z + b_1 (k_y - i \kappa_i - \kappa_r) &= E, \quad k_y + \kappa_r + i \kappa_i = b_1 E, \quad \text{and} \quad E(a_2 + i b_2) = i k_z \\ \Rightarrow b_1 (k_y - \kappa_r) + b_2 k_z &= E, \quad a_2 k_z + b_1 \kappa_i = 0, \quad \kappa_i = 0, \quad b_1 E = k_y + \kappa_r, \quad a_2 E = 0, \quad b_2 E = k_z. \end{aligned} \quad (40)$$

The solutions turn out to be $E = \frac{b_1 k_y + \sqrt{b_1^2(k_y^2 + k_z^2) + k_z^2}}{1 + b_1^2}$, $\kappa_r = \frac{k_z^2 + b_1 \sqrt{b_1^2(k_y^2 + k_z^2) - k_y}}{1 + b_1^2}$, $\kappa_i = 0$, $a_2 = 0$, and $b_2 = \frac{\sqrt{b_1^2(k_y^2 + k_z^2) + k_z^2} - b_1 k_y}{k_z}$. The points on the SBZ where κ_r goes to zero (and the arc becomes tangential to the projection of the FS) are found to be $\{k_y, k_z\} = \mu \{b_1, \pm \sqrt{1 - b_1^2}\}$. This also tells us that the parameter b_1 is constrained to obey $|b_1| \leq 1$. The corresponding tangents are proportional to $\{\pm \sqrt{1 - b_1^2}, -b_1\}$ and, hence, lead to the picture that one arc is entering and the other leaving the bulk-states. If the BZ contains two BC-dipole nodes, separated along the k_z -direction by an amount $2k_w$, the answers are obtained by the replacement $k_z \rightarrow (k_z^2 - k_w^2)$. Fig. 5(b) demonstrates the nature of the Fermi arcs for some distinct values of b_1 . Depending on the value of b_1 , either two separate Fermi arcs graze past each FS-projection, or the same Fermi arc folds back and rejoins the same FS-projection. The overall behaviour is tied to the fact that the 2d layer-Hamiltonians for k_z between $\pm k_w$ carry a vanishing Chern number. Yet they support a pair of counter-propagating (helical) edge modes – one entering and one leaving – much like the edge pair of a quantum-spin-Hall insulator. Outside this range, a 2d layer hosts no edge mode at all. The net chirality and, hence, the Chern number stays zero irrespective of whether zero, two, or four such edge-modes are present. A concrete grounding for the helical interpretation comes directly from the lattice model of Ref. [20]. In their construction, H_H arises as the critical point of a gapped tight-binding model, $h_N^{\text{Hopf}}(\mathbf{k})$. For this lattice model, the three weak topological invariants, namely the layer Chern numbers, are shown to vanish identically. Since a slice at fixed k_z is one of these three orientations, this establishes directly that the layer Chern number of every k_z slice is exactly zero, a property required for the Hopf-number classification to be well defined in the first place. At the same time, the BC vectors of the bands satisfy $\Omega_s = \Omega_{-s}$ [where $s \in (\pm 1, 0)$ is the band index]. Thus, the two dispersive bands carry BC of the same sign in contrast with a Weyl node (which features $\Omega_s = -\Omega_{-s}$ with $s = \pm 1$). Thus, our results coming from the continuum Hamiltonian H_H are a defining consequence of the underlying chiral symmetry that these models possess. Because the layer Chern number is zero throughout the range of k_z bounded by the two FS-projections, whatever edge states do appear must arise as a counter-propagating pair, in direct analogy with the edge pair of a quantum-spin-Hall insulator. Unlike the quantum-spin-Hall case, however, the protection here comes from the chiral symmetry of the Hopf Hamiltonian itself, rather than from time-reversal symmetry.




FIG. 6. (a) The FS-projection is obtained by cutting the 3d FS with the yellow-coloured 2d surface, captured by Eq. (44). Here, $\mu = 0.25$ and $v = 1$. (b) The Fermi arcs represent modes with $E = \mu$, where $\mu = 0.25$. The dashed red closed contour represents the projection of the bulk FS on the $k_y k_z$ -plane.

I. Quadruple-Weyl node with monopole-charge 4

A quadruple-Weyl node (QWN) with twofold degeneracy carries $|C| = 4$ [84–87] and can exist only in spinless systems at specific time-reversal-symmetric points. Thus, they can appear in electronic bandstructures of materials with negligible SOC or in the phonon spectra of artificial crystals (such as photonic crystals), all of which can be treated as spinless systems. Let us take the lattice model of Ref. [87], where two nodes of opposite chiralities emerge at the Γ - and R -points. The node sitting at the Γ -point can be described by the Hamiltonian,

$$H_{qW} = \mathbf{d} \cdot \boldsymbol{\sigma}, \text{ where } \mathbf{d} \equiv \{d_x, d_y, d_z\} = \left\{ \frac{v(k_x^2 - k_y^2)}{2}, \frac{(k_x^2 + k_y^2 - 2k_z^2)}{2}, v k_x k_y k_z \right\}. \quad (41)$$

Here we fix v to be positive. The energy eigenvalues are given by $\pm \sqrt{v^2 [2k_x^2 k_y^2 (2k_z^2 - 1) + k_x^4 + k_y^4] + (k_x^2 + k_y^2 - 2k_z^2)^2} / 2$. Clearly, the dispersion of the bands is anisotropic, with a cubic dispersion along the (111) direction and quadratic dispersion along any other direction. Here, we expect 4 Fermi arcs to emanate from the nodal point [62], which we will derive explicitly by considering a boundary at $x = 0$.

On using $\psi_0^T = [1 \ a_1 + i b_1]$, Eq. (12) yields

$$\kappa_i \left(\psi_0^\dagger \sigma_x \psi_0 + \psi_0^\dagger \sigma_y \psi_0 \right) + v k_y k_z \psi_0^\dagger \sigma_z \psi_0 = 0 \Rightarrow 2 \kappa_i (a_1 v + b_1) = v (1 - a_1^2 - b_1^2) k_y k_z. \quad (42)$$

Employing the matrix equation of Eq. (13), we get

$$\begin{aligned} a_1 \left[(v - i) (\kappa_i - i \kappa_r)^2 - (v + i) k_y^2 + 2 i k_z^2 \right] + b_1 \left[(1 + i v) (\kappa_i - i \kappa_r)^2 + (1 - i v) k_y^2 - 2 k_z^2 \right] &= 2 E + 2 v k_y k_z (\kappa_i - i \kappa_r) \\ \text{and } a_1 E = a_1 v k_y k_z (\kappa_i - i \kappa_r) - i b_1 E + b_1 v k_y k_z (\kappa_r + i \kappa_i) + \frac{v + i}{2} (\kappa_i - i \kappa_r)^2 - \frac{(v - i) k_y^2}{2} - i k_z^2 \\ \Rightarrow 2 E + 2 v \kappa_i k_y k_z &= b_1 (\kappa_i^2 + 2 v \kappa_i \kappa_r + k_y^2 - 2 k_z^2 - \kappa_r^2) - a_1 [2 \kappa_i \kappa_r + v (\kappa_r^2 - \kappa_i^2) + v k_y^2], \\ a_1 (\kappa_i^2 + 2 v \kappa_i \kappa_r + k_y^2 - 2 k_z^2 - \kappa_r^2) &= -b_1 (2 \kappa_i \kappa_r - v \kappa_i^2 + v k_y^2 + v \kappa_r^2) + 2 v k_y k_z \kappa_r, \\ 2 a_1 E &= 2 a_1 v \kappa_i k_y k_z + 2 \kappa_r (b_1 v k_y k_z + \kappa_i) + v \kappa_i^2 - v k_y^2 - v \kappa_r^2, \\ 2 b_1 E &= -2 v \kappa_r (a_1 k_y k_z + \kappa_i) + 2 b_1 v \kappa_i k_y k_z + \kappa_i^2 + k_y^2 - 2 k_z^2 - \kappa_r^2. \end{aligned} \quad (43)$$

The admissible solutions for $\mu \geq 0$ are: (1) $E = -\frac{v(k_y^2 - k_z^2)}{\sqrt{1+v^2}}$, $\kappa_r = -\frac{v k_y k_z}{\sqrt{1+v^2}}$, $\kappa_i = \pm \sqrt{\frac{2k_z^2 - k_y^2[v^2(k_z^2 - 1) + 1]}{1+v^2}}$, $a_1 = \frac{1}{\sqrt{v^2+1}}$, and $b_1 = \frac{-v}{\sqrt{v^2+1}}$; and (2) $E = \frac{v(k_y^2 - k_z^2)}{\sqrt{1+v^2}}$, $\kappa_r = \frac{v k_y k_z}{\sqrt{1+v^2}}$, $\kappa_i = \pm \sqrt{\frac{2k_z^2 - k_y^2[v^2(k_z^2 - 1) + 1]}{1+v^2}}$, $a_1 = \frac{-1}{\sqrt{v^2+1}}$, and $b_1 = \frac{v}{\sqrt{v^2+1}}$.

Unlike the cases discussed so far, the projection of the FS on the $x = 0$ boundary is not obtained by setting $k_x = 0$. Instead, it is given by the values $k_x = \pm \frac{\sqrt{2k_z^2 - 2v^2 k_y^2 k_z^2 + (v^2 - 1)k_y^2}}{\sqrt{1+v^2}}$, which leads to the closed curve (lying in the $k_y k_z$ -plane)

defined by

$$v \sqrt{\frac{k_z^4 - k_y^4 (k_z^2 - 1) (1 + v^2 k_z^2) + 2 k_y^2 k_z^2 (k_z^2 - 1)}{1 + v^2}} = \mu. \quad (44)$$

The case of $v = 1$ and $\mu = 0.25$ is illustrated in Fig. 6(a). Keeping this in mind, the points on the SBZ where κ_r goes to zero, becoming tangential to the FS-projection, are found to be $\{k_y, k_z\} = \left\{0, \pm \frac{\sqrt{\mu} \sqrt[4]{1+v^2}}{\sqrt{v}}\right\}$ and $\{k_y, k_z\} = \left\{\pm \frac{\sqrt{\mu} \sqrt[4]{1+v^2}}{\sqrt{v}}, 0\right\}$, respectively. Therefore, for different values of v , we get Fermi arcs of distinct orientations. The tangents to the FS-projection, where the arcs meet the bulk states, are proportional to $\{\pm 1, 0\}$ and $\{0, \pm 1\}$. These arcs are thus all leaving the bulk states at the projection. Fig. 6(b) illustrates the arcs for $\mu = 0.25$ and two values of v . It might seem that the arcs end in thin air, but in actual lattice calculations, they will be found to end on some other nodal point or continue as arcs connecting with those ending on the conjugate QWN-projections located at the R -point. The effective Hamiltonian in Eq. (41), correct only in the vicinity of the node, of course cannot capture such global details.

IV. SUMMARY, DISCUSSIONS, AND OUTLOOK

From our analysis, we observe the following: While N_3 (and, hence, $\mathcal{C}$) is the topological invariant governing the stability of a point node itself, the existence and multiplicity of the associated Fermi arcs are more directly controlled by the Chern numbers $\mathcal{C}(k_z)$ of the family of 2d Hamiltonians obtained by slicing the BZ at fixed values of one momentum component parallel to the surface (say, k_z). Nodes sharing the same value of N_3 are topologically equivalent in the sense of carrying the same number of protected arc branches, but generically differ in band-multiplicity and in the momentum-power/anisotropy of the dispersion, both of which are non-universal and set the detailed curvature of the arcs rather than their protected count. We provide below a comparison on a case-by-case basis:

- *Untilted versus tilted Weyl node:* The tilt term $\eta k_x \mathbb{I}_{2 \times 2}$ existing in Eq. (17) is proportional to the identity matrix and does not alter the eigenvectors of $H_W(\mathbf{k})$ at all. Thus, the associated BC and, hence, $N_3 = \pm 1$ is completely unchanged. Any visible difference of the resulting Fermi arcs in the two cases is thus not a topological effect at all, but it simply reflects the anisotropic reshaping of the bulk FS (and of its projection) by the tilt.
- *Triple-point node versus double-Weyl node:* Both carry $N_3 = \pm 2$ and, consistently, both source exactly two Fermi arcs per node. However, an TSM node is a threefold-degenerate isotropic crossing, while a double-Weyl node is a twofold-degenerate crossing with an anisotropic dispersion. The value of N_3 , being a total flux (i.e., an integral quantity), is insensitive to this difference in band-multiplicity and angular/radial distribution of the underlying BC — it only counts the net number of protected chiral branches guaranteed by bulk-boundary correspondence, and not their microscopic origin. This is precisely why the two arc families look qualitatively different. The detailed curvature of an individual arc is controlled by non-topological data [e.g., the local dispersion and the boundary-condition parameter(s)], rather than by N_3 itself.
- *RSW node versus quadruple-Weyl node:* Both carry $N_3 = \pm 4$ and both source four Fermi arcs, yet the RSW node is a fourfold-degenerate fully-isotropic linear crossing, whereas the QWN is twofold-degenerate with nonlinear anisotropic dispersion. Correspondingly, the bulk FSs and, thus, the shapes of their projections onto the SBZ, are entirely different in the two cases. In the QWN case, the projected FS is not even a simple curve of the form $k = \mu$, but instead is a more intricate closed contour. Once again, N_3 dictates only the topologically-protected count of arcs (four, in both cases), while their detailed geometry is fixed by the non-universal bandstructure.
- *2-band or 3-band BC-dipole node:* Here $N_3 = 0$, yet a pair of Fermi arcs is found to graze each FS-projection. The existence of the arcs is tied to a finer-grained momentum-resolved structure, obtained by treating each constant- k_z slice of the BZ as an independent 2d Hamiltonian and examining its Chern number $\mathcal{C}(k_z)$. As shown in Ref. [19], this layer Chern number vanishes identically for every k_z lying between the two nodes. Because the Chern number is zero, no slice can host a single unpaired chiral edge mode. Therefore, as in a quantum-spin-Hall insulator, the boundary states are forced to appear as a counter-propagating pair. Unlike a genuine quantum-spin-Hall edge, however, this protection is furnished not by time-reversal symmetry, but by a chiral symmetry.

To summarise, nodes sharing the same N_3 are, from the point of view of the bulk topological classification alone, indeed indistinguishable. After all N_3 is a coarse integer invariant that only counts the total winding of the Green's function (equivalently, the net Berry flux) around the node, and says nothing about how that total charge is distributed among the internal (pseudospin/band) degrees of freedom, or (for the dipole cases) about how it is distributed in k_z . Our boundary-condition formalism, however, is sensitive to more than N_3 alone: it depends on the full polynomial structure of H_N . In particular, it depends on the band multiplicity N and on the power(s) of momentum through which the monopole charge is realised. Consequently, they yield Fermi arcs of visibly-different shapes, curvature, and parameter dependence, even though the number of arcs terminating at each FS-projection (fixed by $|N_3|$, where non-zero) is the same.

It is instructive to compare the arc families derived above with Fermi arcs resolved by ARPES. The number of arc branches emanating from a given nodal projection is fixed by the topological invariant N_3 of the node (equivalently, by the Chern number). ARPES measurements on WSMs of the TaAs family reveal short Fermi arcs consistent with $N_3 = \pm 1$. Chiral crystals such as CoSi, RhSi, and PtGa, on the other hand, host multifold nodal degeneracies (or higher-charge nodes), exemplified by our RSW and pseudospin-1 models. These display long Fermi arcs that traverse an appreciable fraction of the SBZ and connect nodes of opposite chiralities located at different high-symmetry points [61, 88, 89], consistent with $|N_3| = 4$ obtained here. Both features are captured naturally by our results: the number of arc branches sourced at a given projected FS is fixed by N_3 , exactly as observed — single arcs for TaAs-like materials and multiple/longer arcs for the higher-charge multifold semimetals. This protected count is entirely fixed by bulk topology and is insensitive to the boundary-condition parameters. By contrast, the pronounced curvature, kinking, and sometimes counter-intuitive (“bizarre”) shape of individual arcs seen within a single ARPES data set, even for the same bulk charge, is controlled by our boundary-condition parameters in the notation of Sec. III. These parameters are fixed by the microscopic details of the surface termination and, therefore, expected to vary between samples, cleaves, or materials sharing the same bulk topology. In other words, the qualitative topologically-protected features of Fermi arcs (their number and connectivity to bulk FSs’ projections) are governed by N_3 . Their sample-dependent appearance in ARPES reflects the family of admissible boundary conditions instead, which are a direct symmetry-allowed consequence of surface reconstruction/termination chemistry. Our generic construction shows explicitly how a topologically fixed number of arcs can nonetheless be continuously deformed in shape by these parameters. This offers a concrete mechanism for the diversity of arc geometries reported experimentally for materials sharing the same bulk nodal charge, as well as parametrising this correspondence explicitly and analytically for the first time across a range of nodal-point types.

Our derivations for the nature of surface states in 3d semimetals provide an exhaustive analysis of generic boundary conditions for open boundaries. The main line of argument hinges on the preservation of self-adjointness (i.e., Hermiticity) of the effective Hamiltonian of the corresponding surface, which must host eigenstates that decay exponentially as we move away from the boundary with the topological material. On the side of the material itself, the states must merge with the eigenstates (of the bulk Hamiltonian) representing the 3d bulk states. Through explicit examples, we have shown how the number of Fermi arcs, arising in the SBZ, gives us a clear signature of the net Chern number at a given nodal point, conforming to the well-established notion of bulk-boundary correspondence. However exotic the bandstructure might be, our formalism will work in all generic cases. In the future, we plan to investigate the dynamics of the surface states, for example when a magnetic field is applied, when we can observe quantum oscillations [90, 91].

ACKNOWLEDGMENTS

This research, leading to the results reported, has received funding from the Council of Science & Technology (CST), U.P.

APPENDIX: DERIVATION OF THE BOUNDARY CONDITIONS

In this appendix, we demonstrate explicitly that the general boundary term can be obtained by applying a Lagrange/Wronskian identity for systems containing generic higher-order-derivative operators. We break the underlying derivation up into the following steps:

- Step 1 (set-up):
We write the bulk Hamiltonian as a matrix polynomial in the perpendicular momentum as

$$H_N(k_\perp, \mathbf{k}_\parallel) = \sum_{n \geq 0} C_n(\mathbf{k}_\parallel) k_\perp^n.$$

Hermiticity of H_N for every real $k_\perp$ requires each C_n to be a Hermitian matrix. Throughout the derivation, $k_\perp$ should be understood as the differential operator, $-i \partial_{r_\perp}$.

- Step 2 (a Lagrange/Wronskian identity for a single power of $k_\perp$):
By induction on the degree n , one establishes the operator identity

$$\psi^\dagger(r_\perp) [k_\perp^n \phi(r_\perp)] - [k_\perp^n \psi(r_\perp)]^\dagger \phi(r_\perp) = -i \partial_{r_\perp} \sum_{m=0}^{n-1} [k_\perp^m \psi(r_\perp)]^\dagger [k_\perp^{n-1-m} \phi(r_\perp)]. \quad (45)$$

This identity generalises the familiar integration-by-parts formula used for the Weyl-node Hamiltonian. The base case of $n = 1$ is immediate, when $\psi^\dagger(k_\perp \phi) - (k_\perp \psi)^\dagger \phi = -i \partial_{r_\perp} (\psi^\dagger \phi)$, and is exactly the manipulation used implicitly for the linear-in- $k_\perp$ Weyl Hamiltonian. Assuming Eq. (45) holds up to degree $(n - 1)$, writing $k_\perp^n \phi = k_\perp (k_\perp^{n-1} \phi)$, and adding and subtracting $(k_\perp^{n-1} \psi)^\dagger (k_\perp \phi)$ reduces the degree- n identity to the base case (applied to the pair, ψ

and $k_\perp^{n-1} \phi$) plus the degree- $(n-1)$ identity [applied to the pair $k_\perp \psi$ and ϕ]. This completes the induction and fixes the coefficients on the right-hand side of Eq. (45) uniquely.

- Step 3 (boundary functional):

Multiplying Eq. (45) by the constant (i.e., $r_\perp$ -independent) Hermitian matrix C_n , summing over n , and integrating over the half-space gives

$$\psi^\dagger(r_\perp) H_{r_\perp} \phi(r_\perp) - [H_{r_\perp} \psi(r_\perp)]^\dagger \phi(r_\perp) = -i \partial_{r_\perp} \Xi[\psi, \phi](r_\perp), \quad \Xi[\psi, \phi] \equiv \sum_n \sum_{m=0}^{n-1} (k_\perp^m \psi)^\dagger C_n (k_\perp^{n-1-m} \phi). \quad (46)$$

Integrating over $r_\perp \in [0, \infty)$, the contribution at $r_\perp \rightarrow \infty$ vanishes because $\psi, \phi \propto e^{-\kappa r_\perp}$ [with $\text{Re}(\kappa) > 0$] decay exponentially together with all their derivatives, so that Eq. (10) becomes simply $\Xi[\psi, \phi](0) = 0$.

- Step 4 (physical boundary state):

It remains to evaluate $\Xi[\psi, \phi](0)$ on the actual candidate surface state, $\psi(r_\perp) = \phi(r_\perp) = \psi_0 e^{-\kappa r_\perp}$. Writing $\lambda \equiv i\kappa$, so that $k_\perp^m \psi_0 = \lambda^m \psi_0$ for every m (since $-i \partial_{r_\perp} e^{-\kappa r_\perp} = i\kappa e^{-\kappa r_\perp}$). Here one must be careful: normalisability of the surface state fixes only $\kappa_r \equiv \text{Re}(\kappa) > 0$, while $\kappa_i \equiv \text{Im}(\kappa)$ is, in general, an independent real unknown. The latter is solved-for jointly with E [cf. the parametrisation below Eq. (13)]. Consequently, $\text{Im}(\lambda) = \kappa_r > 0$ strictly, implying λ is never real, and $(k_\perp^m \psi_0)^\dagger = \bar{\lambda}^m \psi_0^\dagger$, with $\bar{\lambda} \neq \lambda$ in general. The m -sum defining Ξ must therefore be summed as the (generally non-degenerate) finite geometric series, leading to

$$\sum_{m=0}^{n-1} \bar{\lambda}^m \lambda^{n-1-m} = \frac{\lambda^n - \bar{\lambda}^n}{\lambda - \bar{\lambda}}, \quad \lambda \neq \bar{\lambda}, \quad (47)$$

rather than collapsing termwise to $n \lambda^{n-1}$. This gives

$$\Xi[\psi_0, \psi_0](0) = \sum_n \psi_0^\dagger C_n \psi_0 \frac{\lambda^n - \bar{\lambda}^n}{\lambda - \bar{\lambda}} = \frac{\psi_0^\dagger H_N(\lambda) \psi_0 - \psi_0^\dagger H_N(\bar{\lambda}) \psi_0}{\lambda - \bar{\lambda}}, \quad (48)$$

where $H_N(\lambda) \equiv \sum_n C_n \lambda^n$ denotes the matrix polynomial $H_N(k_\perp, \mathbf{k}_\parallel)$, with $k_\perp \rightarrow \lambda$ (a c-number substitution, not an operator one). Now, ψ_0 solves the eigenvalue equation of Eq. (13) specialised to this ansatz, $H_N(\lambda) \psi_0 = E \psi_0$ — hence, $\psi_0^\dagger H_N(\lambda) \psi_0 = E |\psi_0|^2$. Since $C_n^\dagger = C_n$, we have $H_N(\bar{\lambda}) = H_N(\lambda)^\dagger$, leading to $\psi_0^\dagger H_N(\bar{\lambda}) \psi_0 = [H_N(\lambda) \psi_0]^\dagger \psi_0 = E^* |\psi_0|^2$. Using $\lambda - \bar{\lambda} = 2i \text{Im}(\lambda) = 2i \kappa_r$, we obtain the exact identity,

$$\Xi[\psi_0, \psi_0]|_{r_\perp=0} = \frac{(E - E^*) |\psi_0|^2}{2i \kappa_r} = \frac{\text{Im}(E)}{\kappa_r} |\psi_0|^2. \quad (49)$$

Eq. (10) (i.e., $\Xi(0) = 0$, from Step 3) is therefore equivalent, order by order, and irrespective of the polynomial degree of H_N in $k_\perp$, to the single real condition, $\text{Im}(E) = 0$. The Hermiticity/hard-wall requirement is precisely the statement that a genuine surface-bound state must carry a real energy eigenvalue, as any state in the domain of a self-adjoint operator must. This is the general form of the boundary condition within the class of polynomial continuum Hamiltonians considered here, and is the condition actually enforced [as one real equation among the $(2N+1)$ counted below Eq. (13)]. It reduces to the familiar statement of Eq. (12), $\psi_0^\dagger j_{r_\perp} \psi_0|_{r_\perp=0} = 0$, precisely when H_N is at most linear in $k_\perp$ [i.e., $H_N = C_1 k_\perp + C_0(\mathbf{k}_\parallel)$, as for the untilted WSM]. There, $j_{r_\perp} = \partial_{k_\perp} H_N = C_1$ is κ -independent and Hermitian, the m -sum contains the single term $m = 0$ (so no $\lambda, \bar{\lambda}$ dependence enters at all], and $\Xi = \psi_0^\dagger C_1 \psi_0$ is already manifestly real — consistent with, and equal to, $\text{Im}(E) |\psi_0|^2 / \kappa_r$ above.

The same result also follows directly from the underlying physical continuity equation, independently of the geometric-sum bookkeeping above. Since $\psi(r_\perp)$ solves $H_{r_\perp} \psi(r_\perp) = E \psi(r_\perp)$ pointwise, we have $\psi^\dagger(r_\perp) H_{r_\perp} \psi(r_\perp) = E |\psi(r_\perp)|^2$ and $(H_{r_\perp} \psi(r_\perp))^\dagger \psi(r_\perp) = E^* |\psi(r_\perp)|^2$. Thus, the Step 3 identity, specialised to $\phi = \psi$, reads $(E - E^*) |\psi(r_\perp)|^2 = -i \partial_{r_\perp} \Xi[\psi, \psi](r_\perp)$, i.e., $\partial_{r_\perp} \Xi[\psi, \psi](r_\perp) = -2 \text{Im}(E) |\psi(r_\perp)|^2$. Integrating from $r_\perp = 0$ to ∞ , using $\Xi[\psi, \psi](\infty) = 0$ by decay and $\int_0^\infty |\psi_0|^2 e^{-2\kappa_r r_\perp} dr_\perp = |\psi_0|^2 / (2\kappa_r)$, reproduces $\Xi[\psi_0, \psi_0](0) = \text{Im}(E) |\psi_0|^2 / \kappa_r$ exactly, for any polynomial degree of H_N . We emphasise that this is not the same statement as $\text{Re}[\psi_0^\dagger j_{r_\perp} \psi_0] = 0$: the operator $j_{r_\perp} = \partial_{k_\perp} H_N$ is Hermitian only when evaluated at real $k_\perp$, whereas at the boundary it is evaluated at the complex value $k_\perp \rightarrow \lambda$. Therefore, $\psi_0^\dagger j_{r_\perp} \psi_0|_{r_\perp=0}$ is an analytic continuation rather than a genuine Hermitian expectation value, and need not coincide with the manifestly real $\Xi[\psi_0, \psi_0](0)$ beyond quadratic order in $k_\perp$, as we illustrate explicitly below.

As an explicit illustration beyond the Weyl case, consider the double-Weyl Hamiltonian of Eq. (28), for which C_0, C_1 , and C_2 are all nonzero, so that H_N is quadratic in $k_\perp = k_x$. For any polynomial containing only powers up to $n = 2$,

the geometric sum of Step 4 simplifies further: since the $n = 2$ factor obeys $(\lambda^2 - \bar{\lambda}^2)/(\lambda - \bar{\lambda}) = \lambda + \bar{\lambda} = 2\text{Re}(\lambda)$ for any complex λ , the $n = 2$ contribution to $\Xi[\psi_0, \psi_0](0)$ reduces to $2\text{Re}(\lambda)\psi_0^\dagger C_2 \psi_0$. Hence, it coincides exactly with the real part of the corresponding term of $\psi_0^\dagger j_{r\perp} \psi_0$. Combined with the $n \leq 1$ terms, which are already manifestly real, this gives $\Xi[\psi_0, \psi_0](0) = \text{Re}[\psi_0^\dagger j_{r\perp} \psi_0]_{r\perp=0}$, whenever H_N is at most quadratic in $k_\perp$. Thus, $\text{Im}(E) = 0$ is equivalent, for such Hamiltonians, to the real part of the current condition of Eq. (12), even though κ itself remains complex. Using $\psi_0^T = [1 \quad a_1 + i b_1]$ and $j_x = \partial_{k_x} H_{dW} = 2k_x \sigma_x + 2k_y \sigma_y$ (with k_0 set to 1), one finds $\psi_0^\dagger \sigma_x \psi_0 = 2a_1$ and $\psi_0^\dagger \sigma_y \psi_0 = 2b_1$. This leads to $\psi_0^\dagger j_x \psi_0|_{x=0} = 2i\kappa(2a_1) + 2k_y(2b_1) = (4b_1 k_y - 4a_1 \kappa_i) + 4i a_1 \kappa_r$, whose real part vanishing gives exactly $\kappa_i = (b_1/a_1) k_y$ [reproducing Eq. (29)]. This confirms explicitly, for the case in the paper where H_N is quadratic, that the general condition $\text{Im}(E) = 0$ derived above reduces to the boundary condition already used in Sec. III E. For Hamiltonians containing $k_\perp^n$ with $n \geq 3$ (e.g., the triple- and quadruple-Weyl models), this intermediate identification with $\text{Re}[\psi_0^\dagger j_{r\perp} \psi_0]$ need not hold term by term. There, $\text{Im}(E) = 0$ itself, established generally in Step 4 above, remains the quintessential boundary condition.

-
- [1] A. A. Burkov and L. Balents, Weyl semimetal in a topological insulator multilayer, *Phys. Rev. Lett.* **107**, 127205 (2011).
 - [2] P. Hosur, Friedel oscillations due to Fermi arcs in Weyl semimetals, *Phys. Rev. B* **86**, 195102 (2012).
 - [3] N. P. Armitage, E. J. Mele, and A. Vishwanath, Weyl and Dirac semimetals in three-dimensional solids, *Rev. Mod. Phys.* **90**, 015001 (2018).
 - [4] P. Hosur and X. Qi, Recent developments in transport phenomena in Weyl semimetals, *Comptes Rendus Physique* **14**, 857 (2013).
 - [5] B. Yan and C. Felser, Topological materials: Weyl semimetals, *Annual Rev. of Condensed Matter Phys.* **8**, 337 (2017).
 - [6] I. Mandal and K. Saha, Thermoelectric response in nodal-point semimetals, *Ann. Phys. (Berlin)* **536**, 2400016 (2024).
 - [7] B. Bradlyn, J. Cano, Z. Wang, M. G. Vergniory, C. Felser, R. J. Cava, and B. A. Bernevig, Beyond Dirac and Weyl fermions: Unconventional quasiparticles in conventional crystals, *Science* **353** (2016).
 - [8] C. Fang, M. J. Gilbert, X. Dai, and B. A. Bernevig, Multi-Weyl topological semimetals stabilized by point group symmetry, *Phys. Rev. Lett.* **108**, 266802 (2012).
 - [9] F. Flicker, F. de Juan, B. Bradlyn, T. Morimoto, M. G. Vergniory, and A. G. Grushin, Chiral optical response of multifold fermions, *Phys. Rev. B* **98**, 155145 (2018).
 - [10] F. Balduini, A. Molinari, L. Rocchino, V. Hasse, C. Felser, M. Sousa, C. Zota, H. Schmid, A. G. Grushin, and B. Gotsmann, Intrinsic negative magnetoresistance from the chiral anomaly of multifold fermions, *Nature Communications* **15**, 6526 (2024).
 - [11] L. Liang and Y. Yu, Semimetal with both Rarita-Schwinger-Weyl and Weyl excitations, *Phys. Rev. B* **93**, 045113 (2016).
 - [12] H. Isobe and L. Fu, Quantum critical points of $j = \frac{3}{2}$ Dirac electrons in antiperovskite topological crystalline insulators, *Phys. Rev. B* **93**, 241113 (2016).
 - [13] P. Tang, Q. Zhou, and S.-C. Zhang, Multiple types of topological fermions in transition metal silicides, *Phys. Rev. Lett.* **119**, 206402 (2017).
 - [14] J.-Z. Ma, Q.-S. Wu, M. Song, S.-N. Zhang, E. Guedes, S. Ekahana, M. Krivenkov, M. Yao, S.-Y. Gao, W.-H. Fan, *et al.*, Observation of a singular Weyl point surrounded by charged nodal walls in PtGa, *Nature Communications* **12**, 3994 (2021).
 - [15] Y. Shen, Y. Jin, Y. Ge, M. Chen, and Z. Zhu, Chiral topological metals with multiple types of quasiparticle fermions and large spin Hall effect in the SrGePt family materials, *Phys. Rev. B* **108**, 035428 (2023).
 - [16] R. Ghosh, F. Haidar, and I. Mandal, Linear response in planar Hall and thermal Hall setups for Rarita-Schwinger-Weyl semimetals, *Phys. Rev. B* **110**, 245113 (2024).
 - [17] I. Mandal, S. Saha, and R. Ghosh, Signatures of topology in generic transport measurements for Rarita-Schwinger-Weyl semimetals, *Solid State Communications* **397**, 115799 (2025).
 - [18] I. Mandal, Distinguishing features of longitudinal magnetoconductivity for a Rarita-Schwinger-Weyl node, *Journal of Low Temperature Physics* **222**, 120 (2026).
 - [19] Z.-Y. Zhuang, C. Zhang, X.-J. Wang, and Z. Yan, Berry-dipole semimetals, *Phys. Rev. B* **110**, L121122 (2024).
 - [20] A. Graf and F. Piéchon, Massless multifold Hopf semimetals, *Phys. Rev. B* **108**, 115105 (2023).
 - [21] T. Habe, Optical conductivity of the threefold Hopf semimetal, *Phys. Rev. B* **106**, 205204 (2022).
 - [22] S. Ahn, Magneto-optical conductivity of threefold Hopf semimetals, *Journal of the Korean Physical Society* **84**, 59 (2024).
 - [23] A. Knoll, C. Timm, and T. Meng, Negative longitudinal magnetoconductance at weak fields in Weyl semimetals, *Phys. Rev. B* **101**, 201402 (2020).
 - [24] R. Ghosh and I. Mandal, Electric and thermoelectric response for Weyl and multi-Weyl semimetals in planar Hall configurations including the effects of strain, *Physica E: Low-dimensional Systems and Nanostructures* **159**, 115914 (2024).
 - [25] R. Ghosh and I. Mandal, Direction-dependent conductivity in planar Hall set-ups with tilted Weyl/multi-Weyl semimetals, *Journal of Physics: Condensed Matter* **36**, 275501 (2024).
 - [26] L. Medel, R. Ghosh, A. Martín-Ruiz, and I. Mandal, Electric, thermal, and thermoelectric magnetoconductivity for Weyl/multi-Weyl semimetals in planar Hall set-ups induced by the combined effects of topology and strain, *Sci. Rep.* **14**, 21390 (2024).
 - [27] I. Mandal, Anisotropic conductivity for the type-I and type-II phases of Weyl/multi-Weyl semimetals in planar Hall set-ups, *Annals of Physics* **482**, 170181 (2025).
 - [28] I. Mandal, Effects of time-periodic drive in the linear response for planar-Hall set-ups with Weyl and multi-Weyl semimetals, *Canadian Journal of Physics* **103**, 1147 (2025).

- [29] F. D. M. Haldane, Berry curvature on the Fermi surface: Anomalous Hall effect as a topological Fermi-liquid property, *Phys. Rev. Lett.* **93**, 206602 (2004).
- [30] P. Goswami and S. Tewari, Axionic field theory of $(3 + 1)$ -dimensional Weyl semimetals, *Phys. Rev. B* **88**, 245107 (2013).
- [31] A. A. Burkov, Anomalous Hall effect in Weyl metals, *Phys. Rev. Lett.* **113**, 187202 (2014).
- [32] S.-B. Zhang, H.-Z. Lu, and S.-Q. Shen, Linear magnetoconductivity in an intrinsic topological Weyl semimetal, *New Journal of Phys.* **18**, 053039 (2016).
- [33] Q. Chen and G. A. Fiete, Thermoelectric transport in double-Weyl semimetals, *Phys. Rev. B* **93**, 155125 (2016).
- [34] S. Nandy, G. Sharma, A. Taraphder, and S. Tewari, Chiral anomaly as the origin of the planar Hall effect in Weyl semimetals, *Phys. Rev. Lett.* **119**, 176804 (2017).
- [35] S. Nandy, A. Taraphder, and S. Tewari, Berry phase theory of planar Hall effect in topological insulators, *Sci. Rep.* **8**, 14983 (2018).
- [36] K. Das and A. Agarwal, Linear magnetochiral transport in tilted type-I and type-II Weyl semimetals, *Phys. Rev. B* **99**, 085405 (2019).
- [37] O. Pal, B. Dey, and T. K. Ghosh, Berry curvature induced magnetotransport in 3D noncentrosymmetric metals, *Journal of Phys.: Condensed Matter* **34**, 025702 (2022).
- [38] L. X. Fu and C. M. Wang, Thermoelectric transport of multi-Weyl semimetals in the quantum limit, *Phys. Rev. B* **105**, 035201 (2022).
- [39] M. Stålhammar, J. Larana-Aragon, J. Knolle, and E. J. Bergholtz, Magneto-optical conductivity in generic Weyl semimetals, *Phys. Rev. B* **102**, 235134 (2020).
- [40] S. Yadav, S. Sekh, and I. Mandal, Magneto-optical conductivity in the type-I and type-II phases of Weyl/multi-Weyl semimetals, *Physica B: Condensed Matter* **656**, 414765 (2023).
- [41] I. Mandal, Chiral anomaly and internode scatterings in multifold semimetals, *Phys. Rev. B* **111**, 165116 (2025).
- [42] F. Haidar and I. Mandal, Reflections of topological properties in the planar-Hall response for semimetals carrying pseudospin-1 quantum numbers, *Annals of Physics* **478**, 170010 (2025).
- [43] I. Mandal, Longitudinal magnetoelectricity in multifold semimetals exemplified by pseudospin-1 nodal points, *Eur. Phys. J. Plus* **141**, 75 (2026).
- [44] Direction-dependent linear response for gapped nodal-line semimetals in planar-Hall configurations, *Eur. Phys. J. B* **99**, 41 (2026).
- [45] I. Mandal, Disentangling contributions to longitudinal magnetoelectricity for Kramers-Weyl nodes, *Sci. Rep.* **15**, 37542 (2025).
- [46] M. Papaj and L. Fu, Magnus Hall effect, *Phys. Rev. Lett.* **123**, 216802 (2019).
- [47] D. Mandal, K. Das, and A. Agarwal, Magnus Nernst and thermal Hall effect, *Phys. Rev. B* **102**, 205414 (2020).
- [48] S. Sekh and I. Mandal, Magnus Hall effect in three-dimensional topological semimetals, *Eur. Phys. J. Plus* **137**, 736 (2022).
- [49] S. Sekh and I. Mandal, Circular dichroism as a probe for topology in three-dimensional semimetals, *Phys. Rev. B* **105**, 235403 (2022).
- [50] I. Mandal, Signatures of two- and three-dimensional semimetals from circular dichroism, *International Journal of Modern Physics B* **38**, 2450216 (2024).
- [51] J. E. Moore, Optical properties of Weyl semimetals, *National Science Rev.* **6**, 206 (2018).
- [52] C. Guo, V. S. Asadchy, B. Zhao, and S. Fan, Light control with Weyl semimetals, *eLight* **3**, 2 (2023).
- [53] A. Avdoshkin, V. Kozii, and J. E. Moore, Interactions remove the quantization of the chiral photocurrent at Weyl points, *Phys. Rev. Lett.* **124**, 196603 (2020).
- [54] I. Mandal, Effect of interactions on the quantization of the chiral photocurrent for double-Weyl semimetals, *Symmetry* **12** (2020).
- [55] S.-Y. Xu, I. Belopolski, N. Alidoust, M. Neupane, G. Bian, C. Zhang, R. Sankar, G. Chang, Z. Yuan, C.-C. Lee, S.-M. Huang, H. Zheng, J. Ma, D. S. Sanchez, B. Wang, A. Bansil, F. Chou, P. P. Shibayev, H. Lin, S. Jia, and M. Z. Hasan, Discovery of a Weyl fermion semimetal and topological Fermi arcs, *Science* **349**, 613 (2015).
- [56] B. Q. Lv, H. M. Weng, B. B. Fu, X. P. Wang, H. Miao, J. Ma, P. Richard, X. C. Huang, L. X. Zhao, G. F. Chen, Z. Fang, X. Dai, T. Qian, and H. Ding, Experimental discovery of Weyl semimetal TaAs, *Phys. Rev. X* **5**, 031013 (2015).
- [57] D. S. Sanchez, I. Belopolski, T. A. Cochran, X. Xu, J.-X. Yin, G. Chang, W. Xie, K. Manna, V. Süß, C.-Y. Huang, N. Alidoust, D. Multer, S. S. Zhang, N. Shumiya, X. Wang, G.-Q. Wang, T.-R. Chang, C. Felser, S.-Y. Xu, S. Jia, H. Lin, and M. Zahid Hasan, Topological chiral crystals with helicoid-arc quantum states, *Nature* **567**, 500–505 (2019).
- [58] D. Takane, Z. Wang, S. Souma, K. Nakayama, T. Nakamura, H. Oinuma, Y. Nakata, H. Iwasawa, C. Cacho, T. Kim, K. Horiba, H. Kumigashira, T. Takahashi, Y. Ando, and T. Sato, Observation of chiral fermions with a large topological charge and associated Fermi-arc surface states in CoSi, *Phys. Rev. Lett.* **122**, 076402 (2019).
- [59] N. B. M. Schröter, S. Stolz, K. Manna, F. de Juan, M. G. Vergniory, J. A. Krieger, D. Pei, T. Schmitt, P. Dudin, T. K. Kim, C. Cacho, B. Bradlyn, H. Bormann, M. Schmidt, R. Widmer, V. N. Strocov, and C. Felser, Observation and control of maximal Chern numbers in a chiral topological semimetal, *Science* **369**, 179 (2020).
- [60] M. Yao, K. Manna, Q. Yang, A. Fedorov, V. Voroshnin, B. Valentin Schwarze, J. Hornung, S. Chattopadhyay, Z. Sun, S. N. Guin, J. Wosnitza, H. Bormann, C. Shekhar, N. Kumar, J. Fink, Y. Sun, and C. Felser, Observation of giant spin-split Fermi-arc with maximal Chern number in the chiral topological semimetal PtGa, *Nature Communications* **11**, 2033 (2020).
- [61] G. Chang, S.-Y. Xu, B. J. Wieder, D. S. Sanchez, S.-M. Huang, I. Belopolski, T.-R. Chang, S. Zhang, A. Bansil, H. Lin, and M. Z. Hasan, Unconventional chiral fermions and large topological Fermi arcs in RhSi, *Phys. Rev. Lett.* **119**, 206401 (2017).
- [62] X. Xiao, Y. Jin, D.-S. Ma, W. Kong, J. Fan, R. Wang, and X. Wu, Realization of charge-four Weyl point in fermionic systems, *Phys. Rev. B* **108**, 075130 (2023).
- [63] E. Witten, Three lectures on topological phases of matter, *Riv. Nuovo Cim.* **39**, 313 (2016).
- [64] K. Hashimoto, T. Kimura, and X. Wu, Boundary conditions of Weyl semimetals, *Progress of Theoretical and Experimental Physics* **2017**, 053I01 (2017), [Erratum: PTEP 2019, 029201 (2019)].

- [65] B. Seradjeh and M. Vennettilli, Surface spectra of Weyl semimetals through self-adjoint extensions, *Phys. Rev. B* **97**, 075132 (2018).
- [66] D. Wawrzik, J.-S. You, J. I. Facio, J. van den Brink, and I. Sodemann, Infinite Berry curvature of Weyl Fermi arcs, *Phys. Rev. Lett.* **127**, 056601 (2021).
- [67] R. Okugawa and S. Murakami, Dispersion of Fermi arcs in Weyl semimetals and their evolutions to Dirac cones, *Phys. Rev. B* **89**, 235315 (2014).
- [68] Y. Liu, J. Lin, V. Wang, and J. Nara, Fermi arcs of topological surface states and Lifshitz transitions in multi-Weyl semimetals, *Phys. Scripta* **100**, 025939 (2025).
- [69] Z. Faraei, T. Farajollahpour, and S. A. Jafari, Green's function of semi-infinite Weyl semimetals, *Phys. Rev. B* **98**, 195402 (2018).
- [70] S. Juergens and B. Trauzettel, Exotic surface states in hybrid structures of topological insulators and Weyl semimetals, *Phys. Rev. B* **95**, 085313 (2017).
- [71] M. Kharitonov, J.-B. Mayer, and E. M. Hankiewicz, Universality and stability of the edge states of chiral-symmetric topological semimetals and surface states of the Luttinger semimetal, *Phys. Rev. Lett.* **119**, 266402 (2017).
- [72] G. E. Volovik, *The Universe in a Helium Droplet*, International Series of Monographs on Physics, Vol. 117 (Oxford University Press, Oxford, UK, 2003).
- [73] I. Mandal, Unconventional magnetoelectric conductivity and electrochemical response from dipole-like sources of Berry curvature, *arXiv e-prints* (2026), [arXiv:2602.08844](https://arxiv.org/abs/2602.08844) [[cond-mat.mes-hall](https://arxiv.org/archive/cond-mat)].
- [74] Z. Zhu, G. W. Winkler, Q. Wu, J. Li, and A. A. Soluyanov, Triple point topological metals, *Phys. Rev. X* **6**, 031003 (2016).
- [75] Y.-Q. Zhu, D.-W. Zhang, H. Yan, D.-Y. Xing, and S.-L. Zhu, Emergent pseudospin-1 Maxwell fermions with a threefold degeneracy in optical lattices, *Phys. Rev. A* **96**, 033634 (2017).
- [76] H. Weng, C. Fang, Z. Fang, and X. Dai, Topological semimetals with triply degenerate nodal points in θ -phase tantalum nitride, *Phys. Rev. B* **93**, 241202 (2016).
- [77] P. Tang, Q. Zhou, and S.-C. Zhang, Multiple types of topological fermions in transition metal silicides, *Phys. Rev. Lett.* **119**, 206402 (2017).
- [78] H. Weng, C. Fang, Z. Fang, and X. Dai, Coexistence of Weyl fermion and massless triply degenerate nodal points, *Phys. Rev. B* **94**, 165201 (2016).
- [79] A. Y. Prykhodko, E. V. Gorbar, and P. O. Sukhachov, Surface states and finite size effects in triple-fold semimetals, *Journal of Physics: Condensed Matter* **37**, 405002 (2025).
- [80] G. Xu, H. Weng, Z. Wang, X. Dai, and Z. Fang, Chern semimetal and the quantized anomalous Hall effect in HgCr_2Se_4 , *Phys. Rev. Lett.* **107**, 186806 (2011).
- [81] S.-M. Huang, S.-Y. Xu, I. Belopolski, C.-C. Lee, G. Chang, T.-R. Chang, B. Wang, N. Alidoust, G. Bian, M. Neupane, D. Sanchez, H. Zheng, H.-T. Jeng, A. Bansil, T. Neupert, H. Lin, and M. Z. Hasan, New type of Weyl semimetal with quadratic double weyl fermions, *Proceedings of the National Academy of Sciences* **113**, 1180 (2016).
- [82] B. Singh, G. Chang, T.-R. Chang, S.-M. Huang, C. Su, M.-C. Lin, H. Lin, and A. Bansil, Tunable double-Weyl fermion semimetal state in the SrSi_2 materials class, *Sci. Rep.* **8**, 10540 (2018).
- [83] Q. Liu and A. Zunger, Predicted realization of cubic Dirac fermion in quasi-one-dimensional transition-metal monochalcogenides, *Phys. Rev. X* **7**, 021019 (2017).
- [84] T. Zhang, R. Takahashi, C. Fang, and S. Murakami, Twofold quadruple Weyl nodes in chiral cubic crystals, *Phys. Rev. B* **102**, 125148 (2020).
- [85] C. Cui, X.-P. Li, D.-S. Ma, Z.-M. Yu, and Y. Yao, Charge-four Weyl point: Minimum lattice model and chirality-dependent properties, *Phys. Rev. B* **104**, 075115 (2021).
- [86] L. Luo, W. Deng, Y. Yang, M. Yan, J. Lu, X. Huang, and Z. Liu, Observation of quadruple Weyl point in hybrid-Weyl phononic crystals, *Phys. Rev. B* **106**, 134108 (2022).
- [87] A. Raj, S. Chaudhary, and G. A. Fiete, Photogalvanic response in multi-Weyl semimetals, *Phys. Rev. Res.* **6**, 013048 (2024).
- [88] D. Takane, Z. Wang, S. Souma, K. Nakayama, T. Nakamura, H. Oinuma, Y. Nakata, H. Iwasawa, C. Cacho, T. Kim, K. Horiba, H. Kumigashira, T. Takahashi, Y. Ando, and T. Sato, Observation of chiral fermions with a large topological charge and associated fermi-arc surface states in cosi , *Phys. Rev. Lett.* **122**, 076402 (2019).
- [89] M. Yao, K. Manna, Q. Yang, A. Fedorov, V. Voroshnin, B. Valentin Schwarze, J. Hornung, S. Chattopadhyay, Z. Sun, S. N. Guin, J. Wosnitza, H. Borrmann, C. Shekhar, N. Kumar, J. Fink, Y. Sun, and C. Felser, Observation of giant spin-split Fermi-arc with maximal Chern number in the chiral topological semimetal PtGa , *Nature Communications* **11**, 2033 (2020).
- [90] A. C. Potter, I. Kimchi, and A. Vishwanath, Quantum oscillations from surface Fermi arcs in Weyl and Dirac semimetals, *Nature Communications* **5**, 5161 (2014).
- [91] Y. Zhang, D. Bulmash, P. Hosur, A. C. Potter, and A. Vishwanath, Quantum oscillations from generic surface Fermi arcs and bulk chiral modes in Weyl semimetals, *Sci. Rep.* **6**, 23741 (2016).