



UNIVERSITY OF TRENTO - Italy

Master of Science in Materials and Production Engineering

Melt flow index (MFI), Shore hardness, Vicat/HDT and LOI analysis

Laboratory activity report
Course of Polymeric Materials Engineering

Giacomo Mori 207674
Veronica Pallua 206956
Lorenzo Penna 208221
Gabriel Orsi 207696
Laura Simonini 207317
Alessandro Sorze 207017
Federico Vespa 206913

Trento (Italy), jun 2019

Academic year 2018-19

Abstract

Lorem ipsum dolor sit amet, consectetur adipiscing elit. Vivamus at est non arcu dapibus eleifend. In facilisis, erat ullamcorper condimentum venenatis, magna mi consequat enim, ac faucibus velit libero ut sapien. Nam fringilla elit at magna imperdiet dapibus. Vestibulum malesuada fringilla placerat. Suspendisse potenti. Nam ac vehicula nibh, eget suscipit purus. Curabitur tempus erat id pulvinar consectetur. Etiam quis diam magna. Etiam feugiat vulputate consequat. Nulla libero ligula, tempor quis mollis in, placerat vitae nisi. Proin ornare ut eros ac rhoncus. Integer et metus non mi pharetra sagittis. Praesent dignissim erat vel magna efficitur, sed efficitur mi viverra. Interdum et malesuada fames ac ante ipsum primis in faucibus. Vivamus non ipsum non purus feugiat interdum non vel odio.

1 Introduction

2 Experimental activity

2.1 Compression molding

Prepared amount of polypropylene mixture has been used for compression molding process. A press by Carver has been used, as illustrated in Figure ??.



Figure 1: Carver press for compression molding.

The material to be pressed is put between two stainless steel plates, one having a frame of $12 \times 12 \text{ mm}^2$ in order to produce a square plate of some mm of thickness. To avoid any adhesion with the plates, that are used to evenly distribute the pressure and to confine the melt (since the press is able to provide heat), two Mylar[®] foils have been put in between the steel and the material. The press has been set to produce a pressure of 8 tons, equivalent to 5.45 MPa, in the frame. The material has undergone an heat treatment under this pressure of 200°C for 10 minutes. After this, the press has been cooled with water circulating in a refrigerating circuit inside of it and the molded piece extracted. Produced plate is then visually analyzed and weighted in order to estimate weight losses.

2.1.1 Production of dumbbell specimens

After the analysis of the plate, this has been cut to obtain ISO 527-1BA shaped specimens, that are used in another laboratory activity.