

NİĞTAŞ 40

PRODUCTION SITE	Niade / TURKEY
THODOCHON SHE	MIGGE / TOTAL I

Certified ISO 22000-2005, ISO 22716-2007 OHSAS 1801-2007, ISO 10002-2014, ISO 1401-2015, ISO 9001-2015

PRODUCT SPECIFICATION

Micronized natural calcium carbonate at high purity and whiteness is originated from

natural sources.

	CHE	MICAL	ANAL	_YSIS
--	-----	-------	------	-------

CaCO ₃	$99,35 \pm 0,2$	(%)
MgO	0.3 ± 0.1	(%)
SiO ₂	< 0,1	(%)
Fe_2O_3	0.04 ± 0.01	(%)
HCI Insoluble	< 0,1	(%)

TECHNICAL DATA

Whiteness (L) (ASTM E-313) Elrepho 450x	> 98,00	(%)
Brightness (Ry C/2) (DIN 6174) Elrepho 450x	> 95,50	(%)
Moisture, Factory Depart (ISO 787-2)	< 0,3	(%)
pH value (ISO 787-9)	$8,5 \pm 1,0$	
Hardness by (Moh's)	3	Mohs
Dop Absorbtion (ISO 787-5)	27	gr/100gr
Oil Absorbtion (ISO 787-5)	14	gr/100gr
Refractive Index	1,57	
Tap Density	1,15	gr/ml


APPLICATIONS

Exterior Emulsion Paints

Road Line Paints

- **PVC Shoe Soles**
- Vehicle Tires
- Caoutchouc Car Mats
- Sponges
- Asphalt Productions
- Plasters
- Faux Leathers

Malvern Mastersizer 2000 Particle Size Distribution



PARTICLE SIZE DISTRIBUTION

Parameters	Mastersizer 2000	Value
Mean Grain Size , D50	$9,00 \pm 0,80$	(µ)
Top – Cut, D97	$32,00 \pm 3,0$	(µ)
Volume % of particles below 2µ	$21,00 \pm 2,0$	(%)
Specific Surface Area	$1,90 \pm 0,20$	(m ² /cm ³)
Sieve Residue on 90µ (ISO 787-7)	< 0,1	(%)

PACKING

25 kg kraft / PP sack+1.250/1.000 kg big bag Or bulk in 1.250/1.000 kg big bag (palletized)

These information are related to specific material defined above that they are based on technical measuring data that Nigtas belives to be reliable. Responsibility of appreciate and determine the suitability of this product before any use belongs to customer or corporation.