gr/100gr



## NİĞTAŞ 75K

PRODUCTION SITE Nigde / TURKEY

Certified ISO 22000-2005, ISO 22716-2007 OHSAS 1801-2007, ISO 10002-2014, ISO 1401-2015, ISO 9001-2015

PRODUCT SPECIFICATION Ultra-fine coated natural calcium carbonate at high purity and whiteness is originated

from natural sources.

CHEMICAL ANALYSIS  $CaCO_3$  99,35  $\pm$  0,2 (%)

MgO  $0.3 \pm 0.1$  (%) SiO<sub>2</sub> < 0.1 (%)

Fe<sub>2</sub>O<sub>3</sub> 0,04  $\pm$  0,01 (%) HCI Insoluble < 0,1 (%)

TECHNICAL DATA Whiteness (L) (ASTM E-313) Elrepho 450x > 98,50 (%)

Brightness (Ry C/2) (DIN 6174) Elrepho 450x > 96,50 (%)

Moisture, Factory Depart (ISO 787-2) < 0.3 (%) pH value (ISO 787-9)  $8.5 \pm 1.0$ 

Hardness by (Moh's) 3 Mohs
Dop Absorbtion (ISO 787-5) 21 gr/100gr

Oil Absorbtion (ISO 787-5) 17
Refractive Index 1,57

Tap Density 0,85 gr/ml


## **APPLICATIONS**

- Marine Paints

- Printing İnks

- PVC Profiles
- PVC Floor Covering-Tarpaulin
- Polyolefins (Stretch Films, Nylons etc.)
- Masterbatches
- Elastomers

Malvern Mastersizer 2000 Particle Size Distribution



ADTICI	E CIZE	DISTRIBI	INOITI

Parameters	Mastersizer 2000	value
Mean Grain Size , D50	$1,95 \pm 0,15$	(µ)
Top – Cut, D97	$5,30 \pm 0,30$	(µ)
Volume % of particles below 2µ	$56,00 \pm 5,0$	(%)
Specific Surface Area	$3,90 \pm 0,40$	(m <sup>2</sup> /cm <sup>3</sup> )
Sieve Residue on 45µ (ISO 787-7)	< 0,01	(%)

PACKING

25 kg kraft / PP sack+1.250/1.000 kg big bag Or bulk in 1.250/1.000 kg big bag (palletized)

These information are related to specific material defined above that they are based on technical measuring data that Nigtas belives to be reliable. Responsibility of appreciate and determine the suitability of this product before any use belongs to customer or corporation.