



Plywood Sheet 18mm

WISA®-Form

WISA-Form Slab is a coated special plywood for use in loose panel concrete formwork.

Base board

Spruce plywood made solely from spruce (softwood) veneers bonded together in a cross banded construction.

Bonding

Phenolic resin cross-banded weather resistant glueing according to EN 314-2/class 3 exterior, EN636-3.

Surface

WISA-Form Slab coating weight is 400gm/m² both sides.

Face and reverse: Brown phenolic film combination (abt. RAL 8017).

Edge sealing: Water resistant paint.

Imprinted text: "WISA®-Form Slab".

Thicknesses and weight

Nominal thickness (mm)	Min. thickness (mm)	Max. thickness (mm)	Weight (kg/m ²)
15	14.3	15.3	7.6
18	17.1	18.1	9.0
21	20.0	20.9	10.2

Panel size

2400/2440/2500 x 1200/1220/1250 mm

Size limits

Size tolerances:	< 1000 mm	± 1 mm
	1000-2000 mm	± 2 mm
	> 2000 mm	± 3 mm

Plywood (23/32 in) -18mm technical Data:

Mechanical properties of plywood



Product	Nominal thickness (mm)	Mean modulus of elasticity Bending (N/mm ²)		Characteristic strength Bending (N/mm ²)	
		Em	Em _⊥	fm	fm _⊥
WISA-Form Pro	18 (13-ply)	10048	7452	40.2	34.1
WISA-Form Birch	18 (13-ply)	10048	7452	40.2	34.1
WISA-Form Beto	18 (11-ply)	8767	5988	35.1	17.1
WISA-Form Slab	18 (7-ply)	8170	3830	20.4	13.0

Head Office

Factory: Wady Houf, Helwan

Tel: (+202) 23254532 / 23254519

(+20223254534

Fax: (+202) 23671 347

E-mail: sales@acrow.co





Plywood Sheet 18mm

- Mechanical Properties of Plywood (Design Stress) That are Given in the report are in Basic Condition with Moisture Content $10 \pm 2 \%$.
- Given Properties of Plywood not be adjusted using Concrete Setting Factor C_s

For 1m wide

- $A = 100 \times (1.8) = 180 \text{ cm}^2$
- $I = 100 \times (1.8)^3 / 12 = 48.60 \text{ cm}^4$
- $Z = 100 \times (1.8)^2 / 6 = 54.00 \text{ cm}^3$
- Max allowable deflection in sheeting = $L/300 \text{ mm}$
- Allowable bending stress in plywood (F_{all}) = 341 Kg/cm^2
- (E) For Plywood = 74.52 t/cm^2



Head Office

Factory: Wady Houf, Helwan

Tel: (+202) 23254532 / 23254519
(+20223254534)

Fax: (+202) 23671 347

E-mail: sales@acrow.co

