

Banner

LABORATORY TEST REPORT

TEST RESULTS

Test	Method	Unit	Limit	Result
Flash Point	ASTM D 92	°C	Min 250	334
Ductility @ 25 °C	ASTM D 113	cm	Min 100	>100
Penetration @ 25 °C (100 gm) 5 sec	ASTM D 5	0.1mm	60-70	65
Softening Point	ASTM D 36	°C	49-56	49.2
Specific Gravity @ 60/60°F	ASTM D 70	-	-	1.0226
Density @ 15 °C	ASTM D 70	Kg/L	-	1.0217
Solubility in Trichloroethylene	ASTM D 2042	% Wt	Min 99	99.9
Loss on Heating	ASTM D 1754	% Wt	Max 0.2	0.013
Retained Penetration as % of Original	ASTM D 5	%	Min 54	93
Kinematic Viscosity @ 135°C	ASTM D 2170	cSt	Min 232	407.6
Ductility of Residue @ 25 °C	ASTM D 113	cm	Min 100	>100

Test method deviation : None
Test conducted by Emp. # : 004
Report prepared by Emp. # : 006

The above test results are only applicable to the sample(s) referred above

Reported By

LABORATORY OPERATIONS

The test Report shall not be reproduced (except in full) without the written approval of Spectrum
When analysis is witnessed by us or carried out by sub contract labs, our responsibility is solely
To ensure that the analysis is conducted to standard test methods in accordance with industry
Accepted practice. We are not responsible for apparatus, instrumentation and measuring devices, their
Calibration or working order, Reagents and solutions are accepted as prepared.

SPIT/QA-001A Rev.0