



#### **SERFILL**

## **ESPECIFICACIÓN TÉCNICA**

## DESCRIPCIÓN

Materia prima compuesta básicamente de arena de olivina, con una adecuada distribución granulométrica y una alta resistencia a la temperatura de operación, que evita el sinterizado y permite mejorar su fluidez en el hueco de colada - EBT.

#### APLICACIÓN

Se utiliza como material de relleno en los huecos de colada de vaciado por el fondo (EBT) de los hornos de arco eléctrico.

#### **VENTAJAS**

- Alto % de apertura.
- Baja conductividad térmica.
- · Alta refractariedad.
- Bajo consumo específico (Kg/Tal).
- Libre de cuarzo y feldespato.
- Excelente relación precio-Eficacia.

ANÁLISIS
QUÍMICO
(%)

MgO	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	Otros		
45-50	38-42	10 Max	2 Max		

# ANÁLISIS MINERALÓGICO (%)

Mg,SO,		
<u> </u>		
>90		

Forma de

## PROPIEDADES **FÍSICAS**

Color	Gris	Particula	Angulosa
Temperatura de fusión (°C)	>1700	Humedad (%)	0,5 Max
Dureza (Mohs)	6,5-7	рН	>9
Densidad (gr/cc)	2,9-3,3	LOI (%)	0,7 - 1,5

## **GRANULOMETRÍA**

> 6mm: 0%

> 2 mm y < 6 mm: 95% Min > 6 mm y < 2 mm: 5% Max

#### **EMBALAJE**

En big bag de 1,25 TM

### TIEMPO DE ALMACENAMIENTO

Seis (6) meses, en lugar seco y bajo techo.

Observaciones: Los resultados técnicos no deben tomarse como máximo y mínimo para propósitos de especificaciones.



Dirección:

1830 Nw 7<sup>th</sup> ST # 205 Miami FL 33125

Telfs. Móvil:

+51 971447001 / +51 971448055

Teléfonos de Oficina:

+58 2869941547 +58 2869940635

+51 44 702121

Correos:

director@igminingcorp.com sales@igminingcorp.com comercializacion@igminingcorp.com











#### **SERFILL**

## **TECHNICAL SPECIFICATION**

## DESCRIPTION

Raw material basically composed of olivine sand, with an adequate size distribution and a high resistance to operation temperature that avoid the sintered and allows to improve the flow in the tap hole – EBT.

#### **APPLICATION**

It is used as a filler material in the eccentric bottom tap-hole (EBT) of electric arcfurnaces.

### **ADVANTAGES**

- High % of opening.
- Low thermal conductivity.
- · High refractoriness.
- Low specific consumption (Kg/Tal).
- Quartz and feldspar free.
- High Effectiveness-price relation.

CHEMICAL
ANALYSIS
(%)

MgO	SiO <sub>2</sub>	Fe <sub>2</sub> O <sub>3</sub>	Others		
45-50	38-42	10 Max	2 Max		

#### MINERALOGICAL ANALYSIS (%)

Mg <sub>2</sub> SO <sub>4</sub>		
>90		

## PHYSICAL PROPERTIES

Color	Grey	Particle Form	Angular
Melting Point (°C)	>1700	Moisture (%)	0,5 Max
Hardness (Mohs)	6,5-7	рН	>9
Density (gr/cc)	2,9-3,3	LOI (%)	0,7 - 1,5

## SIZE DISTRIBUTION

- > 6mm: 0%
- > 2 mm y < 6 mm: 95% Min > 6 mm y < 2 mm: 5% Max

#### PACKAGE

1,25 MT big bags.

### STORAGE TIME

Six (6) months, on a dry and roofed place.

 $Observations: Technical \ results \ should \ not \ be \ considered \ as \ maximum \ or \ minimum \ for \ specifications \ purposes.$ 



Addresss:

1830 Nw 7<sup>th</sup> ST # 205 Miami FL 33125

Mobile Phone Numbers: +51 971447001 / +51 971448055

Office Phone

+58 2869941547 +58 2869940635 +51 44 702121

Emails:

director@igminingcorp.com sales@igminingcorp.com comercializacion@igminingcorp.com





