Title	**Standard Washing Instructions**
Owner	Quality Development
Effective Date	November 4, 2019
Last Revised	November 4, 2019
Document Number	GQ-QD-SOP-OV-V2-Standard Washing Instructions

TYPE	CUT & SEW	BONDED	EMBELLISHMENT / SPECIAL APPLICATION
APPLICATION	X	NEXT TO SKIN DRY: 5OX WASH + 1OX 40°C / Tumble Dry Low SECOND LAYERING: 5OX WASH + 1OX 40°C / Tumble Dry Low OUTERWEAR: 25X Wash 5X Tumble Dry Low	10X WASH +10X DRY 40°C / Tumble Dry Low Re: pleating, laser cutting and perforation – 25x WASH +25X 40°C / Tumble Dry Low
FINISHED PRODUCT	Garment wash: -> 2ND PROTO -> 5X WASH + 5X DRY	Garment wash -> @ SECOND PROTO Wash Care Instructions	Garment wash @ 2ND PROTO +ABRASION PRINTS + ARTWORK ONLY

Note: Above number of washes are minimum standard requirement and quality team (QD) may request additional number of washes based on risks identified during commercialization process

TIMELINE	WHEN	CYCLES / TEMP	WHO
RM TEST (BONDING)	PRE SEASON	1OX WASH + 50°C /2X Tumble Dry Low	RM Developer (Owner) ADHESIVE SUPPLIER (Testing Facility)
APPLICATION (BONDING)	AFTER TPHO	5OX WASH + 40°C /1OX Tumble Dry Low	SSC-QD Technician (Owner) ADHESIVE SUPPLIER (Testing Facility)
COMPATIBILITY BONDING	AFTER TPHO	5OX WASH + 40°C /1OX Tumble Dry Low	FACTORY (Owner + Testing Facility)
Garment Wash (ALL)	2ND PROTO	5X WASH + 5X DRY /Wash Care	FACTORY (Approved/Accredited Lab Facilities ONLY)
BULK (ALL)	Before HOD	5X WASH + 5X DRY /Wash Care	BV

LULULEMON TEST REQUIREMENTS FOR BONDED APPLICATION/ LAB TESTING - Apparel level				
Type of testing	**Category**	**Wash Temp (oC)**	**# of washes**	**# of dries (Low)**
Application	Next to Skin Applications	40c	50x	10x
Application	Jackets	40c	50x	10x
Application	Outerwear	40c	25x	5x
Application	OT/decorative	40c	50x	10x
Preliminary (RM)	All	50c	10x	2x

LULULEMON TEST REQUIREMENTS FOR BONDED APPLICATION/ LAB TESTING - Accessories level				
Type of testing	**Category**	**Wash Temp (oC)**	**# of washes**	**# of dries (Low)**
Application	Next to Skin Applications (gloves.etc) and water proof accessories, where applicable	40c	50x	10x
Application	OT/decorative	40c	25x	5x
Application	non-water proof acc., (with care instruction for hand wash cold), i.e. bags, hats etc.	40c	10x	2x
Preliminary (RM)	All	50c	10x	2x

REV	Document Editor	Date Initiated	Change Order	Reason	Description
0.0	Brittany Mardon	November 4, 2019	Whole Document	Outdated	Updated format, removed from Section 2 of QA Manual
0.0	Miraj Uddin	November 4, 2019	Whole document	N/A	Added bonded application tables