

RWB APPLICATION GUIDE

| | 270 | | | | | | | | | | | | | | | | | | | | | |
|--------------------------------------------|------------------|--------------------|--------------|-----------------|--------------------|---------------------|------------------|----------------|-----------------|-------------------|-----------------|--------------|------------------|-------------------|----------------------|-------------------|-------------------|-------------------|---------------------------|-----------------------|-----------------------|----------------|
| FAMILY OF PRODUC | TS | Mix | | | Ω | Z | | | | | | | | ט | | ¥ | | | \dmix | 3AA | OTR | |
| • Concrete Repair • Self-Leveling • Grouts | RWB Patcher 1776 | 321 Old School Mix | RWB Smoother | RWB Strongcrete | RWB Strongcrete FD | RWB Strongcrete LST | RWB Rapid Anchor | RWB Flowtopper | RWB Flowsmooth | RWB Struccrete Cl | RWB Swiftset | RWB Repairer | RWB Repairer F-1 | RWB Repairer VOR, | RWB Seal Coat | RWB Freedom Grout | RWB Liberty Grout | RWB Patriot Grout | RWB Bonding Agent & Admix | RWB Acrylic Latex BAA | RWB Bonding Agent OTR | RWB Rapid Plug |
| FEATURES O | RWE | RWB | RWE | RWE | RWE | RWE | RWE | RWE | RWE | RWE | RWE | RWE | RWE | RWE | RWE | RWE | RWE | RWE | RWB | RWE | RWE | RWE |
| Aggegate Extendable for Deep Repair | • | | | • | | • | | • | • | | | • | • | | | | • | • | | | | |
| Yield, Ft³ Neat Extended | .43 .56 | .43 NA | .40 NA | .43 .56 | .50 NA | .43 .56 | .43 NA | .43 .56 | .43 .56 | .43 .56 | .43 NA | .43 .56 | .43 .56 | .43 NA | .43 NA | .43 .56 | .43 .56 | .43 .56 | NA NA | NA NA | NA NA | NA NA |
| Lifts | | | | | | | | • | • | | • | | • | • | | | | | | | | |
| Min Thickness F = Feather Edge | F | F | F | 1/2" | 1" | 1/2" | 1" | F | F | 1/2" | 1/8" | 1/2" | F | 1/8" | F | 1" | 1" | 1" | NA | NA | NA | NA |
| Max Thickness Neat Extended | <u>1"</u> 4" | <u>1/8"</u> NA | 1/2" NA | 3" 8" | NA 8" | 3" 8" | 8" NA | 1/2" 2" | <u>1"</u> 2" | 3" 8" | <u>2"</u> NA | 3" 8" | <u>1"</u> 4" | <u>2"</u> NA | 1 <u>/16</u> " NA | 3" 8" | 3" 8" | 3" 8" | NA NA | NA NA | NA NA | NA NA |
| Working Time | :60 | :90 | :50 | :30 | :12 | :45 | :10 | :20 | :30 | :25 | :24 | :20 | :30 | :20 | 3:00 | 3:00 | 1:45 | 2:30 | NA | NA | NA | NA |
| Final Set | 2:00 | 5:00 | 2:00 | :55 | :45 | 1:45 | :20 | 1:30 | 1:30 | 1:45 | :50 | 1:05 | 1:20 | :45 | 5:00 | 6:00 | 5:30 | 5:30 | NA | NA | NA | :05 |
| Temperatures | - | | | | | | | | | | | | MAXIN | ИUМ 90 | | | | | | | | • |
| Strengths (PSI) | 5,000 | 4,000 | 2,000 | 7,000 | 6,500 | 6,000 | 5,000 | 5,400 | 3,000 | 9,000 | 6,000 | 7,000 | 4,500 | 5,500 | 3,500 | 6,000 | 7,000 | 7,500 | NA | NA | NA | 5,500 |
| Structural | | | | | | | | | | | | | | | | | | | | | | |
| Cosmetic | • | | | | | | | • | | | • | | | | | | | | | | | |
| Walkways | | | | | | | | | | | | | | | | | | | | | | |
| Garages | • | | | | | | | | | | | | • | | | | | | | | | |
| Commercial Floor | | | | | | | | • | | | | | | | | | | | | | | |
| Industrial | • | | | | | • | | | | | | | | | | | | • | | | | • |
| Horizontal Repair | • | | | | | | | • | | | | | | | | | | | | | | |
| Traffic | • | | | • | • | • | | • | | • | | | | | | | | | | | | |
| Vertical/Overhead | | | | | | • | | | | | • | | | | • | | | | | | | |
| Form and Pour | | | | | | • | | | | • | | | | | | | | | | | | |
| Low Pressure Spray | | | | | | | | | | | | | | | | | | | • | • | | |
| Underlayment | | | | | | | | | | | | | | | | | | | | | | |
| Self-leveling | | | | | | | | • | • | | | | | | | | | | | | | |
| Cementitious | • | • | • | • | • | • | • | • | | | • | | | | • | • | | • | | | | • |
| 2-Component | • | | | | | | | | | | | | | | | | | | | | | |
| Non-Sag Trowelable | | | | | | | | | | | | | | | | | | | | | | |
| Self-Consolidation Pumpable | | | | | | | | | | | | | | | | | | • | | | | |
| Flowable | • | | | | | | | | | | | | • | | | | | | | | | |
| Coating Acceptability | | • | | | | | | | | | | | | | • | | | | | | | |
| Corrosion Inhibitor | | | | | | | | | | | | | | | | | | | | | | |
| Shrinking Compensation | | | | | | | | | | | | | | | | | | • | | | | |
| Polymer Modified | • | • | | | | | | • | | | | | • | | | | | | | | | |
| Light Color | • | | | | | | | • | • | | | | | | | | | | | | | |
| Smooth Texture | | | • | | | | | | | | | | | | | | | | | | | |
| Feather Edge Repairs | • | | | | | | | • | • | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | | | | | | | |

Exclusively manufactured for JANELL, INC. by US SPEC



CINCINNATI, OH 6130 Cornell Rd 45242 513-489-9111

DAYTON, OH 801 E 1st St 45402 937-866-9111 NORWOOD, OH 4686 Paddock Rd 45229 513-651-9111

COLUMBUS, OH 831 Harmon Ave 43223 614-224-9111

ERLANGER, KY 2930 Crescent Sprgs 41018 859-341-9111

LEXINGTON, KY 970 New Circle Rd 40511 859-254-9111

