

# Online Monitoring of Fibre Mat Winding

Janine Müller\*, Philipp Zander\*

## Abstract

For the upgrade of the LHCb detector a scintillating fibre tracker is foreseen. The 250  $\mu\text{m}$  fibres are arranged in multiple layer fibre mats and read out by silicon photomultipliers. This document describes an option of quality assurance during the production of fibre mats. A camera setup monitors the positioning of the fibres by looking tangential on the wheel. Defects in the fibre matrix will be detected by a pattern recognition software.

---

\*Technische Universität Dortmund

# 1 Introduction

The Scintillating Fibre Tracker is part of the LHCb Upgrade to be installed in the LS2 which starts in 2018 (see LHCb Tracker Upgrade Technical Design Report [1]). The Tracker consists of scintillating fibres with a diameter of  $250\text{ }\mu\text{m}$  and a length of 2.4 m. These fibres are stacked in six layers with a  $275\text{ }\mu\text{m}$  horizontal pitch. To detect the scintillation light multichannel silicon photomultipliers (SiPM) with a channel width of  $250\text{ }\mu\text{m}$  are used. Their height matches the height of the six layer fibre mat.

A fibre crossing particle generates a signal in more than one corresponding SiPM channel, so that the hit position is calculated from the charge barycentre. The fibres are mirrored at the middle of the 5 m high acceptance and read out by the SiPMs at the outer edges. The readout electronics are to be based on a custom designed ASIC which includes pre-amplifier, shaper, ADC, clusterization and zero suppression.

This document describes the production of the fibre mat with a focus on the quality assurance during the production.

## 2 Fibre Mat Production

The scintillating fibre mats are the active component of the SciFi Tracker and must be assembled very precisely and with high quality. Single scintillating fibres with a  $250\text{ }\mu\text{m}$  diameter are arranged to six layer fibre mats to receive a sufficient light yield at the photodetector. To produce these mats, the scintillating fibres are wound on a wheel with  $\approx 1\text{ m}$  diameter. A machine has been developed to produce these mats, controlling the speed, tension and winding of the fibre onto the wheel (see Fig. 1)

This wheel has a milled screw to guide the fibres of the first layer and guarantee the correct pitch. At the end of the layer, the fibre is cut for starting the next layer. The layers are shifted by half the horizontal pitch with respect to each other, so that the fibres of the next layer are guided by the fibres of the respective layer before. The fibre is provided by a spool of 12.5 km of scintillating fibre and is pre-guided by means of a small spool which moves along the width of the winding wheel to define the position of the fibre precisely. A loose spool in between defines the tension of the fibre and regulates the speed of the feeding spool.  $\text{TiO}_2$  loaded glue (two component epoxy) is placed between the layers. After curing the mat is cut perpendicular to the fibres and taken off the wheel to be flattened. For more detailed informations about the fibre mat production see also [2].

## 3 Quality Requirements

To ensure a spatial resolution better than  $100\text{ }\mu\text{m}$ , the fibres have to be accurately positioned. Due to many different influences problems occur during the winding process. The exclusive error is the wrong positioning of a fibre. This will manipulate the continuing fibre mat production, so that other fibres can't fit in their decided position. In the most situations




Figure 1: Prototype of a winding machine to produce scintillating fibre mats. The fibre is provided by a feeding spool (right) and moves over a loose spool to the winding wheel. The loose spool defines the tension of the fibre and regulates the speed of the feeding spool. A small spool is moving along the width of the winding wheel, for defining the correct position of the fibre.




Figure 2: Effect of a bump to the fibre matrix. A bump at  $x = 93$  mm (ca.  $300 \mu\text{m}$ ) in the first layer causes errors, which propagate till the highest layer.

the error is limited to a small region, but a small error can get worse in higher layers. Plots shown here are the result of a winding simulation. For more Informations see [3].

One important point is the fluctuating diameter of the scintillating fibre. The trend of the diameter shows thick regions up to  $500 \mu\text{m}$ . These thick regions, called bumps, cause a wrong positioning of the neighbouring fibres. An example of such a error is showed in Fig. 2.




Figure 3: Cantle of a cross section of a fibre mat (12 to 16 mm). Due to a missing fibre in the second layer, fibres from the higher layers fill up the empty space.

Another problem are fibres, who skip a notch and create therefore an empty space. These empty spaces will be filled up by fibres belong to a higher layer actually. This will cause there an empty space too (see Fig. 3).

On the basis of this influences (and many more) a good positioning of the fibres during the winding process has to be guaranteed to receive a good fibre mat. Unfortunately a scintllating fibre without bumps can't be delivered by the manufacturer. As a result of this bumps which cause problems have to be cut out. To make a statement about the positioning of the fibres and if a bump has to be cut out, a camera system will be used to monitor the fibres exactly.

## 4 Hardware

To ensure a right positioning of the fibres in the fibre mat a setup consisting of an industrial camera and a lens with a big magnification is used. A scheme of the setup can found in Fig. 4. Die Camera system is mounted on the same slide as the positioning spool. As a result the camera is moving along the width of the wheel and monitors always the current fibre. Furthermore the camera will have a tangential look an the wheel. A schematic picture of the camera is shown in Fig. 5. The fibres of the first layer are guided by the threat in the wheel and are well positioned. The dark blue fibre is the current one and should be monitored very precisely.

Despite of the many influences which have a bearing on the fibre positioning, there are only two different effects which can be observed during the winding process. On the one hand a fibre can jump in the wrong threat an leave an empty space (see Fig. 6(a)). On the other hand a fibre is able to lie down in the next layer (see Fig. 6(b)).

A picture of the current hardware setup is shown in Fig. 7. The camera can be adjusted by a ball head. Unfortunately the lens has no possibilty to adjust the focus, so that another slide is used for this.




Figure 4: Scheme of the camera setup on the winding machine. The camera (green) will be placed on the same slide as the positioning spool and look tangential on the wheel.



Figure 5: Scheme of the view if the camera looks tangential on the wheel. Fibres in the first layer are guided by the threat in the wheel. The current fibre is marked in dark blue.

## 68 5 Software

69 The picture of the camera is supposed to be controlled with a pattern recognition software.  
 70 This insures, that no person has to be present the whole winding time and have a look on  
 71 the camera picture.

72 For this reason a pattern recognition software based on the open source library *OpenCV*.

## 73 6 Results

74 Show results of the working software.




Figure 6: Two different defects which can occur during the winding process. In (a) the current fibre jumped in the wrong thread and leave an empty space. (b) shows a fibre lying in the wrong layer.




Figure 7: Camera setup mounted on the winding machine.

## 7 Summary

Short summary

## References

- [1] LHCb collaboration, *LHCb Tracker Upgrade Technical Design Report*, CERN-LHCC-2014-001. LHCb-TDR-015.
- [2] R. Ekelhof and J. Mueller, *Fibre Mat Production Dortmund*, Tech. Rep. LHCb-INT-2014-046. CERN-LHCb-INT-2014-046, CERN, Geneva, Nov, 2014.
- [3] J. Mueller, *Winding Simulation*, tech. rep.