

DATA

Source: <https://archive.ics.uci.edu/dataset/165/concrete+compressive+strength>

Description: Experimental laboratory test results recording the development of compressive strength in standard Portland cement concrete mixtures as a function of curing time.

x and y variables:

Independent variable x : Curing Age (Days)

Dependent variable y :Compressive Strength MPa

Observation	Curing Age, x (Days)	Compressive Strength, y (MPa
1	3	12.5
2	3	14.1
3	7	21
4	7	23.4
5	14	29.8
6	14	31.2
7	21	36.5
8	21	38
9	28	42.1
10	28	44.3
11	35	46
12	42	48.5
13	56	51.2
14	90	54
15	100	55.6