

PHYSICOCHEMICAL PROPERTIES OF GUM ARABIC

*¹F. Inegbedion, ²V. U. Okojie and ²F. Egharevba

1. Department of Polymer Technology, Auchi Polytechnic Auchi

2. Department of Chemistry, Ambrose Alli University Ekpoma

Corresponding Author Email: festusinegbedion1@gmail.com

ABSTRACT

Gum Arabic is harvested commercially from wild trees throughout the Sahel from Senegal and Sudan to Somalia and in the northern part of Nigeria. Clumps of gum Arabic were collected and dirt particles were removed, the samples were dried and grounded to fine powder. The Physicochemical properties of gum Arabic was determined using standard methods and the values obtained showed; Moisture content $6.9\% \pm 5$, Soluble content 90.6%, Viscosity $5.45 \pm 3 \text{Ns/m}^2$, Ash content $3.2 \pm 4\%$, Zinc 3mg/kg, Iron 41mg/kg ± 5 , Manganese 48.2mg/kg ± 5 and Copper 33.3mg/kg ± 2 . The gum also contains carbohydrate 0.3ppm ± 2 , protein 0.75ppm ± 2 , starch 0.0076 ± 10 and nitrogen 0.12ppm ± 5 . It was observed that the gum does not contain cadmium and nickel.

Keywords: Gum Arabic, physicochemical, hydrocolloid

INTRODUCTION

Acacia Senegal, popularly known as gum Arabic is a leguminous tree crop which belongs to the family Mimisaceae. This family contains over 300 known species including Acacia Senegal and Acacia Seyal and are the most commercially exploited species. Both species are considered as the important economic Acacia plant in the Sudan-Ssahelian ecological zones covering not less than eleven states in the northern part of Nigeria. The species produces the best grade of gum in commercial quantity in Nigeria and it is an important source of foreign exchange earnings (Aghughu, 1998).

Acacia gum is the dried exudates obtained by tapping the stems and branches of acacia Senegal or other related species. The gum has various uses in the food, textiles, prints and

pharmaceutical industries in the world. The trees are planted in shelterbelt to check wind and soil erosion, hence it is used to fight against desert encroachment (Aghughu, et al., 2005). The plant adds nitrogen to the soil through its nitrogen fixing ability and leaf litter fall thereby improving soil fertility (Cossalter, 1991). Its pods, seeds and leaves are excellent browse and folder for livestock (Scholte, 1992).

Gum Arabic is harvested commercially from wild trees throughout the Sahel from Senegal and Sudan to Somalia, although it has been historically cultivated in Arabia and West Asia. Gum Arabic is a complex mixture of polysaccharides and glycoproteins that is used primarily in the food industry as a stabilizer. It is edible and is a key ingredient in traditional lithography and used in printing, paint production, glue, cosmetics and various industrial applications, including viscosity control in inks and in textile industries, although less expensive materials compete with it for many of these roles. (Smolinske, 1992).

Gum Arabic is unique among the natural hydrocolloid because of its extremely high solubility in water. Most common gums cannot be dissolved in water at concentration higher than about 5% because of their very high viscosities. Gum Arabic is insoluble in oils and in most organic solvents. Whereas most gums form highly viscous solution at low concentration of about 1-5%, high viscosities are not obtained with gum Arabic until concentration of about 40-50% is obtained.

Technically, gum Arabic is classed in a group of substances called arabinogalactan protein. Eighteen different amino acids have been identified in acacia Senegal, although only four comprises more than 10% of the protein. The gum also comprises essentially a complex polysaccharide, consisting mostly of galactose, arabinose, rhamnose and glucuronic acid (William and Idris, 2000). Gum Arabic is useful as hydrocolloid, emulsifier, texturizer and film-former (Phillip and Ogasawara, 2007).

Substances frequently called gums are hydrocarbons of high molecular mass; others are petroleum products, rubber latex, synthetic polymeric gums, balms and resins. Recently, the term “gum” as technically employed in the industry, refers to plant or microbial polysaccharides and their derivatives that are capable of forming dispersions in cold or hot water, producing viscous mixtures or solutions (De Pinto et al., 1995).

MATERIALS AND METHODS

SAMPLING

The sample was harvested from Acacia Senegal. The stem of the specie was cut and the gum oozed out and dried at room temperature of 30°C±5 to form clumps. The clumps were collected and particles such as sand, sticks and dirt were removed from the clumps and preserved with formaldehyde to avoid micro organism infestation which may cause biodegradation of the gum. The samples were dried for easy grounding. The dried samples were grounded to fine power and kept in an air-tight container.

Materials used include; Ethanol, tetraoxosulphate (VI) acid, toluene, anthrone reagent, hydrochloric acid, sodium carbonate, alkaline sodium phenate, sodium hypochlorite, sodium potassium tartrate, dry ammonium sulphate and sodium sulphate. They were supplied and used as standard analytical reagents.

METHODS

Metal contents was determined using the Atomic Absorption Spectrophotometer (AAS), Sugar contents and Carbohydrate contents were determined using Anthrone method, Viscosity was determined using Oswald Viscometer, pH was determined using the Jenway 3510 pH meter. Other properties such as Ash content, Moisture content, Insoluble matter, Soluble matter, Nitrogen and Protein were determined using standard methods.

RESULTS AND DISCUSSION

RESULTS