

Page 1: Environmental Corrosion Standards

Overview of atmospheric oxidation and corrosion prevention in fluid transmission lines and structural steel.

Page 2: Rust & Oxidation Treatment

Defect Type: Surface Corrosion and Rust.

Symptom: Brownish oxide flakes, surface pitting, or paint degradation on metallic piping.

Action Required: Scrape loose rust off using wire brush or sandblasting. Apply chemical rust converter followed by two coats of zinc-rich primer paint. Inspect wall thickness with ultrasonic gauge if pitting exceeds 1mm depth. Priority: Medium.